

**THE CITY OF KENOSHA, WISCONSIN
REQUEST FOR PROPOSAL TO REMOVE AND DISPOSE
OF ASBESTOS CONTAINING MATERIAL, RAZE STRUCTURE(S),
AND RESTORE LOT(S) WITH INSTRUCTIONS TO PROPOSERS**

Proposal No. 02-18

ISSUED: Thursday, February 8, 2018

The City of Kenosha, Wisconsin, will receive proposals for the removal and disposal of Asbestos Containing Material, the razing of the structure(s), and the restoration of the lot(s) described below in accordance with this Request for Proposal with Instructions to Proposers, the Detailed Description of Work to be Performed, the Environmental Inspection Reports, the General Specifications and Conditions, and the Contract.

DEADLINE FOR RECEIPT OF PROPOSAL. February 27, 2018 @ 2:30 P.M.

PROPOSAL OPENING. February 27, 2018 @ 2:30 P.M.

CITY OFFICE WHERE FILED. Department of Finance, Municipal Building, Room 208, 625 - 52nd Street, Kenosha, Wisconsin 53140.

FORM OF PROPOSAL. Proposals must be submitted sealed, on City forms, legible and fully complete in all respects, showing the date and time of the proposal opening on the outside of the sealed proposal. The City reserves the right to reject any proposal which the City deems incomplete.

FOR MORE INFORMATION. Contact Zohrab Khaligian, Community Development Specialist, Community Development and Inspections, 625 52nd Street, Room 308, Kenosha, Wisconsin 53140, (262) 653-4030, zkhaligian@kenosha.org

ASBESTOS REMOVAL AND DISPOSAL. Environmental Inspection Reports indicating the description, location and quantity of Category I, Category II, and Regulated Asbestos Containing Material (RACM) to be removed and disposed of are attached. The Proposer shall be certified by the Wisconsin Department of Health Services to perform asbestos removal and disposal or shall be required to subcontract with an entity certified by the Wisconsin Department of Health Services to perform asbestos removal and disposal. Proof of certification shall be provided to the City. The Proposer shall file all reports regarding asbestos removal and disposal required by Federal and State law, rules and regulations. All Category I, Category II, and Regulated Asbestos Containing Material shall be removed prior to razing the structure(s).

STRUCTURE(S) TO BE RAZED AND LOT(S) TO BE RESTORED.

Address: 1505 60th Street, Kenosha, Wisconsin
Tax Parcel No.: 05-123-06-203-003
Description: Two story, one unit residential frame structure consisting of approximately 2,300 square feet with a basement and attic.

Address: 1727 52nd Street, Kenosha, Wisconsin
Tax Parcel No.: 12-223-31-326-003
Description: Two story, two unit residential brick structure consisting of approximately 3,272 square feet with a basement and attic.

Address: 6720 25th Avenue, Kenosha, Wisconsin
Tax Parcel No.: 01-122-01-404-028
Description: Two story, four unit residential frame structure consisting of approximately 2,560 square feet with a basement and attic.

CONTRACT REQUIRED. The Proposer selected to perform the Work will be required to execute a Contract and related documents on City forms as a condition of performing the Work. All Work is to be performed in accordance with the Contract. A sample of the Contract format is available for inspection in the City Attorney's Office, 625-52nd Street, Room 201, Kenosha, Wisconsin 53140. The provisions of the Contract shall include:

1. A time limit for completion of the Work with liquidated damages of Two Hundred Dollars (\$200.00) per day for delay where a time extension was not granted.
2. One (1) year warranty on the Work performed.
3. Performance and Payment Bond in the amount of the Contract.
4. Insurance from a company licensed to do business in the State of Wisconsin and having a minimum AM Best Financial Strength Rating of "A" or better with the following minimum limits:
 - a. **Commercial General Liability**
\$1,000,000.00 Each Occurrence
\$2,000,000.00 Aggregate
 - b. **Automobile Liability (owned, non-owned, leased)**
\$1,000,000.00 Combined Single Limit
 - c. **Pollution Legal Liability**
\$2,000,000.00 Each Loss where asbestos removal, environmental process,

abatement, remediation or disposal in a Federal or State licensed or permitted disposal site is required.

d. Worker's Compensation: Statutory Limits

Employer's Liability

\$100,000.00 Each Accident

\$100,000.00 Disease, Each Employee

\$500,000.00 Disease, Policy Limit

e. Umbrella Liability

\$3,000,000.00. The umbrella liability policy shall not contain any exclusions or exceptions not identified in the Commercial General Liability, Automobile Liability or Pollution Legal Liability policies.

f. Certificate of Insurance

The insurance coverages listed above shall be verified by a Certificate of Insurance issued to the City of Kenosha as Certificate Holder and shall provide that should any of the described policies be canceled or materially changed before the expiration date thereof, the issuing insurer will mail thirty (30) days written notice to the Certificate Holder before any cancellation or material change takes effect.

g. Additional Insured, Primary Insurance and Waiver of Subrogation Endorsements

The City of Kenosha shall be named as an additional insured with respect to the coverages required by Sections 4(a), 4(b), 4(c), and 4(e) listed above and the City of Kenosha shall be provided with the endorsement certifying that the City of Kenosha is an additional insured with respect to said policies. The coverages required by Sections 4(a), 4(b), 4(c), and 4(e) listed above shall be primary. The City shall be provided a primary insurance endorsement certifying that the insurance coverages listed above are provided on a primary and noncontributory basis. The City shall also be provided with a waiver of subrogation endorsement.

h. Insurance Compliance

Each of the minimum insurance limits listed above must be met. The City reserves the right to reject any Proposal which does not meet each of the minimum insurance limits listed above.

5. Release/waiver of liens.

6. Obtaining City Raze Permit; Street Opening/Occupying Permit (where applicable); Erosion Control Permit, Driveway Approach, Sidewalk, or Curb and Gutter Permit (where

applicable), and Notice to or Permit from the Wisconsin Department of Natural Resources.

7. Utility locations, clearances, hookups or cutoffs.
8. Removal of building materials and restoration of the site.

INSPECTION AND REVIEW OF SITE AND CITY DATA. Each Proposer has an obligation to examine the site(s) upon which the Work will be performed to assess conditions and to review any City furnished data.

The City will open the structure(s) and lot(s) on February 20, 2018 to give Proposers an opportunity to inspect the structure(s) and to ask staff questions. Inspections will commence at 1505 60th Street at 10:00 A.M. The City will not accept a Proposal from any Proposer who has not signed in indicating that the Proposer has inspected the structure(s) and lot(s), or has not made other inspection arrangements with City staff.

LISTING OF SUBCONTRACTORS, MAJOR MATERIAL SUPPLIERS (OVER \$5,000.00), AND DISPOSAL SITES. Proposals shall include on the attached City form a complete list of all subcontractors, including all subcontractors responsible for the removal and disposal of any Category I, Category II, and Regulated Asbestos Containing Material (RACM), together with a complete list of all major material suppliers which are suppliers furnishing over \$5,000.00 in materials. The class of Work to be performed by each subcontractor and major material supplier shall also be provided. The completed list shall also include the disposal sites to be used and where Federal or State law requires certain regulated materials to be disposed of in a Federal or State licensed or permitted disposal site, then such disposal sites shall be used and their License/Permit Number included. The list must be approved by the City and cannot be altered after submission without the written consent of the City. The City reserves the right to reject any Proposal which does not comply with this Paragraph or if in the City's determination any listed subcontractor or major material supplier is deemed not appropriately qualified.

ENVIRONMENTAL MATTERS. Where the Work requires environmental process, abatement, remediation or disposal in a Federal or State licensed or permitted disposal site, the Proposer may propose alternate methods of doing the Work with the cost of each alternative separately noted.

AWARD OF CONTRACT. The City will enter into a Contract with the Proposer deemed most qualified. In making this determination, the City will consider with respect to each Proposer: general qualifications, special expertise, time in which the Work can be performed, financial ability to perform the Work, environmental experience and responsibility (where applicable), work record and history, and experience in projects of a similar magnitude.

The City reserves the right to reject unqualified or nonconforming Proposals, to reject all Proposals and request new Proposals, to accept Proposal(s) if advantageous to the City, or to select the most qualified Proposal and negotiate a Contract. This project is not a public construction contract under

Wisconsin law and the City is not required to award the Contract to the lowest responsible Proposer.

COMMENCEMENT AND DILIGENT COMPLETION OF WORK. The Proposer selected to perform the Work will conduct the Work diligently until fully complete in accordance with the Contract. The time schedule for obtaining a Raze Permit and time of performance is stated in the General Specifications and Conditions.

EXECUTION OF DOCUMENTS. Documents which are required to be executed by the Proposer shall be executed as follows:

1. Corporations. By the President and one (1) other officer, preferably the Secretary.
2. Limited Liability Companies. By a Member, if member managed or the Manager if manager managed.
3. Partnerships. By each general partner, unless the partnership agreement provides otherwise.
4. Sole Proprietors. By each named individual.

Any exception to the above must be approved by the City Attorney who may require such documents as may be necessary to consider an exception.

DOCUMENTS TO BE SUBMITTED. Proposers shall submit the following documents, on City forms, in the course of making a Proposal.

1. Proposal.
2. Affidavit of Organization and Authority and Careful Inspection of Site and Preparation of Proposal.
3. List of Subcontractors and Major Material Suppliers (including disposal site with DNR Permit Number, if any).

The Detailed Description of Work to be Performed, the Environmental Inspection Reports, and the General Specifications and Conditions for the project follow.

**THE CITY OF KENOSHA, WISCONSIN
REQUEST FOR PROPOSAL TO REMOVE AND DISPOSE
OF ASBESTOS CONTAINING MATERIAL, RAZE STRUCTURE(S),
AND RESTORE LOT(S)**

Proposal No. 02-18

DETAILED DESCRIPTION OF WORK TO BE PERFORMED

The following tasks which are hereafter referred to as the "Work" are to be performed in accordance with the Request for Proposal with Instructions to Proposers, the Environmental Inspection Reports, the General Specifications and Conditions, and the Contract.

1505 60TH STREET, 1727 52ND STREET & 6720 25TH AVENUE

Raze and remove all debris from the entire structures including basement walls and floors, remove and replace any sidewalk and curbing as marked by City, remove and cap at curb all sanitary sewer and water laterals, and obtain necessary Federal, State and local permits.

1505 60TH STREET

1. Remove and dispose of all Category I, Category II and other Regulated Asbestos Containing Materials (RACM) as identified in attached NESHAP
2. Remove front and rear porches
3. Remove concrete driveway approach on north side of parcel and replace with full head concrete curb & gutter
4. Remove gravel driveway
5. Remove concrete walkway on north side of parcel and concrete pad on south side of parcel
6. Remove all trees, shrubs, bushes and other foliage as marked by the City or that need to be removed during raze


1727 52ND STREET

1. ALL CATEGORY I, CATEGORY II AND OTHER REGULATED ASBESTOS CONTAINING MATERIALS (RACM) AS IDENTIFIED IN ATTACHED NESHAP HAVE BEEN REMOVED AND DISPOSED OF
2. Remove detached sign on north side of parcel
3. Remove asphalt parking lot and concrete walkway abutting the east side of parcel
4. Remove two concrete driveway approaches on north side of parcel and north side of parking lot and replace with full head concrete curb & gutter
5. Remove all concrete and asphalt paving and curbing surrounding structure
6. Remove yellow parking bollard on south east corner of parcel

6720 25TH AVENUE

1. Remove and dispose of all Category I, Category II and other Regulated Asbestos Containing Materials (RACM) as identified in attached NESHAP
2. Remove front and rear porches and stairs
3. Remove driveway approach on east side of parcel and replace with full head concrete curb & gutter
4. Remove concrete walkway on east and north sides of parcel
5. Remove all trees, shrubs, bushes and other foliage
6. Remove stockade fencing on south and west sides of parcel and railroad ties on west side of parcel

General Location Map



 Subject Property - 1505 60th Street





821 Corporate Court
Waukesha, WI
phone: 262.521.2125
fax: 262.521.2471
intertek.com/building
psiusa.com

November 2, 2017

Mr. Mark Willing
Purchasing Manager
City of Kenosha- Department of Finance
Municipal Building- Room 208
625 52nd Street
Kenosha, Wisconsin 53140

Re: NESHAP Asbestos Survey at
Multi-Family Residence
1505 60th Street
Kenosha, Wisconsin
PSI Project No. 00541478

Dear Mr. Willing:

In accordance with our agreement dated May 15, 2012, Professional Service Industries, Inc. (PSI), has performed an Asbestos Survey of the above-referenced property to identify all Asbestos-Containing Materials (ACM) including Category I and Category II non-friable ACM. Below, please find a discussion of our survey and results.

Facility Description

The facility included in this National Emissions Standard for Hazardous Air Pollutants (NESHAPs) Asbestos Survey was a two-story residential structure with basement and attic. At the time of PSI's survey, the building was vacant.

Survey Intent

This asbestos survey was intended to meet the requirements of the NESHAP for Asbestos demolition or renovation. The survey included a thorough inspection of all areas of demolition or renovation. PSI's inspection team identified, quantified and assessed the condition of all Regulated Asbestos Containing Material (RACM), Category I non-friable ACM and Category II non-friable ACM. A hand pressure test was used to determine whether the material was friable.

Representative samples were collected and submitted to an accredited laboratory for analysis by Polarized Light Microscopy. Reports of Analysis are attached along with Chain of Custody documentation, Bulk Sample Logs, Site Layout Diagrams, and Inspector and Laboratory Certifications.

Findings

Asbestos-containing materials were discovered during this asbestos survey. Assumed asbestos-containing materials were identified and included electrical boxes. The table below details the findings of this survey.

Table 1-Asbestos Containing Materials

Material Description	Locations in Facility	Total Quantity	RACM, Cat. I or Cat. II	Friable (Y/N)	Condition
<i>Flue Packing</i>	<i>Room 01</i>	<i>2 SF</i>	<i>RACM</i>	<i>Y</i>	<i>Good</i>
<i>Paper Insulation</i>	<i>Room 01</i>	<i>1 SF</i>	<i>RACM</i>	<i>Y</i>	<i>Damaged</i>
<i>Duct Wrap</i>	<i>Rooms 105 and STWL1</i>	<i>70 SF</i>	<i>RACM</i>	<i>Y</i>	<i>Damaged</i>
<i>Pipe Caulk – Gray</i>	<i>Room 101</i>	<i>1 SF</i>	<i>Cat. I</i>	<i>N</i>	<i>Good</i>
<i>12" x 12" Gray Floor Tile (Mastic Negative)</i>	<i>Rooms 102 and 103</i>	<i>170 SF</i>	<i>Cat. I</i>	<i>N</i>	<i>Good</i>
<i>Window Pane Glazing</i>	<i>Room STWL3 and Exterior</i>	<i>44 SF (44 Windows)</i>	<i>Cat. I</i>	<i>N</i>	<i>Good</i>
<i>Exterior Vent Caulk – Beige</i>	<i>Exterior (South Side of Building)</i>	<i>1 SF</i>	<i>Cat. I</i>	<i>N</i>	<i>Good</i>
<i>Roof Flashing</i>	<i>Roof</i>	<i>50 SF</i>	<i>Cat. I</i>	<i>N</i>	<i>Good</i>
<i>Electrical Boxes (Assumed Transite Components)</i>	<i>Rooms 02, 100 and Exterior</i>	<i>5 Boxes</i>	<i>Cat. II</i>	<i>N</i>	<i>Good</i>

SF=Square Feet

EA=Each

Warranty

The information contained in this report is based upon the data furnished by the Client and observations and test results provided by PSI. These observations and results are time dependent, are subject to changing site conditions, and revisions to Federal, State and local regulations.

PSI warrants that these findings have been promulgated after being prepared in general accordance with generally accepted practices in the asbestos industry. PSI also recognizes that raw laboratory test data are not usually sufficient to make all abatement and management decisions.

As directed by the client, PSI did not provide any service to investigate or detect the presence of moisture, mold or other biological contaminants in or around any structure, or any service that was designed or intended to prevent or lower the risk of the occurrence of the amplification of the same. Client acknowledges that mold is ubiquitous to the environment with mold amplification occurring when building materials are impacted by moisture. Client further acknowledges that site conditions are outside of PSI's control, and that mold amplification will

likely occur, or continue to occur, in the presence of moisture. As such, PSI cannot and shall not be held responsible for the occurrence or recurrence of mold amplification.

This report was prepared pursuant to the contract PSI has with the City of Kenosha. That contractual relationship included an exchange of information about the subject site that was unique and between PSI and its client and serves as the basis upon which this report was prepared. Because of the importance of the communication between PSI and its client, reliance or any use of this report by anyone other than the City of Kenosha, for whom it was prepared, is prohibited and therefore not foreseeable to PSI.

Reliance or use by any such third party without explicit authorization in the report does not make said third party a third party beneficiary to PSI's contract with the City of Kenosha. Any such unauthorized reliance on or use of this report, including any of its information or conclusions, will be at third party's risk. For the same reasons, no warranties or representations, expressed or implied in this report, are made to any such third party.

No other warranties are implied or expressed.

Unidentifiable Conditions

This report is necessarily limited to the conditions observed and to the information available at the time of the work. Due to the nature of the work, there is a possibility that there may exist conditions which could not be identified within the scope of work or which were not apparent at the time of our site work. This report is also limited to information available from the client at the time it was conducted. The report may not represent all conditions at the subject site as it only reflects the information gathered from specific locations.

Thank you for choosing PSI as your consultant for this project. If you have any questions, or if we can be of additional service, please call us at 262.521.2125.

Respectfully submitted,
PROFESSIONAL SERVICE INDUSTRIES, INC.



Matt Geldmeyer
WI Asbestos Inspector #AII-16803



Michael Tjaden
Principal Consultant

Appendices

- A. Report of Bulk Sample Analysis for Asbestos/Chain of Custody
- B. Asbestos Bulk Sample Log
- C. Site Layout Drawings
- D. Inspector & Company Certifications



October 31, 2017

PSI
821 Corporate Ct.
Waukesha, WI 53189

CLIENT PROJECT: Kenosha- 1505 60th St; 0541478
CEI LAB CODE: A17-15269

Dear Customer:

Enclosed are asbestos analysis results for PLM Bulk samples received at our laboratory on October 27, 2017. The samples were analyzed for asbestos using polarizing light microscopy (PLM) per the EPA 600 Method.

Sample results containing >1% asbestos are considered asbestos-containing materials (ACMs) per EPA regulatory requirements. The detection limit for the EPA 600 Method is <1% asbestos by weight as determined by visual estimation.

Thank you for your business and we look forward to continuing good relations. If you have any questions, please feel free to call our office at 919-481-1413.

Kind Regards,

A handwritten signature in black ink, appearing to read "Tianbao Bai".

Tianbao Bai, Ph.D., CIH
Laboratory Director





ASBESTOS ANALYTICAL REPORT
By: Polarized Light Microscopy

Prepared for

PSI

CLIENT PROJECT: Kenosha- 1505 60th St; 0541478

CEI LAB CODE: A17-15269

TEST METHOD: EPA 600 / R93 / 116 and EPA 600 / M4-82 / 020

REPORT DATE: 10/31/17

TOTAL SAMPLES ANALYZED: 139

SAMPLES >1% ASBESTOS: 21

TEL: 866-481-1412

www.ceilabs.com



Asbestos Report Summary

By: POLARIZING LIGHT MICROSCOPY

PROJECT: Kenosha- 1505 60th St; 0541478

CEI LAB CODE: A17-15269

METHOD: EPA 600 / R93 / 116 and EPA 600 / M4-82 / 020

Client ID	Layer	Lab ID	Color	Sample Description	ASBESTOS %
1		A2531249	Tan	MB	None Detected
2		A2531250	Tan	MB	None Detected
3		A2531251	Tan	MB	None Detected
4		A2531252	Gray	Mbm	None Detected
5		A2531254	Gray	Mbm	None Detected
6		A2531255	Gray	Mbm	None Detected
7		A2531256	Brown,Black	Mfbi	None Detected
8		A2531257	Brown,Black	Mfbi	None Detected
9		A2531258	Brown,Black	Mfbi	None Detected
10		A2531259	Gray	Tfp	None Detected
11		A2531260	Gray	Tfp	Chrysotile 2%
12		A2531261	Gray	Tfp	None Detected
13		A2531262	Gray,White	Tpi	Chrysotile 65%
14		A2531263	Gray,White	Tpi	Chrysotile 65%
15		A2531264	Gray,White	Tpi	Chrysotile 65%
16		A2531265	Off-white,Brown	Tdw	Chrysotile 35%
17		A2531266	Off-white	Tdw	Chrysotile 65%
18		A2531267	Off-white	Tdw	Chrysotile 65%
19		A2531268	Black	MAS	None Detected
20		A2531269	Black	MAS	None Detected
21		A2531270	Black	MAS	None Detected
22		A2531271	Tan,Pink	Msf	None Detected
23		A2531272	Tan,Pink	Msf	None Detected
24		A2531273	Tan,Pink	Msf	None Detected
25		A2531274	Black	Mstp	None Detected
26		A2531275	Black	Mstp	None Detected
27		A2531276	Black	Mstp	None Detected
28		A2531277	Gold	Tvi	None Detected
29		A2531278	Gold	Tvi	None Detected
30		A2531279	Gold	Tvi	None Detected
31		A2531280	Cream	Mflc	None Detected



Asbestos Report Summary

By: POLARIZING LIGHT MICROSCOPY

PROJECT: Kenosha- 1505 60th St; 0541478

CEI LAB CODE: A17-15269

METHOD: EPA 600 / R93 / 116 and EPA 600 / M4-82 / 020

Client ID	Layer	Lab ID	Color	Sample Description	ASBESTOS %
32		A2531281	Cream	Mflc	None Detected
33		A2531282	Cream,White	Mflc	None Detected
34		A2531283	Gray,Red	Mflyr	None Detected
35		A2531284	Gray,Red	Mflyr	None Detected
36		A2531285	Gray,Red	Mflyr	None Detected
37		A2531286	Gray,White	Mscti	None Detected
38		A2531287	Gray,White	Mscti	None Detected
39		A2531288	Gray,White	Mscti	None Detected
40		A2531289	Gray,Green	Mdwc	None Detected
41		A2531290	Gray,Yellow	Mdwc	None Detected
42		A2531291	Gray,Blue	Mdwc	None Detected
43	Layer 1	A2531292	Tan	Mfb	None Detected
	Layer 2	A2531292	Black	Mfb	None Detected
44	Layer 1	A2531293	Tan	Mfb	None Detected
	Layer 2	A2531293	Black	Mfb	None Detected
45	Layer 1	A2531294	Tan	Mfb	None Detected
	Layer 2	A2531294	Black	Mfb	None Detected
46		A2531295	White,Tan	Mzb	None Detected
47		A2531296	White,Tan	Mzb	None Detected
48		A2531297	White,Tan	Mzb	None Detected
49		A2531298	White	Mzbm	None Detected
50		A2531299	White	Mzbm	None Detected
51		A2531300	White	Mzbm	None Detected
52		A2531301	Gray,Black	Mslk	None Detected
53		A2531302	Gray,Black	Mslk	None Detected
54		A2531303	Gray,Black	Mslk	None Detected
55		A2531304	Gray	Mpc	Chrysotile 10%
56		A2531305	Gray	Mpc	Chrysotile 10%
57		A2531306	Gray	Mpc	Chrysotile 10%
58		A2531307	Beige	Mvfe	None Detected
59		A2531308	Beige	Mvfe	None Detected



Asbestos Report Summary

By: POLARIZING LIGHT MICROSCOPY

PROJECT: Kenosha- 1505 60th St; 0541478

CEI LAB CODE: A17-15269

METHOD: EPA 600 / R93 / 116 and EPA 600 / M4-82 / 020

Client ID	Layer	Lab ID	Color	Sample Description	ASBESTOS %
60		A2531309	Beige	Mvfe	None Detected
61		A2531310	Gray,Green	Mflyg	None Detected
62		A2531311	Gray,Green	Mflyg	None Detected
63		A2531312	Gray,Green	Mflyg	None Detected
64	Layer 1	A2531313	White	Sp2	None Detected
	Layer 2	A2531313	White	Sp2	None Detected
	Layer 3	A2531313	Gray	Sp2	None Detected
65	Layer 1	A2531314	White	Sp2	None Detected
	Layer 2	A2531314	Gray	Sp2	None Detected
66	Layer 1	A2531315	White	Sp2	None Detected
	Layer 2	A2531315	White	Sp2	None Detected
	Layer 3	A2531315	Gray	Sp2	None Detected
67		A2531316A	Gray	Mf12y	Chrysotile 5%
		A2531316B	Clear	Mf12y	None Detected
68		A2531317A	Gray	Mf12y	Chrysotile 5%
		A2531317B	Clear	Mf12y	None Detected
69		A2531318A	Gray	Mf12y	Chrysotile 5%
		A2531318B	Clear	Mf12y	None Detected
70		A2531319	Tan	Mflt	None Detected
71		A2531320	Tan	Mflt	None Detected
72		A2531321	Tan	Mflt	None Detected
73		A2531322	Gray	Mctm	None Detected
74		A2531323	Gray	Mctm	None Detected
75		A2531324	Gray	Mctm	None Detected
76		A2531325	Gray	Mctg	None Detected
77		A2531326	Gray	Mctg	None Detected
78		A2531327	Gray	Mctg	None Detected
79		A2531328	Off-white	Mwr	None Detected
80		A2531329	Off-white	Mwr	None Detected
81		A2531330	Off-white	Mwr	None Detected
82		A2531331	White,Tan	Mpg	None Detected



Asbestos Report Summary

By: POLARIZING LIGHT MICROSCOPY

PROJECT: Kenosha- 1505 60th St; 0541478

CEI LAB CODE: A17-15269

METHOD: EPA 600 / R93 / 116 and EPA 600 / M4-82 / 020

Client ID	Layer	Lab ID	Color	Sample Description	ASBESTOS %
83		A2531332	Gray,White	Mpg	Chrysotile 3%
84		A2531333	Gray,White	Mpg	Chrysotile 3%
85		A2531334	Black,Brown	Mrs	None Detected
86		A2531335	Black,Brown	Mrs	None Detected
87		A2531336	Black,Brown	Mrs	None Detected
88		A2531337	Black,Red	Mrs2	None Detected
89		A2531338	Black,Red	Mrs2	None Detected
90		A2531339	Black,Red	Mrs2	None Detected
91		A2531340	White	Mdce	None Detected
92		A2531341	White	Mdce	None Detected
93		A2531342	White	Mdce	None Detected
94		A2531343	White	Mwce	None Detected
95		A2531344	White	Mwce	None Detected
96		A2531345	White	Mwce	None Detected
97		A2531346	Gray	Mpce	None Detected
98		A2531347	Gray	Mpce	None Detected
99		A2531348	Gray	Mpce	None Detected
100		A2531349	White,Gray	Mvce	None Detected
101		A2531350	White,Gray	Mvce	None Detected
102		A2531351	White,Gray	Mvce	None Detected
103		A2531352	Beige,White	Mvce2	Chrysotile 3%
104		A2531353	Beige,White	Mvce2	Chrysotile 3%
105		A2531354	Beige,White	Mvce2	Chrysotile 3%
106		A2531355	Tan,Black	Mrs3	None Detected
107		A2531356	Tan,Black	Mrs3	None Detected
108		A2531357	Tan,Black	Mrs3	None Detected
109		A2531358	Green,Black	Mrs4	None Detected
110		A2531359	Green,Black	Mrs4	None Detected
111		A2531360	Green,Black	Mrs4	None Detected
112		A2531361	Gray,Black	Mrf	Chrysotile 10%
113		A2531362	Gray,Black	Mrf	Chrysotile 10%



Asbestos Report Summary

By: POLARIZING LIGHT MICROSCOPY

PROJECT: Kenosha- 1505 60th St; 0541478

CEI LAB CODE: A17-15269

METHOD: EPA 600 / R93 / 116 and EPA 600 / M4-82 / 020

Client ID	Layer	Lab ID	Color	Sample Description	ASBESTOS %
114		A2531363	Gray,Black	Mrf	Chrysotile 10%
115		A2531364	Black	Mrtp	None Detected
116		A2531365	Black	Mrtp	None Detected
117		A2531366	Black	Mrtp	None Detected
118	Layer 1	A2531367	White	Sp1	None Detected
	Layer 2	A2531367	Gray	Sp1	None Detected
119	Layer 1	A2531368	White	Sp1	None Detected
	Layer 2	A2531368	Gray	Sp1	None Detected
120	Layer 1	A2531369	White,Red	Sp1	None Detected
	Layer 2	A2531369	White	Sp1	None Detected
	Layer 3	A2531369	Gray	Sp1	None Detected
121	Layer 1	A2531370	White,Blue	Sp1	None Detected
	Layer 2	A2531370	Gray	Sp1	None Detected
122	Layer 1	A2531371	White	Sp1	None Detected
	Layer 2	A2531371	Gray	Sp1	None Detected
123	Layer 1	A2531372	White	Sp1	None Detected
	Layer 2	A2531372	Gray	Sp1	None Detected
124	Layer 1	A2531373	White	Sp1	None Detected
	Layer 2	A2531373	Gray	Sp1	None Detected
DH-1		A2531374	Black	Mstp	None Detected
DH-2		A2531375	Black	Mstp	None Detected
DH-3		A2531376	Black	Mstp	None Detected
DH-4		A2531377	White,Gray	Mvce	None Detected
DH-5		A2531378	White,Gray	Mvce	None Detected
DH-6		A2531379	White,Gray	Mvce	None Detected
DH-7		A2531380	Red,Gray	Mrs	None Detected
DH-8		A2531381	Red,Gray	Mrs	None Detected
DH-9		A2531382	Red,Gray	Mrs	None Detected
DH-10		A2531383	Black	Mrtp	None Detected
DH-11		A2531384	Black	Mrtp	None Detected
DH-12		A2531385	Black	Mrtp	None Detected



Asbestos Report Summary

By: POLARIZING LIGHT MICROSCOPY

PROJECT: Kenosha- 1505 60th St; 0541478

CEI LAB CODE: A17-15269

METHOD: EPA 600 / R93 / 116 and EPA 600 / M4-82 / 020

Client ID	Layer	Lab ID	Color	Sample Description	ASBESTOS %
DH-13		A2531386	White	Mhsce	None Detected
DH-14		A2531387	White	Mhsce	None Detected
DH-15		A2531388	White	Mhsce	None Detected



ASBESTOS BULK ANALYSIS

By: POLARIZING LIGHT MICROSCOPY

Client: PSI
 821 Corporate Ct.
 Waukesha, WI 53189

CEI Lab Code: A17-15269
Date Received: 10-27-17
Date Analyzed: 10-30-17
Date Reported: 10-31-17

Project: Kenosha- 1505 60th St; 0541478

ASBESTOS BULK PLM, EPA 600 METHOD

Client ID Lab ID	Lab Description	Lab Attributes	NON-ASBESTOS COMPONENTS			ASBESTOS %	
			Fibrous	Non-Fibrous			
1 A2531249	MB	Heterogeneous	80%	Binder	None Detected		
		Tan	20%	Silicates			
		Non-fibrous					
		Tightly Bound					
2 A2531250	MB	Heterogeneous	80%	Binder	None Detected		
		Tan	20%	Silicates			
		Non-fibrous					
		Tightly Bound					
3 A2531251	MB	Heterogeneous	80%	Binder	None Detected		
		Tan	20%	Silicates			
		Non-fibrous					
		Tightly Bound					
4 A2531252	Mbm	Heterogeneous	40%	Binder	None Detected		
		Gray	60%	Silicates			
		Non-fibrous					
		Tightly Bound					
5 A2531254	Mbm	Heterogeneous	40%	Binder	None Detected		
		Gray	60%	Silicates			
		Non-fibrous					
		Tightly Bound					
6 A2531255	Mbm	Heterogeneous	50%	Cellulose	35%	Tar	None Detected
		Gray	15%	Fiberglass			
		Non-fibrous					
		Tightly Bound					
7 A2531256	Mfbi	Heterogeneous	50%	Cellulose	35%	Tar	None Detected
		Brown,Black	15%	Fiberglass			
		Fibrous					
		Tightly Bound					



ASBESTOS BULK ANALYSIS

By: POLARIZING LIGHT MICROSCOPY

Client: PSI
 821 Corporate Ct.
 Waukesha, WI 53189

CEI Lab Code: A17-15269
Date Received: 10-27-17
Date Analyzed: 10-30-17
Date Reported: 10-31-17

Project: Kenosha- 1505 60th St; 0541478

ASBESTOS BULK PLM, EPA 600 METHOD

Client ID Lab ID	Lab Description	Lab Attributes	NON-ASBESTOS COMPONENTS				ASBESTOS %
			Fibrous		Non-Fibrous		
8 A2531257	Mfbi	Heterogeneous Brown,Black Fibrous Tightly Bound	50%	Cellulose	35%	Tar	None Detected
			15%	Fiberglass			
9 A2531258	Mfbi	Heterogeneous Brown,Black Fibrous Tightly Bound	45%	Cellulose	30%	Tar	None Detected
			15%	Fiberglass	10%	Metal Foil	
10 A2531259	Tfp	Heterogeneous Gray Non-fibrous Bound			35%	Binder	None Detected
					65%	Silicates	
11 A2531260	Tfp	Heterogeneous Gray Fibrous Bound	15%	Wollastonite	73%	Binder	2% Chrysotile
					10%	Silicates	
12 A2531261	Tfp	Heterogeneous Gray Fibrous Bound	15%	Wollastonite	75%	Binder	None Detected
					10%	Silicates	
13 A2531262	Tpi	Heterogeneous Gray,White Fibrous Bound			35%	Binder	65% Chrysotile
14 A2531263	Tpi	Heterogeneous Gray,White Fibrous Bound			35%	Binder	65% Chrysotile



ASBESTOS BULK ANALYSIS

By: POLARIZING LIGHT MICROSCOPY

Client: PSI
821 Corporate Ct.
Waukesha, WI 53189

CEI Lab Code: A17-15269
Date Received: 10-27-17
Date Analyzed: 10-30-17
Date Reported: 10-31-17

Project: Kenosha- 1505 60th St; 0541478

ASBESTOS BULK PLM, EPA 600 METHOD

Client ID Lab ID	Lab Description	Lab Attributes	NON-ASBESTOS COMPONENTS			ASBESTOS %
			Fibrous		Non-Fibrous	
15 A2531264	Tpi	Heterogeneous Gray,White Fibrous Bound	35%		Binder	65% Chrysotile
16 A2531265	Tdw	Heterogeneous Off-white,Brown Fibrous Bound	25%	Cellulose	30% Binder 10% Paint	35% Chrysotile
17 A2531266	Tdw	Heterogeneous Off-white Fibrous Bound			35% Binder	65% Chrysotile
18 A2531267	Tdw	Heterogeneous Off-white Fibrous Bound			35% Binder	65% Chrysotile
19 A2531268	MAS	Heterogeneous Black Fibrous Bound	30%	Cellulose	40% Tar 20% Gravel 10% Mica	None Detected
20 A2531269	MAS	Heterogeneous Black Fibrous Bound	30%	Cellulose	40% Tar 20% Gravel 10% Mica	None Detected
21 A2531270	MAS	Heterogeneous Black Fibrous Bound	30%	Cellulose	40% Tar 20% Gravel 10% Mica	None Detected



ASBESTOS BULK ANALYSIS

By: POLARIZING LIGHT MICROSCOPY

Client: PSI
 821 Corporate Ct.
 Waukesha, WI 53189

CEI Lab Code: A17-15269
Date Received: 10-27-17
Date Analyzed: 10-30-17
Date Reported: 10-31-17

Project: Kenosha- 1505 60th St; 0541478

ASBESTOS BULK PLM, EPA 600 METHOD

Client ID Lab ID	Lab Description	Lab Attributes	NON-ASBESTOS COMPONENTS				ASBESTOS %
			Fibrous		Non-Fibrous		
22 A2531271	Msf	Heterogeneous Tan,Pink Fibrous Bound	90%	Cellulose	10%	Binder	None Detected
23 A2531272	Msf	Heterogeneous Tan,Pink Fibrous Bound	90%	Cellulose	10%	Binder	None Detected
24 A2531273	Msf	Heterogeneous Tan,Pink Fibrous Bound	90%	Cellulose	10%	Binder	None Detected
25 A2531274	Mstp	Heterogeneous Black Fibrous Bound	80%	Cellulose	20%	Tar	None Detected
26 A2531275	Mstp	Heterogeneous Black Fibrous Bound	80%	Cellulose	20%	Tar	None Detected
27 A2531276	Mstp	Heterogeneous Black Fibrous Bound	80%	Cellulose	20%	Tar	None Detected
28 A2531277	Tvi	Heterogeneous Gold Non-fibrous Loose			95%	Vermiculite	None Detected
					5%	Non-Fibrous Debris	



ASBESTOS BULK ANALYSIS

By: POLARIZING LIGHT MICROSCOPY

Client: PSI
 821 Corporate Ct.
 Waukesha, WI 53189

CEI Lab Code: A17-15269
Date Received: 10-27-17
Date Analyzed: 10-30-17
Date Reported: 10-31-17

Project: Kenosha- 1505 60th St; 0541478

ASBESTOS BULK PLM, EPA 600 METHOD

Client ID Lab ID	Lab Description	Lab Attributes	NON-ASBESTOS COMPONENTS			ASBESTOS %	
			Fibrous	Non-Fibrous			
29 A2531278	Tvi	Heterogeneous	95%	Vermiculite	None Detected		
		Gold	5%	Non-Fibrous			
		Non-fibrous		Debris			
		Loose					
30 A2531279	Tvi	Heterogeneous	90%	Vermiculite	None Detected		
		Gold	10%	Non-Fibrous			
		Non-fibrous		Debris			
		Loose					
31 A2531280	Mflc	Heterogeneous	50%	Vinyl	None Detected		
		Cream	45%	Binder			
		Non-fibrous	5%	Mastic			
		Bound					
32 A2531281	Mflc	Heterogeneous	50%	Vinyl	None Detected		
		Cream	50%	Binder			
		Non-fibrous					
		Bound					
33 A2531282	Mflc	Heterogeneous	50%	Vinyl	None Detected		
		Cream,White	50%	Binder			
		Non-fibrous					
		Bound					
34 A2531283	Mflyr	Heterogeneous	30%	Cellulose	50%	Vinyl	None Detected
		Gray,Red	5%	Synthetic Fiber	10%	Tar	
		Fibrous			5%	Mastic	
		Bound					
35 A2531284	Mflyr	Heterogeneous	30%	Cellulose	50%	Vinyl	None Detected
		Gray,Red	5%	Synthetic Fiber	10%	Tar	
		Fibrous			5%	Mastic	
		Bound					



ASBESTOS BULK ANALYSIS

By: POLARIZING LIGHT MICROSCOPY

Client: PSI
 821 Corporate Ct.
 Waukesha, WI 53189

CEI Lab Code: A17-15269
Date Received: 10-27-17
Date Analyzed: 10-30-17
Date Reported: 10-31-17

Project: Kenosha- 1505 60th St; 0541478

ASBESTOS BULK PLM, EPA 600 METHOD

Client ID Lab ID	Lab Description	Lab Attributes	NON-ASBESTOS COMPONENTS				ASBESTOS %
			Fibrous		Non-Fibrous		
36 A2531285	Mflyr	Heterogeneous	30%	Cellulose	50%	Vinyl	None Detected
		Gray,Red	5%	Synthetic Fiber	10%	Tar	
		Fibrous			5%	Mastic	
		Bound					
37 A2531286	Mscti	Heterogeneous	60%	Cellulose	10%	Binder	None Detected
		Gray,White	10%	Fiberglass	15%	Perlite	
		Fibrous			5%	Paint	
		Bound					
38 A2531287	Mscti	Heterogeneous	60%	Cellulose	10%	Binder	None Detected
		Gray,White	10%	Fiberglass	15%	Perlite	
		Fibrous			5%	Paint	
		Bound					
39 A2531288	Mscti	Heterogeneous	60%	Cellulose	10%	Binder	None Detected
		Gray,White	10%	Fiberglass	15%	Perlite	
		Fibrous			5%	Paint	
		Bound					
40 A2531289	Mdwc	Heterogeneous	10%	Cellulose	75%	Gypsum	None Detected
		Gray,Green	5%	Fiberglass	5%	Silicates	
		Fibrous	3%	Talc	2%	Paint	
		Bound					
41 A2531290	Mdwc	Heterogeneous	10%	Cellulose	75%	Gypsum	None Detected
		Gray,Yellow	5%	Fiberglass	5%	Silicates	
		Fibrous	3%	Talc	2%	Paint	
		Bound					
42 A2531291	Mdwc	Heterogeneous	10%	Cellulose	75%	Gypsum	None Detected
		Gray,Blue	5%	Fiberglass	5%	Silicates	
		Fibrous	3%	Talc	2%	Paint	
		Bound					



ASBESTOS BULK ANALYSIS

By: POLARIZING LIGHT MICROSCOPY

Client: PSI
 821 Corporate Ct.
 Waukesha, WI 53189

CEI Lab Code: A17-15269
Date Received: 10-27-17
Date Analyzed: 10-30-17
Date Reported: 10-31-17

Project: Kenosha- 1505 60th St; 0541478

ASBESTOS BULK PLM, EPA 600 METHOD

Client ID Lab ID	Lab Description	Lab Attributes	NON-ASBESTOS COMPONENTS				ASBESTOS %
			Fibrous		Non-Fibrous		
43 Layer 1 A2531292	Mfb	Heterogeneous	90%	Cellulose	10%	Binder	None Detected
		Tan Fibrous Bound					
Layer 2 A2531292	Mfb	Heterogeneous	80%	Cellulose	20%	Binder	None Detected
		Black Fibrous Bound					
44 Layer 1 A2531293	Mfb	Heterogeneous	90%	Cellulose	10%	Binder	None Detected
		Tan Fibrous Bound					
Layer 2 A2531293	Mfb	Heterogeneous	80%	Cellulose	20%	Binder	None Detected
		Black Fibrous Bound					
45 Layer 1 A2531294	Mfb	Heterogeneous	90%	Cellulose	10%	Binder	None Detected
		Tan Fibrous Bound					
Layer 2 A2531294	Mfb	Heterogeneous	80%	Cellulose	20%	Binder	None Detected
		Black Fibrous Bound					
46 A2531295	Mzb	Heterogeneous			80%	Binder	None Detected
		White, Tan			10%	Silicates	
		Non-fibrous			10%	Paint	
		Tightly Bound					



ASBESTOS BULK ANALYSIS

By: POLARIZING LIGHT MICROSCOPY

Client: PSI
 821 Corporate Ct.
 Waukesha, WI 53189

CEI Lab Code: A17-15269
Date Received: 10-27-17
Date Analyzed: 10-30-17
Date Reported: 10-31-17

Project: Kenosha- 1505 60th St; 0541478

ASBESTOS BULK PLM, EPA 600 METHOD

Client ID Lab ID	Lab Description	Lab Attributes	NON-ASBESTOS COMPONENTS		ASBESTOS %
			Fibrous	Non-Fibrous	
47 A2531296	Mzb	Heterogeneous	80%	Binder	None Detected
		White, Tan	10%	Silicates	
		Non-fibrous	10%	Paint	
		Tightly Bound			
48 A2531297	Mzb	Heterogeneous	80%	Binder	None Detected
		White, Tan	10%	Silicates	
		Non-fibrous	10%	Paint	
		Tightly Bound			
49 A2531298	Mzbm	Heterogeneous	35%	Binder	None Detected
		White	65%	Silicates	
		Non-fibrous			
		Tightly Bound			
50 A2531299	Mzbm	Heterogeneous	35%	Binder	None Detected
		White	65%	Silicates	
		Non-fibrous			
		Tightly Bound			
51 A2531300	Mzbm	Heterogeneous	35%	Binder	None Detected
		White	65%	Silicates	
		Non-fibrous			
		Tightly Bound			
52 A2531301	Mslk	Heterogeneous	95%	Binder	None Detected
		Gray, Black	5%	Mastic	
		Non-fibrous			
		Bound			
53 A2531302	Mslk	Heterogeneous	95%	Binder	None Detected
		Gray, Black	5%	Mastic	
		Non-fibrous			
		Bound			



ASBESTOS BULK ANALYSIS

By: POLARIZING LIGHT MICROSCOPY

Client: PSI
 821 Corporate Ct.
 Waukesha, WI 53189

CEI Lab Code: A17-15269
Date Received: 10-27-17
Date Analyzed: 10-30-17
Date Reported: 10-31-17

Project: Kenosha- 1505 60th St; 0541478

ASBESTOS BULK PLM, EPA 600 METHOD

Client ID Lab ID	Lab Description	Lab Attributes	NON-ASBESTOS COMPONENTS		ASBESTOS %
			Fibrous	Non-Fibrous	
54 A2531303	Mslk	Heterogeneous Gray,Black Non-fibrous Bound	95% 5%	Binder Mastic	None Detected
55 A2531304	Mpc	Heterogeneous Gray Non-fibrous Bound	90%	Caulk	10% Chrysotile
56 A2531305	Mpc	Heterogeneous Gray Non-fibrous Bound	90%	Caulk	10% Chrysotile
57 A2531306	Mpc	Heterogeneous Gray Non-fibrous Bound	90%	Caulk	10% Chrysotile
58 A2531307	Mvfe	Heterogeneous Beige Non-fibrous Bound	50% 45% 5%	Vinyl Binder Mastic	None Detected
59 A2531308	Mvfe	Heterogeneous Beige Non-fibrous Bound	50% 45% 5%	Vinyl Binder Mastic	None Detected
60 A2531309	Mvfe	Heterogeneous Beige Non-fibrous Bound	50% 45% 5%	Vinyl Binder Mastic	None Detected



ASBESTOS BULK ANALYSIS

By: POLARIZING LIGHT MICROSCOPY

Client: PSI
 821 Corporate Ct.
 Waukesha, WI 53189

CEI Lab Code: A17-15269
Date Received: 10-27-17
Date Analyzed: 10-30-17
Date Reported: 10-31-17

Project: Kenosha- 1505 60th St; 0541478

ASBESTOS BULK PLM, EPA 600 METHOD

Client ID Lab ID	Lab Description	Lab Attributes	NON-ASBESTOS COMPONENTS				ASBESTOS %
			Fibrous		Non-Fibrous		
61 A2531310	Mflyg	Heterogeneous	30%	Cellulose	50%	Vinyl	None Detected
		Gray,Green	5%	Synthetic Fiber	10%	Tar	
		Fibrous			5%	Mastic	
		Bound					
62 A2531311	Mflyg	Heterogeneous	30%	Cellulose	50%	Vinyl	None Detected
		Gray,Green	5%	Synthetic Fiber	10%	Tar	
		Fibrous			5%	Mastic	
		Bound					
63 A2531312	Mflyg	Heterogeneous	30%	Cellulose	50%	Vinyl	None Detected
		Gray,Green	5%	Synthetic Fiber	10%	Tar	
		Fibrous			5%	Mastic	
		Bound					
64 Layer 1 A2531313	Sp2	Heterogeneous	5%	Talc	40%	Calc Carb	None Detected
		White			5%	Silicates	
		Non-fibrous			50%	Paint	
		Bound					
Layer 2 A2531313	Sp2	Heterogeneous			65%	Binder	None Detected
		White			35%	Silicates	
		Non-fibrous					
		Bound					
Layer 3 A2531313	Sp2	Heterogeneous	5%	Hair	30%	Binder	None Detected
		Gray			65%	Silicates	
		Fibrous					
		Bound					
65 Layer 1 A2531314	Sp2	Heterogeneous			65%	Binder	None Detected
		White			30%	Silicates	
		Non-fibrous			5%	Paint	
		Bound					

Lab Notes: No surface layer present.



ASBESTOS BULK ANALYSIS

By: POLARIZING LIGHT MICROSCOPY

Client: PSI
821 Corporate Ct.
Waukesha, WI 53189

CEI Lab Code: A17-15269
Date Received: 10-27-17
Date Analyzed: 10-30-17
Date Reported: 10-31-17

Project: Kenosha- 1505 60th St; 0541478

ASBESTOS BULK PLM, EPA 600 METHOD

Client ID Lab ID	Lab Description	Lab Attributes	NON-ASBESTOS COMPONENTS				ASBESTOS %
			Fibrous		Non-Fibrous		
Layer 2 A2531314	Sp2	Heterogeneous Gray Fibrous Bound	5%	Hair	30% 65%	Binder Silicates	None Detected
66 Layer 1 A2531315	Sp2	Heterogeneous White Non-fibrous Bound	5%	Talc	40% 5% 50%	Calc Carb Silicates Paint	None Detected
Layer 2 A2531315	Sp2	Heterogeneous White Non-fibrous Bound			65% 35%	Binder Silicates	None Detected
Layer 3 A2531315	Sp2	Heterogeneous Gray Fibrous Bound	5%	Hair	30% 65%	Binder Silicates	None Detected
67 A2531316A	Mf12y	Heterogeneous Gray Non-fibrous Bound			95%	Vinyl	5% Chrysotile
A2531316B	Mf12y	Homogeneous Clear Non-fibrous Bound			100%	Mastic	None Detected
68 A2531317A	Mf12y	Heterogeneous Gray Non-fibrous Bound			95%	Vinyl	5% Chrysotile



ASBESTOS BULK ANALYSIS

By: POLARIZING LIGHT MICROSCOPY

Client: PSI
 821 Corporate Ct.
 Waukesha, WI 53189

CEI Lab Code: A17-15269
Date Received: 10-27-17
Date Analyzed: 10-30-17
Date Reported: 10-31-17

Project: Kenosha- 1505 60th St; 0541478

ASBESTOS BULK PLM, EPA 600 METHOD

Client ID Lab ID	Lab Description	Lab Attributes	NON-ASBESTOS COMPONENTS				ASBESTOS %
			Fibrous		Non-Fibrous		
A2531317B	Mf12y	Homogeneous Clear Non-fibrous Bound	100%		Mastic		None Detected
69 A2531318A	Mf12y	Heterogeneous Gray Non-fibrous Bound	95%		Vinyl		5% Chrysotile
A2531318B	Mf12y	Homogeneous Clear Non-fibrous Bound	100%		Mastic		None Detected
70 A2531319	Mflt	Heterogeneous Tan Non-fibrous Bound	30%	Cellulose	50%	Vinyl	None Detected
					20%	Binder	
71 A2531320	Mflt	Heterogeneous Tan Non-fibrous Bound	40%	Cellulose	50%	Vinyl	None Detected
					10%	Tar	
72 A2531321	Mflt	Heterogeneous Tan Non-fibrous Bound	40%	Cellulose	50%	Vinyl	None Detected
					10%	Tar	
73 A2531322	Mctm	Heterogeneous Gray Non-fibrous Bound			35%	Binder	None Detected
					65%	Silicates	



ASBESTOS BULK ANALYSIS

By: POLARIZING LIGHT MICROSCOPY

Client: PSI
 821 Corporate Ct.
 Waukesha, WI 53189

CEI Lab Code: A17-15269
Date Received: 10-27-17
Date Analyzed: 10-30-17
Date Reported: 10-31-17

Project: Kenosha- 1505 60th St; 0541478

ASBESTOS BULK PLM, EPA 600 METHOD

Client ID Lab ID	Lab Description	Lab Attributes	NON-ASBESTOS COMPONENTS		ASBESTOS %
			Fibrous	Non-Fibrous	
74 A2531323	Mctm	Heterogeneous Gray Non-fibrous Bound	40% 60%	Binder Silicates	None Detected
75 A2531324	Mctm	Heterogeneous Gray Non-fibrous Bound	40% 60%	Binder Silicates	None Detected
76 A2531325	Mctg	Heterogeneous Gray Non-fibrous Bound	60% 40%	Binder Silicates	None Detected
77 A2531326	Mctg	Heterogeneous Gray Non-fibrous Bound	60% 40%	Binder Silicates	None Detected
78 A2531327	Mctg	Heterogeneous Gray Non-fibrous Bound	60% 40%	Binder Silicates	None Detected
79 A2531328	Mwr	Heterogeneous Off-white Fibrous Bound	100%	Cellulose	None Detected
80 A2531329	Mwr	Heterogeneous Off-white Fibrous Bound	100%	Cellulose	None Detected



ASBESTOS BULK ANALYSIS

By: POLARIZING LIGHT MICROSCOPY

Client: PSI
 821 Corporate Ct.
 Waukesha, WI 53189

CEI Lab Code: A17-15269
Date Received: 10-27-17
Date Analyzed: 10-30-17
Date Reported: 10-31-17

Project: Kenosha- 1505 60th St; 0541478

ASBESTOS BULK PLM, EPA 600 METHOD

Client ID Lab ID	Lab Description	Lab Attributes	NON-ASBESTOS COMPONENTS		ASBESTOS %
			Fibrous	Non-Fibrous	
81 A2531330	Mwr	Heterogeneous Off-white Fibrous Bound	100%	Cellulose	None Detected
82 A2531331	Mpg	Heterogeneous White,Tan Non-fibrous Bound	85%	Binder	None Detected
			10%	Calc Carb	
			5%	Paint	
83 A2531332	Mpg	Heterogeneous Gray,White Non-fibrous Bound	82%	Binder	3% Chrysotile
			10%	Calc Carb	
			5%	Paint	
84 A2531333	Mpg	Heterogeneous Gray,White Non-fibrous Bound	82%	Binder	3% Chrysotile
			10%	Calc Carb	
			5%	Paint	
85 A2531334	Mrs	Heterogeneous Black,Brown Fibrous Bound	65%	Cellulose	None Detected
			30%	Tar	
			5%	Silicates	
86 A2531335	Mrs	Heterogeneous Black,Brown Fibrous Bound	65%	Cellulose	None Detected
			30%	Tar	
			5%	Silicates	
87 A2531336	Mrs	Heterogeneous Black,Brown Fibrous Bound	65%	Cellulose	None Detected
			30%	Tar	
			5%	Silicates	



ASBESTOS BULK ANALYSIS

By: POLARIZING LIGHT MICROSCOPY

Client: PSI
 821 Corporate Ct.
 Waukesha, WI 53189

CEI Lab Code: A17-15269
Date Received: 10-27-17
Date Analyzed: 10-30-17
Date Reported: 10-31-17

Project: Kenosha- 1505 60th St; 0541478

ASBESTOS BULK PLM, EPA 600 METHOD

Client ID Lab ID	Lab Description	Lab Attributes	NON-ASBESTOS COMPONENTS				ASBESTOS %
			Fibrous		Non-Fibrous		
88 A2531337	Mrs2	Heterogeneous Black,Red Fibrous Bound	35%	Cellulose	40%	Tar 25% Silicates	None Detected
89 A2531338	Mrs2	Heterogeneous Black,Red Fibrous Bound	35%	Cellulose	40%	Tar 25% Silicates	None Detected
90 A2531339	Mrs2	Heterogeneous Black,Red Fibrous Bound	35%	Cellulose	40%	Tar 25% Silicates	None Detected
91 A2531340	Mdce	Heterogeneous White Non-fibrous Bound			90%	Caulk 10% Paint	None Detected
92 A2531341	Mdce	Heterogeneous White Non-fibrous Bound			90%	Caulk 10% Paint	None Detected
93 A2531342	Mdce	Heterogeneous White Non-fibrous Bound			90%	Caulk 10% Paint	None Detected
94 A2531343	Mwce	Heterogeneous White Non-fibrous Bound			90%	Caulk 10% Paint	None Detected



ASBESTOS BULK ANALYSIS

By: POLARIZING LIGHT MICROSCOPY

Client: PSI
 821 Corporate Ct.
 Waukesha, WI 53189

CEI Lab Code: A17-15269
Date Received: 10-27-17
Date Analyzed: 10-30-17
Date Reported: 10-31-17

Project: Kenosha- 1505 60th St; 0541478

ASBESTOS BULK PLM, EPA 600 METHOD

Client ID Lab ID	Lab Description	Lab Attributes	NON-ASBESTOS COMPONENTS		ASBESTOS %
			Fibrous	Non-Fibrous	
95 A2531344	Mwce	Heterogeneous White Non-fibrous Bound	95% 5%	Caulk Paint	None Detected
96 A2531345	Mwce	Heterogeneous White Non-fibrous Bound	100%	Caulk	None Detected
97 A2531346	Mpce	Heterogeneous Gray Non-fibrous Bound	100%	Caulk	None Detected
98 A2531347	Mpce	Heterogeneous Gray Non-fibrous Bound	100%	Caulk	None Detected
99 A2531348	Mpce	Heterogeneous Gray Non-fibrous Bound	90% 10%	Caulk Paint	None Detected
100 A2531349	Mvce	Heterogeneous White, Gray Non-fibrous Bound	90% 10%	Caulk Paint	None Detected
101 A2531350	Mvce	Heterogeneous White, Gray Non-fibrous Bound	90% 10%	Caulk Paint	None Detected



ASBESTOS BULK ANALYSIS

By: POLARIZING LIGHT MICROSCOPY

Client: PSI
 821 Corporate Ct.
 Waukesha, WI 53189

CEI Lab Code: A17-15269
Date Received: 10-27-17
Date Analyzed: 10-30-17
Date Reported: 10-31-17

Project: Kenosha- 1505 60th St; 0541478

ASBESTOS BULK PLM, EPA 600 METHOD

Client ID Lab ID	Lab Description	Lab Attributes	NON-ASBESTOS COMPONENTS			ASBESTOS %
			Fibrous		Non-Fibrous	
102 A2531351	Mvce	Heterogeneous White, Gray Non-fibrous Bound	90%	Caulk	10%	None Detected
			10%	Paint		
103 A2531352	Mvce2	Heterogeneous Beige, White Non-fibrous Bound	87%	Caulk	10%	3% Chrysotile
			10%	Paint		
104 A2531353	Mvce2	Heterogeneous Beige, White Non-fibrous Bound	87%	Caulk	10%	3% Chrysotile
			10%	Paint		
105 A2531354	Mvce2	Heterogeneous Beige, White Non-fibrous Bound	87%	Caulk	10%	3% Chrysotile
			10%	Paint		
106 A2531355	Mrs3	Heterogeneous Tan, Black Fibrous Bound	35%	Cellulose	40%	None Detected
					25%	
107 A2531356	Mrs3	Heterogeneous Tan, Black Fibrous Bound	35%	Cellulose	40%	None Detected
					25%	
108 A2531357	Mrs3	Heterogeneous Tan, Black Fibrous Bound	35%	Cellulose	40%	None Detected
					25%	



ASBESTOS BULK ANALYSIS

By: POLARIZING LIGHT MICROSCOPY

Client: PSI
 821 Corporate Ct.
 Waukesha, WI 53189

CEI Lab Code: A17-15269
Date Received: 10-27-17
Date Analyzed: 10-30-17
Date Reported: 10-31-17

Project: Kenosha- 1505 60th St; 0541478

ASBESTOS BULK PLM, EPA 600 METHOD

Client ID Lab ID	Lab Description	Lab Attributes	NON-ASBESTOS COMPONENTS				ASBESTOS %
			Fibrous		Non-Fibrous		
109 A2531358	Mrs4	Heterogeneous Green,Black Fibrous Bound	35%	Cellulose	40%	Tar Silicates	None Detected
110 A2531359	Mrs4	Heterogeneous Green,Black Fibrous Bound	35%	Cellulose	40%	Tar Silicates	None Detected
111 A2531360	Mrs4	Heterogeneous Green,Black Fibrous Bound	35%	Cellulose	40%	Tar Silicates	None Detected
112 A2531361	Mrf	Heterogeneous Gray,Black Fibrous Bound			90%	Tar	10% Chrysotile
113 A2531362	Mrf	Heterogeneous Gray,Black Fibrous Bound			90%	Tar	10% Chrysotile
114 A2531363	Mrf	Heterogeneous Gray,Black Fibrous Bound			90%	Tar	10% Chrysotile
115 A2531364	Mrtp	Heterogeneous Black Fibrous Bound	80%	Cellulose	20%	Tar	None Detected



ASBESTOS BULK ANALYSIS

By: POLARIZING LIGHT MICROSCOPY

Client: PSI
 821 Corporate Ct.
 Waukesha, WI 53189

CEI Lab Code: A17-15269
Date Received: 10-27-17
Date Analyzed: 10-30-17
Date Reported: 10-31-17

Project: Kenosha- 1505 60th St; 0541478

ASBESTOS BULK PLM, EPA 600 METHOD

Client ID Lab ID	Lab Description	Lab Attributes	NON-ASBESTOS COMPONENTS				ASBESTOS %
			Fibrous		Non-Fibrous		
116 A2531365	Mrtp	Heterogeneous Black Fibrous Bound	80%	Cellulose	20%	Tar	None Detected
117 A2531366	Mrtp	Heterogeneous Black Fibrous Bound	80%	Cellulose	20%	Tar	None Detected
118 Layer 1 A2531367	Sp1	Heterogeneous White Non-fibrous Bound			65%	Binder 30% Silicates 5% Paint	None Detected
Layer 2 A2531367	Sp1	Heterogeneous Gray Non-fibrous Bound	5%	Hair	30%	Binder 65% Silicates	None Detected
119 Layer 1 A2531368	Sp1	Heterogeneous White Non-fibrous Bound			65%	Binder 30% Silicates 5% Paint	None Detected
Layer 2 A2531368	Sp1	Heterogeneous Gray Non-fibrous Bound	5%	Hair	30%	Binder 65% Silicates	None Detected
120 Layer 1 A2531369	Sp1	Heterogeneous White,Red Non-fibrous Bound	10%	Talc	65%	Binder 15% Silicates 10% Paint	None Detected

Lab Notes: Texture present.



ASBESTOS BULK ANALYSIS

By: POLARIZING LIGHT MICROSCOPY

Client: PSI
 821 Corporate Ct.
 Waukesha, WI 53189

CEI Lab Code: A17-15269
Date Received: 10-27-17
Date Analyzed: 10-30-17
Date Reported: 10-31-17

Project: Kenosha- 1505 60th St; 0541478

ASBESTOS BULK PLM, EPA 600 METHOD

Client ID Lab ID	Lab Description	Lab Attributes	NON-ASBESTOS COMPONENTS		ASBESTOS %
			Fibrous	Non-Fibrous	
Layer 2 A2531369	Sp1	Heterogeneous White Non-fibrous Bound	65%	Binder 30% Silicates 5% Paint	None Detected
Layer 3 A2531369	Sp1	Heterogeneous Gray Non-fibrous Bound	5%	Hair 30% Binder 65% Silicates	None Detected
121 Layer 1 A2531370	Sp1	Heterogeneous White,Blue Non-fibrous Bound	65%	Binder 30% Silicates 5% Paint	None Detected
Layer 2 A2531370	Sp1	Heterogeneous Gray Non-fibrous Bound	5%	Hair 30% Binder 65% Silicates	None Detected
122 Layer 1 A2531371	Sp1	Heterogeneous White Non-fibrous Bound	65%	Binder 30% Silicates 5% Paint	None Detected
Layer 2 A2531371	Sp1	Heterogeneous Gray Non-fibrous Bound	5%	Hair 30% Binder 65% Silicates	None Detected
123 Layer 1 A2531372	Sp1	Heterogeneous White Non-fibrous Bound	65%	Binder 30% Silicates 5% Paint	None Detected



ASBESTOS BULK ANALYSIS

By: POLARIZING LIGHT MICROSCOPY

Client: PSI
 821 Corporate Ct.
 Waukesha, WI 53189

CEI Lab Code: A17-15269
Date Received: 10-27-17
Date Analyzed: 10-30-17
Date Reported: 10-31-17

Project: Kenosha- 1505 60th St; 0541478

ASBESTOS BULK PLM, EPA 600 METHOD

Client ID Lab ID	Lab Description	Lab Attributes	NON-ASBESTOS COMPONENTS				ASBESTOS %
			Fibrous		Non-Fibrous		
Layer 2 A2531372	Sp1	Heterogeneous Gray Non-fibrous Bound	5%	Hair	30%	Binder 65% Silicates	None Detected
124 Layer 1 A2531373	Sp1	Heterogeneous White Non-fibrous Bound			65%	Binder 30% Silicates 5% Paint	None Detected
Layer 2 A2531373	Sp1	Heterogeneous Gray Non-fibrous Bound	5%	Hair	30%	Binder 65% Silicates	None Detected
DH-1 A2531374	Mstp	Heterogeneous Black Fibrous Bound	80%	Cellulose	20%	Tar	None Detected
DH-2 A2531375	Mstp	Heterogeneous Black Fibrous Bound	80%	Cellulose	20%	Tar	None Detected
DH-3 A2531376	Mstp	Heterogeneous Black Fibrous Bound	80%	Cellulose	20%	Tar	None Detected
DH-4 A2531377	Mvce	Homogeneous White, Gray Non-fibrous Bound			100%	Caulk	None Detected



ASBESTOS BULK ANALYSIS

By: POLARIZING LIGHT MICROSCOPY

Client: PSI
 821 Corporate Ct.
 Waukesha, WI 53189

CEI Lab Code: A17-15269
Date Received: 10-27-17
Date Analyzed: 10-30-17
Date Reported: 10-31-17

Project: Kenosha- 1505 60th St; 0541478

ASBESTOS BULK PLM, EPA 600 METHOD

Client ID Lab ID	Lab Description	Lab Attributes	NON-ASBESTOS COMPONENTS				ASBESTOS %
			Fibrous		Non-Fibrous		
DH-5 A2531378	Mvce	Homogeneous White,Gray Non-fibrous Bound	100%	Caulk			None Detected
DH-6 A2531379	Mvce	Homogeneous White,Gray Non-fibrous Bound	100%	Caulk			None Detected
DH-7 A2531380	Mrs	Homogeneous Red,Gray Fibrous Bound	25%	Fiberglass	40%	Tar Silicates	None Detected
DH-8 A2531381	Mrs	Homogeneous Red,Gray Fibrous Bound	25%	Fiberglass	40%	Tar Silicates	None Detected
DH-9 A2531382	Mrs	Homogeneous Red,Gray Fibrous Bound	25%	Fiberglass	40%	Tar Silicates	None Detected
DH-10 A2531383	Mrtp	Homogeneous Black Fibrous Bound	80%	Cellulose	20%	Tar	None Detected
DH-11 A2531384	Mrtp	Homogeneous Black Fibrous Bound	80%	Cellulose	20%	Tar	None Detected



ASBESTOS BULK ANALYSIS

By: POLARIZING LIGHT MICROSCOPY

Client: PSI
821 Corporate Ct.
Waukesha, WI 53189

CEI Lab Code: A17-15269
Date Received: 10-27-17
Date Analyzed: 10-30-17
Date Reported: 10-31-17

Project: Kenosha- 1505 60th St; 0541478

ASBESTOS BULK PLM, EPA 600 METHOD

Client ID Lab ID	Lab Description	Lab Attributes	NON-ASBESTOS COMPONENTS			ASBESTOS %	
			Fibrous	Non-Fibrous			
DH-12 A2531385	Mrtp	Homogeneous Black Fibrous Bound	80%	Cellulose	20%	Tar	None Detected
DH-13 A2531386	Mhsce	Homogeneous White Non-fibrous Bound			100%	Caulk	None Detected
DH-14 A2531387	Mhsce	Homogeneous White Non-fibrous Bound			100%	Caulk	None Detected
DH-15 A2531388	Mhsce	Homogeneous White Non-fibrous Bound			100%	Caulk	None Detected



LEGEND: Non-Anth = Non-Asbestiform Anthophyllite
Non-Trem = Non-Asbestiform Tremolite
Calc Carb = Calcium Carbonate

METHOD: EPA 600 / R93 / 116 and EPA 600 / M4-82 / 020

REPORTING LIMIT: <1% by visual estimation


REPORTING LIMIT FOR POINT COUNTS: 0.25% by 400 Points or 0.1% by 1,000 Points

REGULATORY LIMIT: >1% by weight

Due to the limitations of the EPA 600 method, nonfriable organically bound materials (NOBs) such as vinyl floor tiles can be difficult to analyze via polarized light microscopy (PLM). EPA recommends that all NOBs analyzed by PLM, and found not to contain asbestos, be further analyzed by Transmission Electron Microscopy (TEM). Please note that PLM analysis of dust and soil samples for asbestos is not covered under NVLAP accreditation. Estimated measurement of uncertainty is available on request.

This report relates only to the samples tested or analyzed and may not be reproduced, except in full, without written approval by CEI Labs, Inc. CEI Labs makes no warranty representation regarding the accuracy of client submitted information in preparing and presenting analytical results. Interpretation of the analytical results is the sole responsibility of the client. Samples were received in acceptable condition unless otherwise noted. This report may not be used by the client to claim product endorsement by NVLAP or any other agency of the U.S. Government.

ANALYST: 
Taylor B. Metcalf

APPROVED BY: 
Tianbao Bai, Ph.D., CIH
Laboratory Director





107 New Edition Court, Cary, NC 27511
 Tel: 866-481-1412; Fax: 919-481-1442

(139) A7-15. 269
 ASBESTOS A2531249
 CHAIN OF CUSTODY A2531388

LAB USE ONLY:
CEI Lab Code:
CEI Lab I.D. Range:

COMPANY INFORMATION	PROJECT INFORMATION
CEI CLIENT #:	Job Contact: <i>Jim Updike</i>
Company: <i>PSI, Inc.</i>	Email / Tel: <i>Same</i>
Address: <i>821 Corporate Ct</i>	Project Name: <i>Kenosha - 1505 60th St</i>
<i>Waukesha, WI 53189</i>	Project ID# <i>0541478</i>
Email: <i>jim.updike@psiusa.com</i>	PO #:
Tel: <i>262-521-2125</i> Fax:	STATE SAMPLES COLLECTED IN: <i>WI</i>

IF TAT IS NOT MARKED STANDARD 3 DAY TAT APPLIES.

ASBESTOS	METHOD	TURN AROUND TIME					
		4 HR	8 HR	24 HR	2 DAY	3 DAY	5 DAY
PLM BULK	EPA 600	<input type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>	<input checked="" type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>
PLM POINT COUNT (400)	EPA 600	<input type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>
PLM POINT COUNT (1000)	EPA 600	<input type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>
PLM GRAV w POINT COUNT	EPA 600	<input type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>
PLM BULK	CARB 435	<input type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>
PCM AIR	NIOSH 7400	<input type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>
TEM AIR	EPA AHERA	<input type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>
TEM AIR	NIOSH 7402	<input type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>
TEM AIR	ISO 10312	<input type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>
TEM AIR	ASTM 6281-09	<input type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>
TEM BULK	CHATFIELD	<input type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>
TEM DUST WIPE	ASTM D6480-05	<input type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>
TEM DUST MICROVAC	ASTM D5755-09	<input type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>
TEM SOIL	ASTM D7521-13	<input type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>
TEM VERMICULITE	CINCINNATI METHOD	<input type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>
OTHER:		<input type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>

REMARKS / SPECIAL INSTRUCTIONS: <i>Bag #1: Samples 1-66</i> <i>Bag #2 Samples 67-124</i> <i>Dog House Samples 1-15</i>			<input checked="" type="checkbox"/> Accept Samples <input type="checkbox"/> Reject Samples
Relinquished By:	Date/Time	Received By:	Date/Time
<i>Matthew Giddings</i>	<i>10-26-17/By 12:00</i>	<i>AA</i>	<i>10 27 17 9:40</i>

Samples will be disposed of 30 days after analysis

BULK SAMPLE LOG

Client:	City of Kenosha	Construction Date:	Unknown
Project:	Multi-Family Residential Building	Date of Inspection:	10/25/2017
Address:	1505 60th St., Kenosha, WI	Inspector:	Matt Geldmeyer
		Inspector #:	All-13850

SAMPLE NUMBER	SAMPLE LOCATION	MATERIAL DESCRIPTION
01	01	Brick
02	02	Brick
03	Exterior	Brick
04	01	Brick Mortar
05	02	Brick Mortar
06	Exterior	Brick Mortar
07	01	Fiberglass Batt Insulation with Suspect Layer
08	02	Fiberglass Batt Insulation with Suspect Layer
09	101	Fiberglass Batt Insulation with Suspect Layer
10	01	Flue Packing
11	01	Flue Packing
12	01	Flue Packing
13	01	Paper Insulation
14	01	Paper Insulation
15	01	Paper Insulation
16	STWL1	Duct Wrap
17	105	Duct Wrap
18	105	Duct Wrap
19	100	Asphalt Sheeting
20	100	Asphalt Sheeting
21	100	Asphalt Sheeting
22	100	Siding Felt - Tan
23	Exterior	Siding Felt - Tan
24	Exterior	Siding Felt - Tan
25	100	Siding Tar Paper
26	100	Siding Tar Paper
27	100	Siding Tar Paper
28	100	Vermiculite Insulation
29	208	Vermiculite Insulation
30	300	Vermiculite Insulation
31	107	Cream Linoleum
32	204	Cream Linoleum
33	208	Cream Linoleum

BULK SAMPLE LOG


Client: City of Kenosha	Construction Date: Unknown
Project: Multi-Family Residential Building	Date of Inspection: 10/25/2017
Address: 1505 60th St., Kenosha, WI	Inspector: Matt Geldmeyer
	Inspector #: All-13850

SAMPLE NUMBER	SAMPLE LOCATION	MATERIAL DESCRIPTION
34	107	Gray/Red Linoleum
35	107	Gray/Red Linoleum
36	107	Gray/Red Linoleum
37	101	2' x 2' Suspended Ceiling Tile: Pinholes and Fissures
38	101	2' x 2' Suspended Ceiling Tile: Pinholes and Fissures
39	101	2' x 2' Suspended Ceiling Tile: Pinholes and Fissures
40	101	Drywall/Joint Compound System
41	103	Drywall/Joint Compound System
42	106	Drywall/Joint Compound System
43	101	Fiberboard with Suspect Black Layer
44	101	Fiberboard with Suspect Black Layer
45	101	Fiberboard with Suspect Black Layer
46	101	Z-Brick
47	101	Z-Brick
48	101	Z-Brick
49	101	Z-Brick Mortar
50	101	Z-Brick Mortar
51	101	Z-Brick Mortar
52	101	Sink Undercoating - Black
53	101	Sink Undercoating - Black
54	101	Sink Undercoating - Black
55	101	Pipe Caulk - Gray
56	101	Pipe Caulk - Gray
57	101	Pipe Caulk - Gray
58	101	Beige Vinyl Flooring
59	101	Beige Vinyl Flooring
60	101	Beige Vinyl Flooring
61	101	Gray/Green Linoleum
62	101	Gray/Green Linoleum
63	101	Gray/Green Linoleum
64	101	Plaster with Troweled on Surface Coat
65	203	Plaster with Troweled on Surface Coat
66	210	Plaster with Troweled on Surface Coat

BULK SAMPLE LOG

Client:	City of Kenosha	Construction Date:	Unknown
Project:	Multi-Family Residential Building	Date of Inspection:	10/25/2017
Address:	1505 60th St., Kenosha, WI	Inspector:	Matt Geldmeyer
		Inspector #:	All-13850

SAMPLE NUMBER	SAMPLE LOCATION	MATERIAL DESCRIPTION
67	102	12" x 12" Gray Floor Tile and Associated Mastic
68	103	12" x 12" Gray Floor Tile and Associated Mastic
69	103	12" x 12" Gray Floor Tile and Associated Mastic
70	102	Tan Linoleum
71	102	Tan Linoleum
72	102	Tan Linoleum
73	207	Ceramic Tile Mastic
74	207	Ceramic Tile Mastic
75	207	Ceramic Tile Mastic
76	207	Ceramic Tile Grout
77	207	Ceramic Tile Grout
78	207	Ceramic Tile Grout
79	208	Window Rope
80	208	Window Rope
81	208	Window Rope
82	STWL3	Window Pane Glazing
83	Exterior	Window Pane Glazing
84	Exterior	Window Pane Glazing
85	300	Roof Shingles - Brown
86	300	Roof Shingles - Brown
87	300	Roof Shingles - Brown
88	300	Roof Shingles - Red
89	300	Roof Shingles - Red
90	300	Roof Shingles - Red
91	Exterior	Exterior Door Caulk - White
92	Exterior	Exterior Door Caulk - White
93	Exterior	Exterior Door Caulk - White
94	Exterior	Exterior Window Caulk - White
95	Exterior	Exterior Window Caulk - White
96	Exterior	Exterior Window Caulk - White
97	Exterior	Exterior Pipe Caulk - Gray (West Side of Building)
98	Exterior	Exterior Pipe Caulk - Gray (West Side of Building)
99	Exterior	Exterior Pipe Caulk - Gray (West Side of Building)



NORTH

PSI Project Number:
00541478

Date:
10/25/2017


Scale:
Not to Scale

City of Kenosha
1505 60th Street
Kenosha, WI

**Floor Plan
Basement**

Environmental Services
821 Corporate Court
Waukesha, Wisconsin 53189
(262) 521-2125 Fax (262) 521-2471





NORTH

PSI Project Number:
00541478

Date:
10/25/2017


Scale:
Not to Scale

City of Kenosha
1505 60th Street
Kenosha, WI

Floor Plan
First Floor

Environmental Services
821 Corporate Court
Waukesha, Wisconsin 53189
(262) 521-2125 Fax (262) 521-2471





NORTH

PSI Project Number:
00541478

Date:
10/25/2017


Scale:
Not to Scale

City of Kenosha
1505 60th Street
Kenosha, WI

Floor Plan
Second Floor

Environmental Services
821 Corporate Court
Waukesha, Wisconsin 53189
(262) 521-2125 Fax (262) 521-2471





NORTH

PSI Project Number:
00541478

Date:
10/25/2017

Scale:
Not to Scale

City of Kenosha
1505 60th Street
Kenosha, WI

Floor Plan
Attic

Environmental Services
821 Corporate Court
Waukesha, Wisconsin 53189
(262) 521-2125 Fax (262) 521-2471



Milwaukee Lead/Asbestos Information Center

A division of Midwest Certified Training, Inc.
3495 North 124th Street, Brookfield, WI 53005 Phone: 414-481-9070



Matthew Raymond Geldmeyer

Has successfully completed a course and passed the examination on January 12, 2017 with a minimum score of 70 percent, that meets all criteria for the State of Wisconsin Recertification as an

Asbestos Inspector Refresher Course

Date of Course: January 12, 2017

Date Issued: January 12, 2017

Date of Expiration: January 12, 2018

Certification Number: AIR17011256344

Location: Milwaukee Lead/Asbestos Information Center, 3495 North 124th Street, Brookfield, WI 53005

DCQ Course ID #: 9606

Rocky Early

Rocky Early, Director of Milwaukee Lead/Asbestos Information Center, Inc.
3495 North 124th Street
Brookfield, WI 53005
414-481-9070

Company Certificate

This certifies that

PSI - PROFESSIONAL SERVICE INDUSTRIES INC

821 CORPORATE CT
WAUKESHA WI 53189-5009

is certified under ch. DHS 159, Wis. Adm. Code as a

Asbestos Company - Primary

Certificate Issue Date: 07/16/2015
Expiration Date: 08/01/2017, 12:01 a.m.
Certification #: CAP-16820

Wisconsin Department of Health Services
Division of Public Health
Bureau of Environmental and Occupational Health
Asbestos & Lead Section
PO Box 2659
Madison WI 53701-2659
Phone: (608) 261-6876



Shelley A Bruce
Shelley A Bruce,
Unit Supervisor.



SCOPE OF ACCREDITATION TO ISO/IEC 17025:2005

CEI Labs, Inc.
730 SE Maynard Road
Cary, NC 27511
Dr. Tianbao Bai
Phone: 919-481-1413 Fax: 919-481-1442
Email: bai@ceilabs.com
<http://www.ceilabs.com>

ASBESTOS FIBER ANALYSIS

NVLAP LAB CODE 101768-0

Bulk Asbestos Analysis

<u>Code</u>	<u>Description</u>
18/A01	EPA 600/M4-82-020: Interim Method for the Determination of Asbestos in Bulk Insulation Samples
18/A03	EPA 600/R-93/116: Method for the Determination of Asbestos in Bulk Building Materials

Airborne Asbestos Analysis

<u>Code</u>	<u>Description</u>
18/A02	U.S. EPA's "Interim Transmission Electron Microscopy Analytical Methods-Mandatory and Nonmandatory-and Mandatory Section to Determine Completion of Response Actions" as found in 40 CFR, Part 763, Subpart E, Appendix A.

A handwritten signature in black ink, appearing to read "Dana S. Laman".

For the National Voluntary Laboratory Accreditation Program

United States Department of Commerce
National Institute of Standards and Technology



Certificate of Accreditation to ISO/IEC 17025:2005

NVLAP LAB CODE: 101768-0

CEI Labs, Inc.
Cary, NC

is accredited by the National Voluntary Laboratory Accreditation Program for specific services,
listed on the Scope of Accreditation, for:

Asbestos Fiber Analysis

This laboratory is accredited in accordance with the recognized International Standard ISO/IEC 17025:2005.
This accreditation demonstrates technical competence for a defined scope and the operation of a laboratory quality management system (refer to joint ISO-ILAC-IAF Communique dated January 2009).

2016-04-01 through 2017-03-31

Effective Dates



David F. Alderman

For the National Voluntary Laboratory Accreditation Program

General Location Map



Subject Property: 6720 25th Avenue
PIN: 01-122-01-404-028





821 Corporate Court
Waukesha, WI
phone: 262.521.2125
fax: 262.521.2471
intertek.com/building
psiusa.com

October 31, 2017

Mr. Mark Willing
Purchasing Manager
City of Kenosha- Department of Finance
Municipal Building- Room 208
625 52nd Street
Kenosha, Wisconsin 53140

Re: NESHAP Asbestos Survey at
Multi-Family Residence
6720 25th Avenue
Kenosha, Wisconsin
PSI Project No. 00541480

Dear Mr. Willing:

In accordance with our agreement dated May 15, 2012, Professional Service Industries, Inc. (PSI), has performed an Asbestos Survey of the above-referenced property to identify all Asbestos-Containing Materials (ACM) including Category I and Category II non-friable ACM. Below, please find a discussion of our survey and results.

Facility Description

The facility included in this National Emissions Standard for Hazardous Air Pollutants (NESHAPs) Asbestos Survey was a two-story residential structure with basement and attic. At the time of PSI's survey, the building was vacant.

Survey Intent

This asbestos survey was intended to meet the requirements of the NESHAP for Asbestos demolition or renovation. The survey included a thorough inspection of all areas of demolition or renovation. PSI's inspection team identified, quantified and assessed the condition of all Regulated Asbestos Containing Material (RACM), Category I non-friable ACM and Category II non-friable ACM. A hand pressure test was used to determine whether the material was friable.

Representative samples were collected and submitted to an accredited laboratory for analysis by Polarized Light Microscopy. Reports of Analysis are attached along with Chain of Custody documentation, Bulk Sample Logs, Site Layout Diagrams, and Inspector and Laboratory Certifications.

Findings

Asbestos-containing materials were discovered during this asbestos survey. Assumed asbestos-containing materials were identified and included electrical boxes. The table below details the findings of this survey.

Table 1-Asbestos Containing Materials

Material Description	Locations in Facility	Total Quantity	RACM, Cat. I or Cat. II	Friable (Y/N)	Condition
<i>Asphalt Sheeting (Bottom Layer)</i>	<i>Roof</i>	<i>1,100 SF</i>	<i>Cat. I</i>	<i>N</i>	<i>Good</i>
<i>Asphalt Sheeting (Middle Layer)</i>	<i>Roof</i>	<i>1,100 SF</i>	<i>Cat. I</i>	<i>N</i>	<i>Good</i>
<i>Transite Siding</i>	<i>Exterior</i>	<i>2,300 SF</i>	<i>Cat. II</i>	<i>N</i>	<i>Good</i>
<i>9" x 9" Tan Floor Tile and Associated Mastic</i>	<i>Rooms 102, 104, 208 and STWL1</i>	<i>308 SF</i>	<i>Cat. I</i>	<i>N</i>	<i>Good</i>
<i>12" x 12" Beige Floor Tile (Mastic Negative)</i>	<i>Rooms 100 and 101</i>	<i>240 SF</i>	<i>Cat. I</i>	<i>N</i>	<i>Good</i>
<i>Roof Flashing (Assumed, Inaccessible)</i>	<i>Roof</i>	<i>80 SF</i>	<i>Cat. I</i>	<i>N</i>	<i>Good</i>
<i>Electrical Boxes (Assumed Transite Components)</i>	<i>Room 04</i>	<i>4 Boxes</i>	<i>Cat. II</i>	<i>N</i>	<i>Good</i>

SF=Square Feet
EA=Each

Warranty

The information contained in this report is based upon the data furnished by the Client and observations and test results provided by PSI. These observations and results are time dependent, are subject to changing site conditions, and revisions to Federal, State and local regulations.

PSI warrants that these findings have been promulgated after being prepared in general accordance with generally accepted practices in the asbestos industry. PSI also recognizes that raw laboratory test data are not usually sufficient to make all abatement and management decisions.

As directed by the client, PSI did not provide any service to investigate or detect the presence of moisture, mold or other biological contaminants in or around any structure, or any service that was designed or intended to prevent or lower the risk of the occurrence of the amplification of the same. Client acknowledges that mold is ubiquitous to the environment with mold amplification occurring when building materials are impacted by moisture. Client further acknowledges that site conditions are outside of PSI's control, and that mold amplification will likely occur, or continue to occur, in the presence of moisture. As such, PSI cannot and shall not be held responsible for the occurrence or recurrence of mold amplification.

This report was prepared pursuant to the contract PSI has with the City of Kenosha. That contractual relationship included an exchange of information about the subject site that was unique and between PSI and its client and serves as the basis upon which this report was

prepared. Because of the importance of the communication between PSI and its client, reliance or any use of this report by anyone other than the City of Kenosha, for whom it was prepared, is prohibited and therefore not foreseeable to PSI.

Reliance or use by any such third party without explicit authorization in the report does not make said third party a third party beneficiary to PSI's contract with the City of Kenosha. Any such unauthorized reliance on or use of this report, including any of its information or conclusions, will be at third party's risk. For the same reasons, no warranties or representations, expressed or implied in this report, are made to any such third party.

No other warranties are implied or expressed.

Unidentifiable Conditions

This report is necessarily limited to the conditions observed and to the information available at the time of the work. Due to the nature of the work, there is a possibility that there may exist conditions which could not be identified within the scope of work or which were not apparent at the time of our site work. This report is also limited to information available from the client at the time it was conducted. The report may not represent all conditions at the subject site as it only reflects the information gathered from specific locations.

Thank you for choosing PSI as your consultant for this project. If you have any questions, or if we can be of additional service, please call us at 262.521.2125.

Respectfully submitted,
PROFESSIONAL SERVICE INDUSTRIES, INC.



Mike Larsen
WI Asbestos Inspector #All-13850



Michael Tjaden
Principal Consultant

Appendices

- A. Report of Bulk Sample Analysis for Asbestos/Chain of Custody
- B. Asbestos Bulk Sample Log
- C. Site Layout Drawings
- D. Inspector & Company Certifications



October 27, 2017

PSI
821 Corporate Ct.
Waukesha, WI 53189

CLIENT PROJECT: 6720 25th Av, Kenosha; 0541480
CEI LAB CODE: A17-15138

Dear Customer:

Enclosed are asbestos analysis results for PLM Bulk samples received at our laboratory on October 25, 2017. The samples were analyzed for asbestos using polarizing light microscopy (PLM) per the EPA 600 Method.

Sample results containing >1% asbestos are considered asbestos-containing materials (ACMs) per EPA regulatory requirements. The detection limit for the EPA 600 Method is <1% asbestos by weight as determined by visual estimation.

Thank you for your business and we look forward to continuing good relations. If you have any questions, please feel free to call our office at 919-481-1413.

Kind Regards,

A handwritten signature in black ink, appearing to read "Tianbao Bai".

Tianbao Bai, Ph.D., CIH
Laboratory Director





ASBESTOS ANALYTICAL REPORT

By: Polarized Light Microscopy

Prepared for

PSI

CLIENT PROJECT: 6720 25th Av, Kenosha; 0541480

CEI LAB CODE: A17-15138

TEST METHOD: EPA 600 / R93 / 116 and EPA 600 / M4-82 / 020

REPORT DATE: 10/27/17

TOTAL SAMPLES ANALYZED: 180

SAMPLES >1% ASBESTOS: 18

TEL: 866-481-1412

www.ceilabs.com



Asbestos Report Summary

By: POLARIZING LIGHT MICROSCOPY

PROJECT: 6720 25th Av, Kenosha; 0541480

CEI LAB CODE: A17-15138

METHOD: EPA 600 / R93 / 116 and EPA 600 / M4-82 / 020

Client ID	Layer	Lab ID	Color	Sample Description	ASBESTOS %
01		A2529146	Black,Brown	Mrtp	None Detected
02		A2529147	Black,Brown	Mrtp	None Detected
03		A2529148	Black,Brown	Mrtp	None Detected
04		A2529149	Black,Red	Mrs	None Detected
05		A2529150	Black,Red	Mrs	None Detected
06		A2529151	Black,Red	Mrs	None Detected
07		A2529152	Black,Brown	Mra1	Chrysotile 5%
08		A2529153	Black,Brown	Mra1	Chrysotile 5%
09		A2529154	Black,Brown	Mra1	Chrysotile 5%
10		A2529155	Black,Brown	Mra2	Chrysotile 5%
11		A2529156	Black,Brown	Mra2	Chrysotile 5%
12		A2529157	Black,Brown	Mra2	Chrysotile 5%
13		A2529158	Black,Gray	Mra3	None Detected
14		A2529159	Black,Gray	Mra3	None Detected
15		A2529160	Black,Gray	Mra3	None Detected
16		A2529161	Black,Gray	Mrs2	None Detected
17		A2529162	Black,Gray	Mrs2	None Detected
18		A2529163	Black,Gray	Mrs2	None Detected
19		A2529164	Black,Gray	Mra	None Detected
20		A2529165	Black,Gray	Mra	None Detected
21		A2529166	Black,Gray	Mra	None Detected
22		A2529167	Beige,Off-white	Mpge	None Detected
23		A2529168	Beige,Off-white	Mpge	None Detected
24		A2529169	Beige,Off-white	Mpge	None Detected
25		A2529170	White	Mpge2	None Detected
26		A2529171	White	Mpge2	None Detected
27		A2529172	White	Mpge2	None Detected
28		A2529173	Off-white,Gray	Mwce	None Detected
29		A2529174	Off-white,Gray	Mwce	None Detected
30		A2529175	Off-white,Gray	Mwce	None Detected
31		A2529176	Off-white,Gray	Mts	Chrysotile 15%



Asbestos Report Summary

By: POLARIZING LIGHT MICROSCOPY

PROJECT: 6720 25th Av, Kenosha; 0541480

CEI LAB CODE: A17-15138

METHOD: EPA 600 / R93 / 116 and EPA 600 / M4-82 / 020

Client ID	Layer	Lab ID	Color	Sample Description	ASBESTOS %
32		A2529177	Off-white,Gray	Mts	Chrysotile 15%
33		A2529178	Off-white,Gray	Mts	Chrysotile 15%
34		A2529179	Black,Brown	Mstp	None Detected
35		A2529180	Black,Brown	Mstp	None Detected
36		A2529181	Black,Brown	Mstp	None Detected
37		A2529182	Gray	Mpce	None Detected
38		A2529183	Gray	Mpce	None Detected
39		A2529184	Gray	Mpce	None Detected
40		A2529185	Gray,Off-white	Msc1	None Detected
41		A2529186	Gray,Off-white	Msc1	None Detected
42		A2529187	Gray,Off-white	Msc1	None Detected
43		A2529188	Red	MB	None Detected
44		A2529189	Red	MB	None Detected
45		A2529190	Red	MB	None Detected
46		A2529191	Gray	Mbm	None Detected
47		A2529192	Gray	Mbm	None Detected
48		A2529193	Gray	Mbm	None Detected
49		A2529194	Red	Mpc	None Detected
50		A2529195	Red	Mpc	None Detected
51		A2529196	Red	Mpc	None Detected
52		A2529197A	Beige,Tan	Mf9t	Chrysotile 3%
		A2529197B	Black	Mf9t	Chrysotile 5%
53		A2529198A	Beige,Tan	Mf9t	Chrysotile 3%
		A2529198B	Black	Mf9t	Chrysotile 5%
54		A2529199A	Beige,Tan	Mf9t	Chrysotile 3%
		A2529199B	Black	Mf9t	Chrysotile 5%
55		A2529200A	Off-white,Beige	Mf12t	None Detected
		A2529200B	Clear	Mf12t	None Detected
56		A2529201A	Off-white,Beige	Mf12t	None Detected
		A2529201B	Clear	Mf12t	None Detected
57		A2529202A	Off-white,Beige	Mf12t	None Detected



Asbestos Report Summary

By: POLARIZING LIGHT MICROSCOPY

PROJECT: 6720 25th Av, Kenosha; 0541480

CEI LAB CODE: A17-15138

METHOD: EPA 600 / R93 / 116 and EPA 600 / M4-82 / 020

Client ID	Layer	Lab ID	Color	Sample Description	ASBESTOS %
		A2529202B	Clear	Mf12t	None Detected
58		A2529203A	Brown,Off-white	Mf12n	None Detected
		A2529203B	Clear	Mf12n	None Detected
59		A2529204A	Brown,Off-white	Mf12n	None Detected
		A2529204B	Clear	Mf12n	None Detected
60		A2529205A	Brown,Off-white	Mf12n	None Detected
		A2529205B	Clear	Mf12n	None Detected
61		A2529206	Off-white	Mwc	None Detected
62		A2529207	Off-white	Mwc	None Detected
63		A2529208	Off-white	Mwc	None Detected
64		A2529209	Off-white	Mdc	None Detected
65		A2529210	Off-white	Mdc	None Detected
66		A2529211	Off-white	Mdc	None Detected
67		A2529212A	Brown	Mf12e	Chrysotile 5%
		A2529212B	Tan	Mf12e	None Detected
68		A2529213A	Brown	Mf12e	Chrysotile 5%
		A2529213B	Tan	Mf12e	None Detected
69		A2529214A	Brown	Mf12e	Chrysotile 5%
		A2529214B	Tan	Mf12e	None Detected
70		A2529215	Beige,Tan	Mfl	None Detected
71		A2529216	Beige,Tan	Mfl	None Detected
72		A2529217	Beige,Tan	Mfl	None Detected
73		A2529218	Tan	Mpm	None Detected
74		A2529219	Tan	Mpm	None Detected
75		A2529220	Tan	Mpm	None Detected
76		A2529221	Tan	Mtsm	None Detected
77		A2529222	Tan	Mtsm	None Detected
78		A2529223	Tan	Mtsm	None Detected
79		A2529224	Tan	Mbb	None Detected
80		A2529225	Tan	Mbb	None Detected
81		A2529226	Tan	Mbb	None Detected



Asbestos Report Summary

By: POLARIZING LIGHT MICROSCOPY

PROJECT: 6720 25th Av, Kenosha; 0541480

CEI LAB CODE: A17-15138

METHOD: EPA 600 / R93 / 116 and EPA 600 / M4-82 / 020

Client ID	Layer	Lab ID	Color	Sample Description	ASBESTOS %
82		A2529227A	Green,Off-white	Mf12cg	None Detected
		A2529227B	Clear	Mf12cg	None Detected
83		A2529228A	Green,Off-white	Mf12cg	None Detected
		A2529228B	Clear	Mf12cg	None Detected
84		A2529229A	Green,Off-white	Mf12cg	None Detected
		A2529229B	Clear	Mf12cg	None Detected
85		A2529230A	Green,Gray	Mf12g	None Detected
		A2529230B	Clear	Mf12cg	None Detected
86		A2529231A	Green,Gray	Mf12g	None Detected
		A2529231B	Clear	Mf12g	None Detected
87		A2529232A	Green,Gray	Mf12g	None Detected
		A2529232B	Clear	Mf12g	None Detected
88		A2529233	Black,Brown	Mslk	None Detected
89		A2529234	Black,Brown	Mslk	None Detected
90		A2529235	Black,Brown	Mslk	None Detected
91		A2529236	White	Mwr	None Detected
92		A2529237	White	Mwr	None Detected
93		A2529238	White	Mwr	None Detected
94		A2529239	Green	Mfl Lk	None Detected
95		A2529240	Green	Mfl Lk	None Detected
96		A2529241	Green	Mfl Lk	None Detected
97		A2529242A	Pink,Green	Mf12 P	None Detected
		A2529242B	Clear	Mf12 P	None Detected
98		A2529243A	Pink,Green	Mf12 P	None Detected
		A2529243B	Clear	Mf12 P	None Detected
99		A2529244A	Pink,Green	Mf12 P	None Detected
		A2529244B	Clear	Mf12 P	None Detected
100		A2529245A	White,Gray	Mf12 En	None Detected
		A2529245B	Black	Mf12 En	None Detected
101		A2529246A	White,Gray	Mf12 En	None Detected
		A2529246B	Clear	Mf12 En	None Detected



Asbestos Report Summary

By: POLARIZING LIGHT MICROSCOPY

PROJECT: 6720 25th Av, Kenosha; 0541480

CEI LAB CODE: A17-15138

METHOD: EPA 600 / R93 / 116 and EPA 600 / M4-82 / 020

Client ID	Layer	Lab ID	Color	Sample Description	ASBESTOS %
102		A2529247A	White,Gray	Mf12 En	None Detected
		A2529247B	Clear	Mf12 En	None Detected
103		A2529248A	Gray	Mf12 Ct	None Detected
		A2529248B	Clear	Mf12 Ct	None Detected
104		A2529249A	Gray	Mf12 Ct	None Detected
		A2529249B	Clear	Mf12 Ct	None Detected
105		A2529250A	Gray	Mf12 Ct	None Detected
		A2529250B	Clear	Mf12 Ct	None Detected
106		A2529251A	Gray,White	Mf12 Wk	None Detected
		A2529251B	Clear	Mf12 Wk	None Detected
107		A2529252A	Gray,White	Mf12 Wk	None Detected
		A2529252B	Clear	Mf12 Wk	None Detected
108		A2529253A	Gray,White	Mf12 Wk	None Detected
		A2529253B	Clear	Mf12 Wk	None Detected
109		A2529254	Gray	Mdw	None Detected
110		A2529255	Gray	Mdw	None Detected
111		A2529256	Gray	Mdw	None Detected
112		A2529257A	Brown	Mf9 N	None Detected
		A2529257B	Brown	Mf9 N	None Detected
113		A2529258A	Brown	Mf9 N	None Detected
		A2529258B	Brown	Mf9 N	None Detected
114		A2529259A	Brown	Mf9 N	None Detected
		A2529259B	Brown	Mf9 N	None Detected
115		A2529260	Tan	Mfl C	None Detected
116		A2529261	Tan	Mfl C	None Detected
117		A2529262	Tan	Mfl C	None Detected
118		A2529263A	Black	Mf12 K	None Detected
		A2529263B	Clear	Mf12 K	None Detected
119		A2529264A	Black	Mf12 K	None Detected
		A2529264B	Clear	Mf12 K	None Detected
120		A2529265A	Black	Mf12 K	None Detected



Asbestos Report Summary

By: POLARIZING LIGHT MICROSCOPY

PROJECT: 6720 25th Av, Kenosha; 0541480

CEI LAB CODE: A17-15138

METHOD: EPA 600 / R93 / 116 and EPA 600 / M4-82 / 020

Client ID	Layer	Lab ID	Color	Sample Description	ASBESTOS %
		A2529265B	Clear	Mf12 K	None Detected
121		A2529266	Brown	Mst N	None Detected
122		A2529267	Brown	Mst N	None Detected
123		A2529268	Brown	Mst N	None Detected
124		A2529269A	Gray	Mf12 V	None Detected
		A2529269B	Yellow	Mf12 V	None Detected
125		A2529270A	Gray	Mf12 V	None Detected
		A2529270B	Yellow	Mf12 V	None Detected
126		A2529271A	Gray	Mf12 V	None Detected
		A2529271B	Yellow	Mf12 V	None Detected
127		A2529272A	Tan,Gray	Mf12 Ot	None Detected
		A2529272B	Clear	Mf12 Ot	None Detected
128		A2529273A	Tan,Gray	Mf12 Ot	None Detected
		A2529273B	Clear	Mf12 Ot	None Detected
129		A2529274A	Tan,Gray	Mf12 Ot	None Detected
		A2529274B	Clear	Mf12 Ot	None Detected
130		A2529275A	White,Gray	Mf12 Ect	None Detected
		A2529275B	Clear	Mf12 Ect	None Detected
131		A2529276A	White,Gray	Mf12 Ect	None Detected
		A2529276B	Clear	Mf12 Ect	None Detected
132		A2529277A	White,Gray	Mf12 Ect	None Detected
		A2529277B	Clear	Mf12 Ect	None Detected
133		A2529278	White	Mctm	None Detected
134		A2529279	White	Mctm	None Detected
135		A2529280	White,Yellow	Mctm	None Detected
136		A2529281	White	Mctg	None Detected
137		A2529282	White	Mctg	None Detected
138		A2529283	White	Mctg	None Detected
139		A2529284	White,Black	Mfl Wy	None Detected
140		A2529285	White,Black	Mfl Wy	None Detected
141		A2529286	White,Black	Mfl Wy	None Detected



Asbestos Report Summary

By: POLARIZING LIGHT MICROSCOPY

PROJECT: 6720 25th Av, Kenosha; 0541480

CEI LAB CODE: A17-15138

METHOD: EPA 600 / R93 / 116 and EPA 600 / M4-82 / 020

Client ID	Layer	Lab ID	Color	Sample Description	ASBESTOS %
142		A2529287	White,Gray	Mct1	None Detected
143		A2529288	White,Gray	Mct1	None Detected
144		A2529289	White,Gray	Mct1	None Detected
145		A2529290A	White,Tan	Mf12 Ly	None Detected
		A2529290B	Clear	Mf12 Ly	None Detected
146		A2529291A	White,Tan	Mf12 Ly	None Detected
		A2529291B	Clear	Mf12 Ly	None Detected
147		A2529292A	White,Tan	Mf12 Ly	None Detected
		A2529292B	Clear	Mf12 Ly	None Detected
148		A2529293	Gray,White	Sp1	None Detected
149		A2529294	Gray,White	Sp1	None Detected
150		A2529295	Gray,White	Sp1	None Detected
151		A2529296	Gray,White	Sp1	None Detected
152	Layer 1	A2529297	Green	Sp1	None Detected
	Layer 2	A2529297	Gray	Sp1	None Detected
153	Layer 1	A2529298	White	Sp2	None Detected
	Layer 2	A2529298	Gray	Sp2	None Detected
154	Layer 1	A2529299	White	Sp2	None Detected
	Layer 2	A2529299	Gray	Sp2	None Detected
155	Layer 1	A2529300	White	Sp2	None Detected
	Layer 2	A2529300	Gray	Sp2	None Detected
156	Layer 1	A2529301	White	Sp2	None Detected
	Layer 2	A2529301	Gray	Sp2	None Detected
157	Layer 1	A2529302	White	Sp2	None Detected
	Layer 2	A2529302	Gray	Sp2	None Detected
158	Layer 1	A2529303	White	Sp2	None Detected
	Layer 2	A2529303	Gray	Sp2	None Detected
159	Layer 1	A2529304	White	Sp2	None Detected
	Layer 2	A2529304	Gray	Sp2	None Detected
160	Layer 1	A2529305	White	Sp3	None Detected
	Layer 2	A2529305	Gray	Sp3	None Detected



Asbestos Report Summary

By: POLARIZING LIGHT MICROSCOPY

PROJECT: 6720 25th Av, Kenosha; 0541480

CEI LAB CODE: A17-15138

METHOD: EPA 600 / R93 / 116 and EPA 600 / M4-82 / 020

Client ID	Layer	Lab ID	Color	Sample Description	ASBESTOS %
161	Layer 1	A2529306	White	Sp3	None Detected
	Layer 2	A2529306	White	Sp3	None Detected
	Layer 3	A2529306	Gray	Sp3	None Detected
162	Layer 1	A2529307	White	Sp3	None Detected
	Layer 2	A2529307	Gray	Sp3	None Detected
163		A2529308	Black	Mflr	None Detected
164		A2529309	Black	Mflr	None Detected
165		A2529310	Black	Mflr	None Detected
166		A2529311	Tan	Mff	None Detected
167		A2529312	Tan	Mff	None Detected
168		A2529313	Tan	Mff	None Detected
169		A2529314	Tan	Mfl Ek	None Detected
170		A2529315	Tan	Mfl Ek	None Detected
171		A2529316	Tan	Mfl Ek	None Detected
172		A2529317	Red,Tan	Mfl Ekr	None Detected
173		A2529318	Red,Tan	Mfl Ekr	None Detected
174		A2529319	Red,Tan	Mfl Ekr	None Detected
175		A2529320	Tan	Mfl E	None Detected
176		A2529321	Tan	Mfl E	None Detected
177		A2529322	Tan	Mfl E	None Detected
178		A2529323	Black,Green	Mfl B,g,l,o	None Detected
179		A2529324	Black,Green	Mfl B,g,l,o	None Detected
180		A2529325	Black,Green	Mfl B,g,l,o	None Detected



ASBESTOS BULK ANALYSIS

By: POLARIZING LIGHT MICROSCOPY

Client: PSI
 821 Corporate Ct.
 Waukesha, WI 53189

CEI Lab Code: A17-15138
Date Received: 10-25-17
Date Analyzed: 10-26-17
Date Reported: 10-27-17

Project: 6720 25th Av, Kenosha; 0541480

ASBESTOS BULK PLM, EPA 600 METHOD

Client ID Lab ID	Lab Description	Lab Attributes	NON-ASBESTOS COMPONENTS				ASBESTOS %
			Fibrous	Cellulose	Non-Fibrous		
01 A2529146	Mrtpt	Heterogeneous Black,Brown Fibrous Bound	55%	Cellulose	35% 10%	Tar Binder	None Detected
02 A2529147	Mrtpt	Heterogeneous Black,Brown Fibrous Bound	55%	Cellulose	35% 10%	Tar Binder	None Detected
03 A2529148	Mrtpt	Heterogeneous Black,Brown Fibrous Bound	55%	Cellulose	35% 10%	Tar Binder	None Detected
04 A2529149	Mrs	Heterogeneous Black,Red Fibrous Bound	30%	Cellulose	25% 35% 10%	Tar Gravel Mica	None Detected
05 A2529150	Mrs	Heterogeneous Black,Red Fibrous Bound	30%	Cellulose	25% 35% 10%	Tar Gravel Mica	None Detected
06 A2529151	Mrs	Heterogeneous Black,Red Fibrous Bound	30%	Cellulose	25% 35% 10%	Tar Gravel Mica	None Detected
07 A2529152	Mra1	Heterogeneous Black,Brown Fibrous Bound	25%	Cellulose	45% 15% 10%	Tar Binder Silicates	5% Chrysotile



ASBESTOS BULK ANALYSIS

By: POLARIZING LIGHT MICROSCOPY

Client: PSI
821 Corporate Ct.
Waukesha, WI 53189

CEI Lab Code: A17-15138
Date Received: 10-25-17
Date Analyzed: 10-26-17
Date Reported: 10-27-17

Project: 6720 25th Av, Kenosha; 0541480

ASBESTOS BULK PLM, EPA 600 METHOD

Client ID Lab ID	Lab Description	Lab Attributes	NON-ASBESTOS COMPONENTS				ASBESTOS %
			Fibrous		Non-Fibrous		
08 A2529153	Mra1	Heterogeneous Black,Brown Fibrous Bound	25%	Cellulose	45%	Tar Binder Silicates	5% Chrysotile
09 A2529154	Mra1	Heterogeneous Black,Brown Fibrous Bound	25%	Cellulose	45%	Tar Binder Silicates	5% Chrysotile
10 A2529155	Mra2	Heterogeneous Black,Brown Fibrous Bound	25%	Cellulose	45%	Tar Binder Silicates	5% Chrysotile
11 A2529156	Mra2	Heterogeneous Black,Brown Fibrous Bound	25%	Cellulose	45%	Tar Binder Silicates	5% Chrysotile
12 A2529157	Mra2	Heterogeneous Black,Brown Fibrous Bound	25%	Cellulose	45%	Tar Binder Silicates	5% Chrysotile
13 A2529158	Mra3	Heterogeneous Black,Gray Fibrous Bound	10% 25%	Cellulose Synthetic Fiber	25% 30%	Tar Vinyl Binder	None Detected
14 A2529159	Mra3	Heterogeneous Black,Gray Fibrous Bound	10% 25%	Cellulose Synthetic Fiber	25% 30%	Tar Vinyl Binder	None Detected



ASBESTOS BULK ANALYSIS

By: POLARIZING LIGHT MICROSCOPY

Client: PSI
 821 Corporate Ct.
 Waukesha, WI 53189

CEI Lab Code: A17-15138
Date Received: 10-25-17
Date Analyzed: 10-26-17
Date Reported: 10-27-17

Project: 6720 25th Av, Kenosha; 0541480

ASBESTOS BULK PLM, EPA 600 METHOD

Client ID Lab ID	Lab Description	Lab Attributes	NON-ASBESTOS COMPONENTS				ASBESTOS %
			Fibrous		Non-Fibrous		
15 A2529160	Mra3	Heterogeneous Black,Gray Fibrous Bound	10%	Cellulose	25%	Tar	None Detected
			25%	Synthetic Fiber	30%	Vinyl	
					10%	Binder	
16 A2529161	Mrs2	Heterogeneous Black,Gray Fibrous Bound	25%	Fiberglass	25%	Tar	None Detected
					40%	Gravel	
					10%	Silicates	
17 A2529162	Mrs2	Heterogeneous Black,Gray Fibrous Bound	25%	Fiberglass	25%	Tar	None Detected
					40%	Gravel	
					10%	Silicates	
18 A2529163	Mrs2	Heterogeneous Black,Gray Fibrous Bound	25%	Fiberglass	25%	Tar	None Detected
					40%	Gravel	
					10%	Silicates	
19 A2529164	Mra	Heterogeneous Black,Gray Fibrous Bound	25%	Fiberglass	25%	Tar	None Detected
					40%	Gravel	
					10%	Silicates	
20 A2529165	Mra	Heterogeneous Black,Gray Fibrous Bound	25%	Fiberglass	25%	Tar	None Detected
					40%	Gravel	
					10%	Silicates	
21 A2529166	Mra	Heterogeneous Black,Gray Fibrous Bound	25%	Fiberglass	25%	Tar	None Detected
					40%	Gravel	
					10%	Silicates	



ASBESTOS BULK ANALYSIS

By: POLARIZING LIGHT MICROSCOPY

Client: PSI
 821 Corporate Ct.
 Waukesha, WI 53189

CEI Lab Code: A17-15138
Date Received: 10-25-17
Date Analyzed: 10-26-17
Date Reported: 10-27-17

Project: 6720 25th Av, Kenosha; 0541480

ASBESTOS BULK PLM, EPA 600 METHOD

Client ID Lab ID	Lab Description	Lab Attributes	NON-ASBESTOS COMPONENTS				ASBESTOS %
			Fibrous	Cellulose	Non-Fibrous		
22 A2529167	Mpge	Heterogeneous Beige,Off-white Fibrous Bound	<1%	Cellulose	85% 5% 10%	Caulk Binder Paint	None Detected
23 A2529168	Mpge	Heterogeneous Beige,Off-white Fibrous Bound	<1%	Cellulose	85% 5% 10%	Caulk Binder Paint	None Detected
24 A2529169	Mpge	Heterogeneous Beige,Off-white Fibrous Bound	<1%	Cellulose	85% 5% 10%	Caulk Binder Paint	None Detected
25 A2529170	Mpge2	Heterogeneous White Fibrous Bound	<1%	Cellulose	90% 10%	Caulk Binder	None Detected
26 A2529171	Mpge2	Heterogeneous White Fibrous Bound	<1%	Cellulose	90% 10%	Caulk Binder	None Detected
27 A2529172	Mpge2	Heterogeneous White Fibrous Bound	<1%	Cellulose	90% 10%	Caulk Binder	None Detected
28 A2529173	Mwce	Heterogeneous Off-white,Gray Fibrous Bound	<1%	Cellulose	90% 10%	Caulk Binder	None Detected



ASBESTOS BULK ANALYSIS

By: POLARIZING LIGHT MICROSCOPY

Client: PSI
821 Corporate Ct.
Waukesha, WI 53189

CEI Lab Code: A17-15138
Date Received: 10-25-17
Date Analyzed: 10-26-17
Date Reported: 10-27-17

Project: 6720 25th Av, Kenosha; 0541480

ASBESTOS BULK PLM, EPA 600 METHOD

Client ID Lab ID	Lab Description	Lab Attributes	NON-ASBESTOS COMPONENTS				ASBESTOS %
			Fibrous	Cellulose	Non-Fibrous		
29 A2529174	Mwce	Heterogeneous Off-white, Gray Fibrous Bound	<1%	Cellulose	90%	Caulk Binder	None Detected
30 A2529175	Mwce	Heterogeneous Off-white, Gray Fibrous Bound	<1%	Cellulose	90%	Caulk Binder	None Detected
31 A2529176	Mts	Heterogeneous Off-white, Gray Fibrous Tightly Bound	<1%	Cellulose	70%	Calc Carb Binder Paint	15% Chrysotile
32 A2529177	Mts	Heterogeneous Off-white, Gray Fibrous Tightly Bound	<1%	Cellulose	70%	Calc Carb Binder Paint	15% Chrysotile
33 A2529178	Mts	Heterogeneous Off-white, Gray Fibrous Tightly Bound	<1%	Cellulose	70%	Calc Carb Binder Paint	15% Chrysotile
34 A2529179	Mstp	Heterogeneous Black, Brown Fibrous Bound	55%	Cellulose	35%	Tar Binder	None Detected
35 A2529180	Mstp	Heterogeneous Black, Brown Fibrous Bound	55%	Cellulose	35%	Tar Binder	None Detected



ASBESTOS BULK ANALYSIS

By: POLARIZING LIGHT MICROSCOPY

Client: PSI
 821 Corporate Ct.
 Waukesha, WI 53189

CEI Lab Code: A17-15138
Date Received: 10-25-17
Date Analyzed: 10-26-17
Date Reported: 10-27-17

Project: 6720 25th Av, Kenosha; 0541480

ASBESTOS BULK PLM, EPA 600 METHOD

Client ID Lab ID	Lab Description	Lab Attributes	NON-ASBESTOS COMPONENTS				ASBESTOS %
			Fibrous		Non-Fibrous		
36 A2529181	Mstp	Heterogeneous Black,Brown Fibrous Bound	55%	Cellulose	35%	Tar 10% Binder	None Detected
37 A2529182	Mpce	Heterogeneous Gray Fibrous Bound	<1%	Cellulose	90%	Caulk 10% Binder	None Detected
38 A2529183	Mpce	Heterogeneous Gray Fibrous Bound	<1%	Cellulose	90%	Caulk 10% Binder	None Detected
39 A2529184	Mpce	Heterogeneous Gray Fibrous Bound	<1%	Cellulose	90%	Caulk 10% Binder	None Detected
40 A2529185	Msc1	Heterogeneous Gray,Off-white Fibrous Bound	35% 25%	Cellulose Fiberglass	10% 10%	Binder Paint 20% Perlite	None Detected
41 A2529186	Msc1	Heterogeneous Gray,Off-white Fibrous Bound	35% 25%	Cellulose Fiberglass	10% 10%	Binder Paint 20% Perlite	None Detected
42 A2529187	Msc1	Heterogeneous Gray,Off-white Fibrous Bound	35% 25%	Cellulose Fiberglass	10% 10%	Binder Paint 20% Perlite	None Detected



ASBESTOS BULK ANALYSIS

By: POLARIZING LIGHT MICROSCOPY

Client: PSI
 821 Corporate Ct.
 Waukesha, WI 53189

CEI Lab Code: A17-15138
Date Received: 10-25-17
Date Analyzed: 10-26-17
Date Reported: 10-27-17

Project: 6720 25th Av, Kenosha; 0541480

ASBESTOS BULK PLM, EPA 600 METHOD

Client ID Lab ID	Lab Description	Lab Attributes	NON-ASBESTOS COMPONENTS				ASBESTOS %
			Fibrous		Non-Fibrous		
43 A2529188	MB	Heterogeneous			30%	Silicates	None Detected
		Red			70%	Binder	
		Non-fibrous					
		Tightly Bound					
44 A2529189	MB	Heterogeneous			30%	Silicates	None Detected
		Red			70%	Binder	
		Non-fibrous					
		Tightly Bound					
45 A2529190	MB	Heterogeneous			30%	Silicates	None Detected
		Red			70%	Binder	
		Non-fibrous					
		Tightly Bound					
46 A2529191	Mbm	Heterogeneous	<1%	Cellulose	50%	Calc Carb	None Detected
		Gray			40%	Silicates	
		Fibrous			10%	Binder	
		Tightly Bound					
47 A2529192	Mbm	Heterogeneous	<1%	Cellulose	50%	Calc Carb	None Detected
		Gray			40%	Silicates	
		Fibrous			10%	Binder	
		Tightly Bound					
48 A2529193	Mbm	Heterogeneous	<1%	Cellulose	50%	Calc Carb	None Detected
		Gray			40%	Silicates	
		Fibrous			10%	Binder	
		Tightly Bound					
49 A2529194	Mpc	Heterogeneous	<1%	Cellulose	90%	Caulk	None Detected
		Red			10%	Binder	
		Fibrous					
		Bound					



ASBESTOS BULK ANALYSIS

By: POLARIZING LIGHT MICROSCOPY

Client: PSI
821 Corporate Ct.
Waukesha, WI 53189

CEI Lab Code: A17-15138
Date Received: 10-25-17
Date Analyzed: 10-26-17
Date Reported: 10-27-17

Project: 6720 25th Av, Kenosha; 0541480

ASBESTOS BULK PLM, EPA 600 METHOD

Client ID Lab ID	Lab Description	Lab Attributes	NON-ASBESTOS COMPONENTS				ASBESTOS %
			Fibrous		Non-Fibrous		
50 A2529195	Mpc	Heterogeneous Red Fibrous Bound	<1%	Cellulose	90%	Caulk 10% Binder	None Detected
51 A2529196	Mpc	Heterogeneous Red Fibrous Bound	<1%	Cellulose	90%	Caulk 10% Binder	None Detected
52 A2529197A	Mf9t	Heterogeneous Beige,Tan Fibrous Tightly Bound	<1%	Cellulose	85%	Vinyl 12% Calc Carb	3% Chrysotile
A2529197B	Mf9t	Heterogeneous Black Fibrous Bound	<1%	Cellulose	95%	Mastic	5% Chrysotile
Lab Notes: Mastic layer.							
53 A2529198A	Mf9t	Heterogeneous Beige,Tan Fibrous Tightly Bound	<1%	Cellulose	85%	Vinyl 12% Calc Carb	3% Chrysotile
A2529198B	Mf9t	Heterogeneous Black Fibrous Bound	<1%	Cellulose	95%	Mastic	5% Chrysotile
Lab Notes: Mastic layer,							
54 A2529199A	Mf9t	Heterogeneous Beige,Tan Fibrous Tightly Bound	<1%	Cellulose	85%	Vinyl 12% Calc Carb	3% Chrysotile



ASBESTOS BULK ANALYSIS

By: POLARIZING LIGHT MICROSCOPY

Client: PSI
821 Corporate Ct.
Waukesha, WI 53189

CEI Lab Code: A17-15138
Date Received: 10-25-17
Date Analyzed: 10-26-17
Date Reported: 10-27-17

Project: 6720 25th Av, Kenosha; 0541480

ASBESTOS BULK PLM, EPA 600 METHOD

Client ID Lab ID	Lab Description	Lab Attributes	NON-ASBESTOS COMPONENTS				ASBESTOS %
			Fibrous		Non-Fibrous		
A2529199B	Mf9t	Heterogeneous Black Fibrous Bound	<1%	Cellulose	95%	Mastic	5% Chrysotile
Lab Notes: Mastic layer.							
55 A2529200A	Mf12t	Heterogeneous Off-white,Beige Fibrous Tightly Bound	<1%	Cellulose	90%	Vinyl	None Detected
					10%	Calc Carb	
A2529200B	Mf12t	Heterogeneous Clear Fibrous Bound	2%	Cellulose	98%	Mastic	None Detected
Lab Notes: Mastic layer.							
56 A2529201A	Mf12t	Heterogeneous Off-white,Beige Fibrous Tightly Bound	<1%	Cellulose	90%	Vinyl	None Detected
					10%	Calc Carb	
A2529201B	Mf12t	Heterogeneous Clear Fibrous Bound	2%	Cellulose	98%	Mastic	None Detected
Lab Notes: Mastic layer							
57 A2529202A	Mf12t	Heterogeneous Off-white,Beige Fibrous Tightly Bound	<1%	Cellulose	90%	Vinyl	None Detected
					10%	Calc Carb	



ASBESTOS BULK ANALYSIS

By: POLARIZING LIGHT MICROSCOPY

Client: PSI
 821 Corporate Ct.
 Waukesha, WI 53189

CEI Lab Code: A17-15138
Date Received: 10-25-17
Date Analyzed: 10-26-17
Date Reported: 10-27-17

Project: 6720 25th Av, Kenosha; 0541480

ASBESTOS BULK PLM, EPA 600 METHOD

Client ID Lab ID	Lab Description	Lab Attributes	NON-ASBESTOS COMPONENTS				ASBESTOS %
			Fibrous		Non-Fibrous		
A2529202B	Mf12t	Heterogeneous Clear Fibrous Bound	2%	Cellulose	98%	Mastic	None Detected
Lab Notes: Mastic layer.							
58 A2529203A	Mf12n	Heterogeneous Brown,Off-white Fibrous Tightly Bound	<1%	Cellulose	90%	Vinyl	None Detected
					10%	Calc Carb	
A2529203B	Mf12n	Heterogeneous Clear Fibrous Bound	2%	Cellulose	98%	Mastic	None Detected
Lab Notes: Mastic layer.							
59 A2529204A	Mf12n	Heterogeneous Brown,Off-white Fibrous Tightly Bound	<1%	Cellulose	90%	Vinyl	None Detected
					10%	Calc Carb	
A2529204B	Mf12n	Heterogeneous Clear Fibrous Bound	2%	Cellulose	98%	Mastic	None Detected
Lab Notes: Mastic layer.							
60 A2529205A	Mf12n	Heterogeneous Brown,Off-white Fibrous Tightly Bound	<1%	Cellulose	90%	Vinyl	None Detected
					10%	Calc Carb	



ASBESTOS BULK ANALYSIS

By: POLARIZING LIGHT MICROSCOPY

Client: PSI
 821 Corporate Ct.
 Waukesha, WI 53189

CEI Lab Code: A17-15138
Date Received: 10-25-17
Date Analyzed: 10-26-17
Date Reported: 10-27-17

Project: 6720 25th Av, Kenosha; 0541480

ASBESTOS BULK PLM, EPA 600 METHOD

Client ID Lab ID	Lab Description	Lab Attributes	NON-ASBESTOS COMPONENTS			ASBESTOS %	
			Fibrous	Non-Fibrous			
A2529205B	Mf12n	Heterogeneous Clear Fibrous Bound	2%	Cellulose	98%	Mastic	None Detected
Lab Notes: Mastic layer.							
61 A2529206	Mwc	Heterogeneous Off-white Fibrous Bound	<1%	Cellulose	90%	Caulk 10% Binder	None Detected
62 A2529207	Mwc	Heterogeneous Off-white Fibrous Bound	<1%	Cellulose	90%	Caulk 10% Binder	None Detected
63 A2529208	Mwc	Heterogeneous Off-white Fibrous Bound	<1%	Cellulose	90%	Caulk 10% Binder	None Detected
64 A2529209	Mdc	Heterogeneous Off-white Fibrous Bound	<1%	Cellulose	90%	Caulk 10% Binder	None Detected
65 A2529210	Mdc	Heterogeneous Off-white Fibrous Bound	<1%	Cellulose	90%	Caulk 10% Binder	None Detected
66 A2529211	Mdc	Heterogeneous Off-white Fibrous Bound	<1%	Cellulose	90%	Caulk 10% Binder	None Detected



ASBESTOS BULK ANALYSIS

By: POLARIZING LIGHT MICROSCOPY

Client: PSI
821 Corporate Ct.
Waukesha, WI 53189

CEI Lab Code: A17-15138
Date Received: 10-25-17
Date Analyzed: 10-26-17
Date Reported: 10-27-17

Project: 6720 25th Av, Kenosha; 0541480

ASBESTOS BULK PLM, EPA 600 METHOD

Client ID Lab ID	Lab Description	Lab Attributes	NON-ASBESTOS COMPONENTS				ASBESTOS %
			Fibrous		Non-Fibrous		
67 A2529212A	Mf12e	Heterogeneous Brown Fibrous Tightly Bound	<1%	Cellulose	85%	Vinyl	5% Chrysotile
A2529212B	Mf12e	Heterogeneous Tan Fibrous Bound	2%	Cellulose	98%	Mastic	None Detected
Lab Notes: Mastic layer.							
68 A2529213A	Mf12e	Heterogeneous Brown Fibrous Tightly Bound	<1%	Cellulose	85%	Vinyl	5% Chrysotile
A2529213B	Mf12e	Heterogeneous Tan Fibrous Bound	2%	Cellulose	98%	Mastic	None Detected
Lab Notes: Mastic layer.							
69 A2529214A	Mf12e	Heterogeneous Brown Fibrous Tightly Bound	<1%	Cellulose	85%	Vinyl	5% Chrysotile
A2529214B	Mf12e	Heterogeneous Tan Fibrous Bound	2%	Cellulose	98%	Mastic	None Detected
Lab Notes: Mastic layer.							
70 A2529215	Mfl	Heterogeneous Beige, Tan Fibrous Bound	15%	Cellulose	50%	Vinyl	None Detected
			10%	Fiberglass	20%	Binder	
					5%	Mastic	



ASBESTOS BULK ANALYSIS

By: POLARIZING LIGHT MICROSCOPY

Client: PSI
 821 Corporate Ct.
 Waukesha, WI 53189

CEI Lab Code: A17-15138
Date Received: 10-25-17
Date Analyzed: 10-26-17
Date Reported: 10-27-17

Project: 6720 25th Av, Kenosha; 0541480

ASBESTOS BULK PLM, EPA 600 METHOD

Client ID Lab ID	Lab Description	Lab Attributes	NON-ASBESTOS COMPONENTS				ASBESTOS %
			Fibrous		Non-Fibrous		
71 A2529216	Mfl	Heterogeneous	15%	Cellulose	50%	Vinyl	None Detected
		Beige,Tan	10%	Fiberglass	20%	Binder	
		Fibrous Bound			5%	Mastic	
72 A2529217	Mfl	Heterogeneous	15%	Cellulose	50%	Vinyl	None Detected
		Beige,Tan	10%	Fiberglass	20%	Binder	
		Fibrous Bound			5%	Mastic	
73 A2529218	Mpm	Heterogeneous	2%	Cellulose	98%	Mastic	None Detected
		Tan					
		Fibrous Bound					
74 A2529219	Mpm	Heterogeneous	2%	Cellulose	98%	Mastic	None Detected
		Tan					
		Fibrous Bound					
75 A2529220	Mpm	Heterogeneous	2%	Cellulose	98%	Mastic	None Detected
		Tan					
		Fibrous Bound					
76 A2529221	Mtsm	Heterogeneous	2%	Cellulose	98%	Mastic	None Detected
		Tan					
		Fibrous Bound					
77 A2529222	Mtsm	Heterogeneous	2%	Cellulose	98%	Mastic	None Detected
		Tan					
		Fibrous Bound					



ASBESTOS BULK ANALYSIS

By: POLARIZING LIGHT MICROSCOPY

Client: PSI
 821 Corporate Ct.
 Waukesha, WI 53189

CEI Lab Code: A17-15138
Date Received: 10-25-17
Date Analyzed: 10-26-17
Date Reported: 10-27-17

Project: 6720 25th Av, Kenosha; 0541480

ASBESTOS BULK PLM, EPA 600 METHOD

Client ID Lab ID	Lab Description	Lab Attributes	NON-ASBESTOS COMPONENTS				ASBESTOS %
			Fibrous		Non-Fibrous		
78 A2529223	Mtsm	Heterogeneous Tan Fibrous Bound	2%	Cellulose	98%	Mastic	None Detected
79 A2529224	Mbb	Heterogeneous Tan Fibrous Bound	<1%	Cellulose	85%	Calc Carb Binder	None Detected
80 A2529225	Mbb	Heterogeneous Tan Fibrous Bound	<1%	Cellulose	85%	Calc Carb Binder	None Detected
81 A2529226	Mbb	Heterogeneous Tan Fibrous Bound	<1%	Cellulose	85%	Calc Carb Binder	None Detected
82 A2529227A	Mf12cg	Heterogeneous Green,Off-white Fibrous Tightly Bound	<1%	Cellulose	90%	Vinyl Calc Carb	None Detected
A2529227B	Mf12cg	Heterogeneous Clear Fibrous Bound	2%	Cellulose	98%	Mastic	None Detected
Lab Notes: Mastic layer.							
83 A2529228A	Mf12cg	Heterogeneous Green,Off-white Fibrous Tightly Bound	<1%	Cellulose	90%	Vinyl Calc Carb	None Detected



ASBESTOS BULK ANALYSIS

By: POLARIZING LIGHT MICROSCOPY

Client: PSI
 821 Corporate Ct.
 Waukesha, WI 53189

CEI Lab Code: A17-15138
Date Received: 10-25-17
Date Analyzed: 10-26-17
Date Reported: 10-27-17

Project: 6720 25th Av, Kenosha; 0541480

ASBESTOS BULK PLM, EPA 600 METHOD

Client ID Lab ID	Lab Description	Lab Attributes	NON-ASBESTOS COMPONENTS				ASBESTOS %
			Fibrous		Non-Fibrous		
A2529228B	Mf12cg	Heterogeneous Clear Fibrous Bound	2%	Cellulose	98%	Mastic	None Detected
Lab Notes: Mastic layer.							
84 A2529229A	Mf12cg	Heterogeneous Green,Off-white Fibrous Tightly Bound	<1%	Cellulose	90%	Vinyl	None Detected
					10%	Calc Carb	
A2529229B	Mf12cg	Heterogeneous Clear Fibrous Bound	2%	Cellulose	98%	Mastic	None Detected
Lab Notes: Mastic layer.							
85 A2529230A	Mf12g	Heterogeneous Green,Gray Fibrous Tightly Bound	2%	Cellulose	85%	Vinyl	None Detected
					13%	Calc Carb	
A2529230B	Mf12cg	Heterogeneous Clear Fibrous Bound	2%	Cellulose	98%	Mastic	None Detected
Lab Notes: Mastic layer.							
86 A2529231A	Mf12g	Heterogeneous Green,Gray Fibrous Tightly Bound	2%	Cellulose	85%	Vinyl	None Detected
					13%	Calc Carb	



ASBESTOS BULK ANALYSIS

By: POLARIZING LIGHT MICROSCOPY

Client: PSI
 821 Corporate Ct.
 Waukesha, WI 53189

CEI Lab Code: A17-15138
Date Received: 10-25-17
Date Analyzed: 10-26-17
Date Reported: 10-27-17

Project: 6720 25th Av, Kenosha; 0541480

ASBESTOS BULK PLM, EPA 600 METHOD

Client ID Lab ID	Lab Description	Lab Attributes	NON-ASBESTOS COMPONENTS				ASBESTOS %
			Fibrous		Non-Fibrous		
A2529231B	Mf12g	Heterogeneous Clear Fibrous Bound	2%	Cellulose	98%	Mastic	None Detected
Lab Notes: Mastic layer.							
87 A2529232A	Mf12g	Heterogeneous Green,Gray Fibrous Tightly Bound	2%	Cellulose	85%	Vinyl	None Detected
					13%	Calc Carb	
A2529232B	Mf12g	Heterogeneous Clear Fibrous Bound	2%	Cellulose	98%	Mastic	None Detected
Lab Notes: Mastic layer.							
88 A2529233	Mslk	Heterogeneous Black,Brown Fibrous Bound	10%	Cellulose	80%	Mastic	None Detected
					10%	Binder	
89 A2529234	Mslk	Heterogeneous Black,Brown Fibrous Bound	10%	Cellulose	80%	Mastic	None Detected
					10%	Binder	
90 A2529235	Mslk	Heterogeneous Black,Brown Fibrous Bound	10%	Cellulose	80%	Mastic	None Detected
					10%	Binder	
91 A2529236	Mwr	Heterogeneous White Fibrous Loosely Bound	90%	Cellulose	5%	Binder	None Detected
					5%	Paint	



ASBESTOS BULK ANALYSIS

By: POLARIZING LIGHT MICROSCOPY

Client: PSI
 821 Corporate Ct.
 Waukesha, WI 53189

CEI Lab Code: A17-15138
Date Received: 10-25-17
Date Analyzed: 10-26-17
Date Reported: 10-27-17

Project: 6720 25th Av, Kenosha; 0541480

ASBESTOS BULK PLM, EPA 600 METHOD

Client ID Lab ID	Lab Description	Lab Attributes	NON-ASBESTOS COMPONENTS				ASBESTOS %
			Fibrous	Non-Fibrous			
92 A2529237	Mwr	Heterogeneous White Fibrous Loosely Bound	90%	Cellulose	5%	Binder Paint	None Detected
93 A2529238	Mwr	Heterogeneous White Fibrous Loosely Bound	90%	Cellulose	5%	Binder Paint	None Detected
94 A2529239	Mfl Lk	Heterogeneous Green Fibrous Bound	25%	Cellulose	50%	Vinyl Binder Mastic	None Detected
95 A2529240	Mfl Lk	Heterogeneous Green Fibrous Bound	25%	Cellulose	50%	Vinyl Binder Mastic	None Detected
96 A2529241	Mfl Lk	Heterogeneous Green Fibrous Bound	25%	Cellulose	50%	Vinyl Binder Mastic	None Detected
97 A2529242A	Mf12 P	Heterogeneous Pink, Green Fibrous Bound	2%	Cellulose	70%	Vinyl Calc Carb Binder	None Detected
A2529242B	Mf12 P	Heterogeneous Clear Fibrous Bound	2%	Cellulose	98%	Mastic	None Detected



ASBESTOS BULK ANALYSIS

By: POLARIZING LIGHT MICROSCOPY

Client: PSI
 821 Corporate Ct.
 Waukesha, WI 53189

CEI Lab Code: A17-15138
Date Received: 10-25-17
Date Analyzed: 10-26-17
Date Reported: 10-27-17

Project: 6720 25th Av, Kenosha; 0541480

ASBESTOS BULK PLM, EPA 600 METHOD

Client ID Lab ID	Lab Description	Lab Attributes	NON-ASBESTOS COMPONENTS				ASBESTOS %
			Fibrous		Non-Fibrous		
98 A2529243A	Mf12 P	Heterogeneous Pink,Green Fibrous Bound	2%	Cellulose	70%	Vinyl 20% Calc Carb 8% Binder	None Detected
A2529243B	Mf12 P	Heterogeneous Clear Fibrous Bound	2%	Cellulose	98%	Mastic	None Detected
99 A2529244A	Mf12 P	Heterogeneous Pink,Green Fibrous Bound	2%	Cellulose	70%	Vinyl 20% Calc Carb 8% Binder	None Detected
A2529244B	Mf12 P	Heterogeneous Clear Fibrous Bound	2%	Cellulose	98%	Mastic	None Detected
100 A2529245A	Mf12 En	Heterogeneous White,Gray Fibrous Bound	2%	Cellulose	70%	Vinyl 20% Calc Carb 8% Binder	None Detected
A2529245B	Mf12 En	Heterogeneous Black Fibrous Bound	2%	Cellulose	98%	Mastic	None Detected
101 A2529246A	Mf12 En	Heterogeneous White,Gray Fibrous Bound	2%	Cellulose	70%	Vinyl 20% Calc Carb 8% Binder	None Detected



ASBESTOS BULK ANALYSIS

By: POLARIZING LIGHT MICROSCOPY

Client: PSI
 821 Corporate Ct.
 Waukesha, WI 53189

CEI Lab Code: A17-15138
Date Received: 10-25-17
Date Analyzed: 10-26-17
Date Reported: 10-27-17

Project: 6720 25th Av, Kenosha; 0541480

ASBESTOS BULK PLM, EPA 600 METHOD

Client ID Lab ID	Lab Description	Lab Attributes	NON-ASBESTOS COMPONENTS				ASBESTOS %
			Fibrous		Non-Fibrous		
A2529246B	Mf12 En	Heterogeneous Clear Fibrous Bound	2%	Cellulose	98%	Mastic	None Detected
102 A2529247A	Mf12 En	Heterogeneous White, Gray Fibrous Bound	2%	Cellulose	70% 20% 8%	Vinyl Calc Carb Binder	None Detected
A2529247B	Mf12 En	Heterogeneous Clear Fibrous Bound	2%	Cellulose	98%	Mastic	None Detected
103 A2529248A	Mf12 Ct	Heterogeneous Gray Fibrous Bound	2%	Cellulose	70% 20% 8%	Vinyl Calc Carb Binder	None Detected
A2529248B	Mf12 Ct	Heterogeneous Clear Fibrous Bound	2%	Cellulose	98%	Mastic	None Detected
104 A2529249A	Mf12 Ct	Heterogeneous Gray Fibrous Bound	2%	Cellulose	70% 20% 8%	Vinyl Calc Carb Binder	None Detected
A2529249B	Mf12 Ct	Heterogeneous Clear Fibrous Bound	2%	Cellulose	98%	Mastic	None Detected



ASBESTOS BULK ANALYSIS

By: POLARIZING LIGHT MICROSCOPY

Client: PSI
 821 Corporate Ct.
 Waukesha, WI 53189

CEI Lab Code: A17-15138
Date Received: 10-25-17
Date Analyzed: 10-26-17
Date Reported: 10-27-17

Project: 6720 25th Av, Kenosha; 0541480

ASBESTOS BULK PLM, EPA 600 METHOD

Client ID Lab ID	Lab Description	Lab Attributes	NON-ASBESTOS COMPONENTS				ASBESTOS %
			Fibrous		Non-Fibrous		
105 A2529250A	Mf12 Ct	Heterogeneous Gray Fibrous Bound	2%	Cellulose	70%	Vinyl 20% Calc Carb 8% Binder	None Detected
A2529250B	Mf12 Ct	Heterogeneous Clear Fibrous Bound	2%	Cellulose	98%	Mastic	None Detected
106 A2529251A	Mf12 Wk	Heterogeneous Gray,White Fibrous Bound	2%	Cellulose	70%	Vinyl 20% Calc Carb 8% Binder	None Detected
A2529251B	Mf12 Wk	Heterogeneous Clear Fibrous Bound	2%	Cellulose	98%	Mastic	None Detected
107 A2529252A	Mf12 Wk	Heterogeneous Gray,White Fibrous Bound	2%	Cellulose	70%	Vinyl 20% Calc Carb 8% Binder	None Detected
A2529252B	Mf12 Wk	Heterogeneous Clear Fibrous Bound	2%	Cellulose	98%	Mastic	None Detected
108 A2529253A	Mf12 Wk	Heterogeneous Gray,White Fibrous Bound	2%	Cellulose	70%	Vinyl 20% Calc Carb 8% Binder	None Detected



ASBESTOS BULK ANALYSIS

By: POLARIZING LIGHT MICROSCOPY

Client: PSI
 821 Corporate Ct.
 Waukesha, WI 53189

CEI Lab Code: A17-15138
Date Received: 10-25-17
Date Analyzed: 10-26-17
Date Reported: 10-27-17

Project: 6720 25th Av, Kenosha; 0541480

ASBESTOS BULK PLM, EPA 600 METHOD

Client ID Lab ID	Lab Description	Lab Attributes	NON-ASBESTOS COMPONENTS				ASBESTOS %
			Fibrous		Non-Fibrous		
A2529253B	Mf12 Wk	Heterogeneous Clear Fibrous Bound	2%	Cellulose	98%	Mastic	None Detected
109 A2529254	Mdw	Heterogeneous Gray Fibrous Loosely Bound	5%	Cellulose	70%	Gypsum 25% Binder	None Detected
110 A2529255	Mdw	Heterogeneous Gray Fibrous Loosely Bound	5%	Cellulose	70%	Gypsum 25% Binder	None Detected
111 A2529256	Mdw	Heterogeneous Gray Fibrous Loosely Bound	5%	Cellulose	70%	Gypsum 25% Binder	None Detected
112 A2529257A	Mf9 N	Heterogeneous Brown Non-fibrous Bound			100%	Vinyl	None Detected
A2529257B	Mf9 N	Heterogeneous Brown Non-fibrous Bound			100%	Mastic	None Detected
113 A2529258A	Mf9 N	Heterogeneous Brown Non-fibrous Bound			100%	Vinyl	None Detected



ASBESTOS BULK ANALYSIS

By: POLARIZING LIGHT MICROSCOPY

Client: PSI
 821 Corporate Ct.
 Waukesha, WI 53189

CEI Lab Code: A17-15138
Date Received: 10-25-17
Date Analyzed: 10-26-17
Date Reported: 10-27-17

Project: 6720 25th Av, Kenosha; 0541480

ASBESTOS BULK PLM, EPA 600 METHOD

Client ID Lab ID	Lab Description	Lab Attributes	NON-ASBESTOS COMPONENTS				ASBESTOS %
			Fibrous		Non-Fibrous		
A2529258B	Mf9 N	Heterogeneous Brown Non-fibrous Bound	100%		Mastic		None Detected
114 A2529259A	Mf9 N	Heterogeneous Brown Non-fibrous Bound	100%		Vinyl		None Detected
A2529259B	Mf9 N	Heterogeneous Brown Non-fibrous Bound	100%		Mastic		None Detected
115 A2529260	Mfl C	Heterogeneous Tan Fibrous Bound	25%	Cellulose	50%	Vinyl Binder Mastic	None Detected
116 A2529261	Mfl C	Heterogeneous Tan Fibrous Bound	25%	Cellulose	50%	Vinyl Binder Mastic	None Detected
117 A2529262	Mfl C	Heterogeneous Tan Fibrous Bound	25%	Cellulose	50%	Vinyl Binder Mastic	None Detected
118 A2529263A	Mf12 K	Heterogeneous Black Fibrous Bound	2%	Cellulose	70%	Vinyl Calc Carb Binder	None Detected



ASBESTOS BULK ANALYSIS

By: POLARIZING LIGHT MICROSCOPY

Client: PSI
 821 Corporate Ct.
 Waukesha, WI 53189

CEI Lab Code: A17-15138
Date Received: 10-25-17
Date Analyzed: 10-26-17
Date Reported: 10-27-17

Project: 6720 25th Av, Kenosha; 0541480

ASBESTOS BULK PLM, EPA 600 METHOD

Client ID Lab ID	Lab Description	Lab Attributes	NON-ASBESTOS COMPONENTS				ASBESTOS %
			Fibrous		Non-Fibrous		
A2529263B	Mf12 K	Heterogeneous Clear Fibrous Bound	2%	Cellulose	98%	Mastic	None Detected
119 A2529264A	Mf12 K	Heterogeneous Black Fibrous Bound	2%	Cellulose	70%	Vinyl 20% Calc Carb 8% Binder	None Detected
A2529264B	Mf12 K	Heterogeneous Clear Fibrous Bound	2%	Cellulose	98%	Mastic	None Detected
120 A2529265A	Mf12 K	Heterogeneous Black Fibrous Bound	2%	Cellulose	70%	Vinyl 20% Calc Carb 8% Binder	None Detected
A2529265B	Mf12 K	Heterogeneous Clear Fibrous Bound	2%	Cellulose	98%	Mastic	None Detected
121 A2529266	Mst N	Heterogeneous Brown Non-fibrous Bound			100%	Vinyl	None Detected
122 A2529267	Mst N	Heterogeneous Brown Non-fibrous Bound			100%	Vinyl	None Detected



ASBESTOS BULK ANALYSIS

By: POLARIZING LIGHT MICROSCOPY

Client: PSI
 821 Corporate Ct.
 Waukesha, WI 53189

CEI Lab Code: A17-15138
Date Received: 10-25-17
Date Analyzed: 10-26-17
Date Reported: 10-27-17

Project: 6720 25th Av, Kenosha; 0541480

ASBESTOS BULK PLM, EPA 600 METHOD

Client ID Lab ID	Lab Description	Lab Attributes	NON-ASBESTOS COMPONENTS				ASBESTOS %
			Fibrous		Non-Fibrous		
123 A2529268	Mst N	Heterogeneous Brown Non-fibrous Bound			100%	Vinyl	None Detected
124 A2529269A	Mf12 V	Heterogeneous Gray Fibrous Bound	2%	Cellulose	60%	Vinyl	None Detected
A2529269B	Mf12 V	Heterogeneous Yellow Fibrous Bound	2%	Cellulose	30%	Calc Carb	
					8%	Binder	
A2529269B	Mf12 V	Heterogeneous Yellow Fibrous Bound	2%	Cellulose	98%	Mastic	None Detected
125 A2529270A	Mf12 V	Heterogeneous Gray Fibrous Bound	2%	Cellulose	60%	Vinyl	None Detected
					30%	Calc Carb	
					8%	Binder	
A2529270B	Mf12 V	Heterogeneous Yellow Fibrous Bound	2%	Cellulose	98%	Mastic	None Detected
126 A2529271A	Mf12 V	Heterogeneous Gray Fibrous Bound	2%	Cellulose	60%	Vinyl	None Detected
					30%	Calc Carb	
					8%	Binder	
A2529271B	Mf12 V	Heterogeneous Yellow Fibrous Bound	2%	Cellulose	98%	Mastic	None Detected



ASBESTOS BULK ANALYSIS

By: POLARIZING LIGHT MICROSCOPY

Client: PSI
 821 Corporate Ct.
 Waukesha, WI 53189

CEI Lab Code: A17-15138
Date Received: 10-25-17
Date Analyzed: 10-26-17
Date Reported: 10-27-17

Project: 6720 25th Av, Kenosha; 0541480

ASBESTOS BULK PLM, EPA 600 METHOD

Client ID Lab ID	Lab Description	Lab Attributes	NON-ASBESTOS COMPONENTS				ASBESTOS %
			Fibrous		Non-Fibrous		
127 A2529272A	Mf12 Ot	Heterogeneous	2%	Cellulose	70%	Vinyl	None Detected
		Tan,Gray Fibrous Bound			20%	Calc Carb 8% Binder	
A2529272B	Mf12 Ot	Heterogeneous Clear Fibrous Bound	2%	Cellulose	98%	Mastic	None Detected
128 A2529273A	Mf12 Ot	Heterogeneous	2%	Cellulose	70%	Vinyl	None Detected
		Tan,Gray Fibrous Bound			20%	Calc Carb 8% Binder	
A2529273B	Mf12 Ot	Heterogeneous Clear Fibrous Bound	2%	Cellulose	98%	Mastic	None Detected
129 A2529274A	Mf12 Ot	Heterogeneous	2%	Cellulose	70%	Vinyl	None Detected
		Tan,Gray Fibrous Bound			20%	Calc Carb 8% Binder	
A2529274B	Mf12 Ot	Heterogeneous Clear Fibrous Bound	2%	Cellulose	98%	Mastic	None Detected
130 A2529275A	Mf12 Ect	Heterogeneous	2%	Cellulose	60%	Vinyl	None Detected
		White,Gray Fibrous Bound			30%	Calc Carb 8% Binder	



ASBESTOS BULK ANALYSIS

By: POLARIZING LIGHT MICROSCOPY

Client: PSI
 821 Corporate Ct.
 Waukesha, WI 53189

CEI Lab Code: A17-15138
Date Received: 10-25-17
Date Analyzed: 10-26-17
Date Reported: 10-27-17

Project: 6720 25th Av, Kenosha; 0541480

ASBESTOS BULK PLM, EPA 600 METHOD

Client ID Lab ID	Lab Description	Lab Attributes	NON-ASBESTOS COMPONENTS			ASBESTOS %	
			Fibrous	Non-Fibrous			
A2529275B	Mf12 Ect	Heterogeneous Clear Fibrous Bound	2%	Cellulose	98%	Mastic	None Detected
131 A2529276A	Mf12 Ect	Heterogeneous White,Gray Fibrous Bound	2%	Cellulose	60%	Vinyl 30% Calc Carb 8% Binder	None Detected
A2529276B	Mf12 Ect	Heterogeneous Clear Fibrous Bound	2%	Cellulose	98%	Mastic	None Detected
132 A2529277A	Mf12 Ect	Heterogeneous White,Gray Fibrous Bound	2%	Cellulose	60%	Vinyl 30% Calc Carb 8% Binder	None Detected
A2529277B	Mf12 Ect	Heterogeneous Clear Fibrous Bound	2%	Cellulose	98%	Mastic	None Detected
133 A2529278	Mctm	Heterogeneous White Fibrous Bound	2%	Cellulose	90%	Mastic 8% Paint	None Detected
134 A2529279	Mctm	Heterogeneous White Fibrous Bound	2%	Cellulose	90%	Mastic 8% Paint	None Detected



ASBESTOS BULK ANALYSIS

By: POLARIZING LIGHT MICROSCOPY

Client: PSI
821 Corporate Ct.
Waukesha, WI 53189

CEI Lab Code: A17-15138
Date Received: 10-25-17
Date Analyzed: 10-26-17
Date Reported: 10-27-17

Project: 6720 25th Av, Kenosha; 0541480

ASBESTOS BULK PLM, EPA 600 METHOD

Client ID Lab ID	Lab Description	Lab Attributes	NON-ASBESTOS COMPONENTS				ASBESTOS %
			Fibrous		Non-Fibrous		
135 A2529280	Mctm	Heterogeneous White, Yellow Fibrous Bound	2%	Cellulose	90%	Mastic 8% Paint	None Detected
136 A2529281	Mctg	Heterogeneous White Fibrous Bound	<1%	Cellulose	50%	Silicates 45% Binder 5% Paint	None Detected
137 A2529282	Mctg	Heterogeneous White Fibrous Bound	<1%	Cellulose	60%	Silicates 35% Binder 5% Paint	None Detected
138 A2529283	Mctg	Heterogeneous White Fibrous Bound	<1%	Cellulose	60%	Silicates 35% Binder 5% Paint	None Detected
139 A2529284	Mfl Wy	Heterogeneous White, Black Fibrous Bound	25%	Cellulose	50%	Vinyl 20% Binder 5% Mastic	None Detected
140 A2529285	Mfl Wy	Heterogeneous White, Black Fibrous Bound	25%	Cellulose	50%	Vinyl 20% Binder 5% Mastic	None Detected
141 A2529286	Mfl Wy	Heterogeneous White, Black Fibrous Bound	25%	Cellulose	50%	Vinyl 20% Binder 5% Mastic	None Detected



ASBESTOS BULK ANALYSIS

By: POLARIZING LIGHT MICROSCOPY

Client: PSI
 821 Corporate Ct.
 Waukesha, WI 53189

CEI Lab Code: A17-15138
Date Received: 10-25-17
Date Analyzed: 10-26-17
Date Reported: 10-27-17

Project: 6720 25th Av, Kenosha; 0541480

ASBESTOS BULK PLM, EPA 600 METHOD

Client ID Lab ID	Lab Description	Lab Attributes	NON-ASBESTOS COMPONENTS				ASBESTOS %
			Fibrous		Non-Fibrous		
142 A2529287	Mct1	Heterogeneous	30%	Cellulose	30%	Perlite	None Detected
		White, Gray	15%	Fiberglass	20%	Binder	
		Fibrous			5%	Paint	
		Bound					
143 A2529288	Mct1	Heterogeneous	30%	Cellulose	30%	Perlite	None Detected
		White, Gray	15%	Fiberglass	20%	Binder	
		Fibrous			5%	Paint	
		Bound					
144 A2529289	Mct1	Heterogeneous	30%	Cellulose	30%	Perlite	None Detected
		White, Gray	15%	Fiberglass	20%	Binder	
		Fibrous			5%	Paint	
		Bound					
145 A2529290A	Mf12 Ly	Heterogeneous	2%	Cellulose	70%	Vinyl	None Detected
		White, Tan			20%	Calc Carb	
		Fibrous			8%	Binder	
		Bound					
A2529290B	Mf12 Ly	Heterogeneous	2%	Cellulose	98%	Mastic	None Detected
		Clear					
		Fibrous					
		Bound					
146 A2529291A	Mf12 Ly	Heterogeneous	2%	Cellulose	70%	Vinyl	None Detected
		White, Tan			20%	Calc Carb	
		Fibrous			8%	Binder	
		Bound					
A2529291B	Mf12 Ly	Heterogeneous	2%	Cellulose	98%	Mastic	None Detected
		Clear					
		Fibrous					
		Bound					



ASBESTOS BULK ANALYSIS

By: POLARIZING LIGHT MICROSCOPY

Client: PSI
821 Corporate Ct.
Waukesha, WI 53189

CEI Lab Code: A17-15138
Date Received: 10-25-17
Date Analyzed: 10-26-17
Date Reported: 10-27-17

Project: 6720 25th Av, Kenosha; 0541480

ASBESTOS BULK PLM, EPA 600 METHOD

Client ID Lab ID	Lab Description	Lab Attributes	NON-ASBESTOS COMPONENTS				ASBESTOS %
			Fibrous		Non-Fibrous		
147 A2529292A	Mf12 Ly	Heterogeneous	2%	Cellulose	70%	Vinyl	None Detected
		White, Tan Fibrous Bound			20%	Calc Carb 8% Binder	
A2529292B	Mf12 Ly	Heterogeneous Clear Fibrous Bound	2%	Cellulose	98%	Mastic	None Detected
148 A2529293	Sp1	Heterogeneous	<1%	Cellulose	70%	Silicates	None Detected
		Gray, White Fibrous Loosely Bound	<1%	Hair	20%	Calc Carb 10% Binder	
149 A2529294	Sp1	Heterogeneous	<1%	Cellulose	70%	Silicates	None Detected
		Gray, White Fibrous Loosely Bound	<1%	Hair	20%	Calc Carb 10% Binder	
150 A2529295	Sp1	Heterogeneous	<1%	Cellulose	70%	Silicates	None Detected
		Gray, White Fibrous Loosely Bound	<1%	Hair	20%	Calc Carb 10% Binder	
151 A2529296	Sp1	Heterogeneous	<1%	Cellulose	70%	Silicates	None Detected
		Gray, White Fibrous Loosely Bound	<1%	Hair	20%	Calc Carb 10% Binder	
152 Layer 1 A2529297	Sp1	Heterogeneous	<1%	Cellulose	60%	Silicates	None Detected
		Green Fibrous Loosely Bound			35%	Calc Carb 5% Paint	



ASBESTOS BULK ANALYSIS

By: POLARIZING LIGHT MICROSCOPY

Client: PSI
 821 Corporate Ct.
 Waukesha, WI 53189

CEI Lab Code: A17-15138
Date Received: 10-25-17
Date Analyzed: 10-26-17
Date Reported: 10-27-17

Project: 6720 25th Av, Kenosha; 0541480

ASBESTOS BULK PLM, EPA 600 METHOD

Client ID Lab ID	Lab Description	Lab Attributes	NON-ASBESTOS COMPONENTS				ASBESTOS %
			Fibrous		Non-Fibrous		
Layer 2 A2529297	Sp1	Heterogeneous Gray Fibrous Loosely Bound	<1%	Cellulose	50%	Calc Carb 30% Perlite 20% Binder	None Detected
153 Layer 1 A2529298	Sp2	Heterogeneous White Fibrous Loosely Bound	<1%	Cellulose	50%	Calc Carb 45% Binder 5% Paint	None Detected
Layer 2 A2529298	Sp2	Heterogeneous Gray Fibrous Loosely Bound	<1%	Cellulose	50%	Calc Carb 30% Perlite 20% Binder	None Detected
154 Layer 1 A2529299	Sp2	Heterogeneous White Fibrous Loosely Bound	<1%	Cellulose	60%	Silicates 35% Calc Carb 5% Paint	None Detected
Layer 2 A2529299	Sp2	Heterogeneous Gray Fibrous Loosely Bound	<1%	Cellulose	50%	Calc Carb 30% Perlite 20% Binder	None Detected
155 Layer 1 A2529300	Sp2	Heterogeneous White Fibrous Loosely Bound	<1%	Cellulose	50%	Calc Carb 45% Binder 5% Paint	None Detected
Layer 2 A2529300	Sp2	Heterogeneous Gray Fibrous Loosely Bound	<1%	Cellulose	50%	Calc Carb 30% Perlite 20% Binder	None Detected



ASBESTOS BULK ANALYSIS

By: POLARIZING LIGHT MICROSCOPY

Client: PSI
 821 Corporate Ct.
 Waukesha, WI 53189

CEI Lab Code: A17-15138
Date Received: 10-25-17
Date Analyzed: 10-26-17
Date Reported: 10-27-17

Project: 6720 25th Av, Kenosha; 0541480

ASBESTOS BULK PLM, EPA 600 METHOD

Client ID Lab ID	Lab Description	Lab Attributes	NON-ASBESTOS COMPONENTS				ASBESTOS %
			Fibrous	Cellulose	Non-Fibrous		
156 Layer 1 A2529301	Sp2	Heterogeneous	<1%	Cellulose	60%	Silicates	None Detected
		White			35%	Calc Carb	
		Fibrous			5%	Paint	
		Loosely Bound					
Layer 2 A2529301	Sp2	Heterogeneous	<1%	Cellulose	50%	Calc Carb	None Detected
		Gray			30%	Perlite	
		Fibrous			20%	Binder	
		Loosely Bound					
157 Layer 1 A2529302	Sp2	Heterogeneous	<1%	Cellulose	60%	Silicates	None Detected
		White			35%	Calc Carb	
		Fibrous			5%	Paint	
		Loosely Bound					
Layer 2 A2529302	Sp2	Heterogeneous	<1%	Cellulose	50%	Calc Carb	None Detected
		Gray			30%	Perlite	
		Fibrous			20%	Binder	
		Loosely Bound					
158 Layer 1 A2529303	Sp2	Heterogeneous	<1%	Cellulose	50%	Calc Carb	None Detected
		White			45%	Binder	
		Fibrous			5%	Paint	
		Loosely Bound					
Layer 2 A2529303	Sp2	Heterogeneous	<1%	Cellulose	50%	Calc Carb	None Detected
		Gray			30%	Perlite	
		Fibrous			20%	Binder	
		Loosely Bound					
159 Layer 1 A2529304	Sp2	Heterogeneous	<1%	Cellulose	60%	Silicates	None Detected
		White			35%	Calc Carb	
		Fibrous			5%	Paint	
		Loosely Bound					



ASBESTOS BULK ANALYSIS

By: POLARIZING LIGHT MICROSCOPY

Client: PSI
 821 Corporate Ct.
 Waukesha, WI 53189

CEI Lab Code: A17-15138
Date Received: 10-25-17
Date Analyzed: 10-26-17
Date Reported: 10-27-17

Project: 6720 25th Av, Kenosha; 0541480

ASBESTOS BULK PLM, EPA 600 METHOD

Client ID Lab ID	Lab Description	Lab Attributes	NON-ASBESTOS COMPONENTS				ASBESTOS %
			Fibrous		Non-Fibrous		
Layer 2 A2529304	Sp2	Heterogeneous Gray Fibrous Loosely Bound	<1%	Cellulose	50%	Calc Carb 30% Perlite 20% Binder	None Detected
160 Layer 1 A2529305	Sp3	Heterogeneous White Fibrous Loosely Bound	2%	Cellulose	70%	Calc Carb 20% Binder 8% Paint	None Detected
Layer 2 A2529305	Sp3	Heterogeneous Gray Fibrous Loosely Bound	<1%	Cellulose	70%	Silicates 20% Calc Carb 10% Binder	None Detected
161 Layer 1 A2529306	Sp3	Heterogeneous White Fibrous Loosely Bound	2%	Cellulose	70%	Calc Carb 20% Binder 8% Paint	None Detected
Layer 2 A2529306	Sp3	Heterogeneous White Fibrous Loosely Bound	<1%	Cellulose	60%	Silicates 35% Calc Carb 5% Paint	None Detected
Layer 3 A2529306	Sp3	Heterogeneous Gray Fibrous Loosely Bound	<1%	Cellulose	50%	Silicates 30% Perlite 20% Calc Carb	None Detected
162 Layer 1 A2529307	Sp3	Heterogeneous White Fibrous Loosely Bound	2%	Cellulose	70%	Calc Carb 20% Binder 8% Paint	None Detected



ASBESTOS BULK ANALYSIS

By: POLARIZING LIGHT MICROSCOPY

Client: PSI
 821 Corporate Ct.
 Waukesha, WI 53189

CEI Lab Code: A17-15138
Date Received: 10-25-17
Date Analyzed: 10-26-17
Date Reported: 10-27-17

Project: 6720 25th Av, Kenosha; 0541480

ASBESTOS BULK PLM, EPA 600 METHOD

Client ID Lab ID	Lab Description	Lab Attributes	NON-ASBESTOS COMPONENTS				ASBESTOS %
			Fibrous		Non-Fibrous		
Layer 2 A2529307	Sp3	Heterogeneous Gray Fibrous Loosely Bound	<1%	Cellulose Hair	70% 20% 10%	Silicates Calc Carb Binder	None Detected
163 A2529308	Mflr	Heterogeneous Black Fibrous Bound	30%	Cellulose	60% 10%	Tar Binder	None Detected
164 A2529309	Mflr	Heterogeneous Black Fibrous Bound	30%	Cellulose	60% 10%	Tar Binder	None Detected
165 A2529310	Mflr	Heterogeneous Black Fibrous Bound	30%	Cellulose	60% 10%	Tar Binder	None Detected
166 A2529311	Mff	Heterogeneous Tan Fibrous Bound	100%	Cellulose			None Detected
167 A2529312	Mff	Heterogeneous Tan Fibrous Bound	100%	Cellulose			None Detected
168 A2529313	Mff	Heterogeneous Tan Fibrous Bound	100%	Cellulose			None Detected



ASBESTOS BULK ANALYSIS

By: POLARIZING LIGHT MICROSCOPY

Client: PSI
 821 Corporate Ct.
 Waukesha, WI 53189

CEI Lab Code: A17-15138
Date Received: 10-25-17
Date Analyzed: 10-26-17
Date Reported: 10-27-17

Project: 6720 25th Av, Kenosha; 0541480

ASBESTOS BULK PLM, EPA 600 METHOD

Client ID Lab ID	Lab Description	Lab Attributes	NON-ASBESTOS COMPONENTS				ASBESTOS %
			Fibrous		Non-Fibrous		
169 A2529314	Mfl Ek	Heterogeneous Tan Fibrous Bound	25%	Cellulose	50%	Vinyl Tar	None Detected
170 A2529315	Mfl Ek	Heterogeneous Tan Fibrous Bound	25%	Cellulose	50%	Vinyl Tar	None Detected
171 A2529316	Mfl Ek	Heterogeneous Tan Fibrous Bound	25%	Cellulose	50%	Vinyl Tar	None Detected
172 A2529317	Mfl Ekr	Heterogeneous Red,Tan Fibrous Bound	25%	Cellulose	50%	Vinyl Tar	None Detected
173 A2529318	Mfl Ekr	Heterogeneous Red,Tan Fibrous Bound	25%	Cellulose	50%	Vinyl Tar	None Detected
174 A2529319	Mfl Ekr	Heterogeneous Red,Tan Fibrous Bound	25%	Cellulose	50%	Vinyl Tar	None Detected
175 A2529320	Mfl E	Heterogeneous Tan Fibrous Bound	100%	Cellulose			None Detected



ASBESTOS BULK ANALYSIS

By: POLARIZING LIGHT MICROSCOPY

Client: PSI
 821 Corporate Ct.
 Waukesha, WI 53189

CEI Lab Code: A17-15138
Date Received: 10-25-17
Date Analyzed: 10-26-17
Date Reported: 10-27-17

Project: 6720 25th Av, Kenosha; 0541480

ASBESTOS BULK PLM, EPA 600 METHOD

Client ID Lab ID	Lab Description	Lab Attributes	NON-ASBESTOS COMPONENTS				ASBESTOS %
			Fibrous	Non-Fibrous			
176 A2529321	Mfl E	Heterogeneous Tan Fibrous Bound	100%	Cellulose			None Detected
177 A2529322	Mfl E	Heterogeneous Tan Fibrous Bound	100%	Cellulose			None Detected
178 A2529323	Mfl B,g,l,o	Heterogeneous Black,Green Fibrous Bound	25%	Cellulose	50%	Vinyl Tar	None Detected
179 A2529324	Mfl B,g,l,o	Heterogeneous Black,Green Fibrous Bound	25%	Cellulose	50%	Vinyl Tar	None Detected
180 A2529325	Mfl B,g,l,o	Heterogeneous Black,Green Fibrous Bound	25%	Cellulose	50%	Vinyl Tar	None Detected



LEGEND: Non-Anth = Non-Asbestiform Anthophyllite
Non-Trem = Non-Asbestiform Tremolite
Calc Carb = Calcium Carbonate

METHOD: EPA 600 / R93 / 116 and EPA 600 / M4-82 / 020

REPORTING LIMIT: <1% by visual estimation

REPORTING LIMIT FOR POINT COUNTS: 0.25% by 400 Points or 0.1% by 1,000 Points

REGULATORY LIMIT: >1% by weight

Due to the limitations of the EPA 600 method, nonfriable organically bound materials (NOBs) such as vinyl floor tiles can be difficult to analyze via polarized light microscopy (PLM). EPA recommends that all NOBs analyzed by PLM, and found not to contain asbestos, be further analyzed by Transmission Electron Microscopy (TEM). Please note that PLM analysis of dust and soil samples for asbestos is not covered under NVLAP accreditation. Estimated measurement of uncertainty is available on request.

This report relates only to the samples tested or analyzed and may not be reproduced, except in full, without written approval by CEI Labs, Inc. CEI Labs makes no warranty representation regarding the accuracy of client submitted information in preparing and presenting analytical results. Interpretation of the analytical results is the sole responsibility of the client. Samples were received in acceptable condition unless otherwise noted. This report may not be used by the client to claim product endorsement by NVLAP or any other agency of the U.S. Government.

ANALYST:

Scott Minyard

APPROVED BY:

Tianbao Bai, Ph.D., CIH
Laboratory Director

Sarah Talley





107 New Edition Court, Cary, NC 27511
 Tel: 866-481-1412; Fax: 919-481-1442

(180) Am. 15.138
ASBESTOS A2529146
CHAIN OF CUSTODY A2529325

LAB USE ONLY:
CEI Lab Code:
CEI Lab I.D. Range:

COMPANY INFORMATION	PROJECT INFORMATION
CEI CLIENT #:	Job Contact: <i>Jim Updike</i>
Company: <i>PSI, Inc</i>	Email / Tel: <i>Same</i>
Address: <i>821 Corporate Ct</i>	Project Name: <i>6720 25th Av, Kenosha</i>
<i>Waukesha, WI 53189</i>	Project ID# <i>0541480</i>
Email: <i>jim.updike@psiusa.com</i>	PO #:
Tel: <i>262-521-2125</i> Fax:	STATE SAMPLES COLLECTED IN: <i>WI</i>

IF TAT IS NOT MARKED STANDARD 3 DAY TAT APPLIES.

ASBESTOS	METHOD	TURN AROUND TIME					
		4 HR	8 HR	24 HR	2 DAY	3 DAY	5 DAY
PLM BULK	EPA 600	<input type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>	<input checked="" type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>
PLM POINT COUNT (400)	EPA 600	<input type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>
PLM POINT COUNT (1000)	EPA 600	<input type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>
PLM GRAV w POINT COUNT	EPA 600		<input type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>
PLM BULK	CARB 435		<input type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>
PCM AIR	NIOSH 7400	<input type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>
TEM AIR	EPA AHERA	<input type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>
TEM AIR	NIOSH 7402	<input type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>
TEM AIR	ISO 10312	<input type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>
TEM AIR	ASTM 6281-09	<input type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>
TEM BULK	CHATFIELD		<input type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>
TEM DUST WIPE	ASTM D6480-05	<input type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>
TEM DUST MICROVAC	ASTM D5755-09	<input type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>
TEM SOIL	ASTM D7521-13			<input type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>
TEM VERMICULITE	CINCINNATI METHOD			<input type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>
OTHER:		<input type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>

REMARKS / SPECIAL INSTRUCTIONS: <i>Samples 01-180</i>		<input checked="" type="checkbox"/> Accept Samples
		<input type="checkbox"/> Reject Samples
Relinquished By:	Date/Time	Received By:
<i>[Signature]</i>	<i>10/24/17 17:00</i>	<i>A</i>
		<i>10 25 17 9:10</i>

Samples will be disposed of 30 days after analysis

BULK SAMPLE LOG

Client: City of Kenosha	Construction Date: Unknown
Project: Multi-Family Residential Building	Date of Inspection: 10/19/2017
Address: 6720 25th Ave. Kenosha, WI	Inspector: Mike Larsen
	Inspector #: All-13850

SAMPLE NUMBER	SAMPLE LOCATION	MATERIAL DESCRIPTION
01	Roof	Roofing Tar paper
02	Roof	Roofing Tar paper
03	Roof	Roofing Tar paper
04	Roof	Roof Shingles: Red and Black
05	Roof	Roof Shingles: Red and Black
06	Roof	Roof Shingles: Red and Black
07	Roof	Asphalt Sheeting (Bottom Layer)
08	Roof	Asphalt Sheeting (Bottom Layer)
09	Roof	Asphalt Sheeting (Bottom Layer)
10	Roof	Asphalt Sheeting (Middle Layer)
11	Roof	Asphalt Sheeting (Middle Layer)
12	Roof	Asphalt Sheeting (Middle Layer)
13	Roof	Asphalt Sheeting (Top Layer)
14	Roof	Asphalt Sheeting (Top Layer)
15	Roof	Asphalt Sheeting (Top Layer)
16	Roof 2	Roof Shingles - Gray
17	Roof 2	Roof Shingles - Gray
18	Roof 2	Roof Shingles - Gray
19	210	Asphalt Sheeting - Gray
20	210	Asphalt Sheeting - Gray
21	210	Asphalt Sheeting - Gray
22	Exterior	Window Pane Glazing - Hard, Beige
23	Exterior	Window Pane Glazing - Hard, Beige
24	Exterior	Window Pane Glazing - Hard, Beige
25	Exterior	Window Pane Glazing - Soft, White
26	Exterior	Window Pane Glazing - Soft, White
27	Exterior	Window Pane Glazing - Soft, White
28	Exterior	Window Caulk - White
29	Exterior	Window Caulk - White
30	Exterior	Window Caulk - White
31	Exterior	Transite Siding
32	Exterior	Transite Siding
33	Exterior	Transite Siding

BULK SAMPLE LOG

Client:	City of Kenosha	Construction Date:	Unknown
Project:	Multi-Family Residential Building	Date of Inspection:	10/19/2017
Address:	6720 25th Ave. Kenosha, WI	Inspector:	Mike Larsen
		Inspector #:	All-13850

SAMPLE NUMBER	SAMPLE LOCATION	MATERIAL DESCRIPTION
34	Exterior	Siding Tar Paper
35	Exterior	Siding Tar Paper
36	Exterior	Siding Tar Paper
37	Exterior	Pipe Caulk - Beige
38	Exterior	Pipe Caulk - Beige
39	Exterior	Pipe Caulk - Beige
40	103	2' x 4' Suspended Ceiling Tile: Pinholes and Fissures
41	103	2' x 4' Suspended Ceiling Tile: Pinholes and Fissures
42	103	2' x 4' Suspended Ceiling Tile: Pinholes and Fissures
43	01	Brick
44	04	Brick
45	05	Brick
46	01	Brick Mortar
47	04	Brick Mortar
48	05	Brick Mortar
49	02	Pipe Caulk - Red
50	02	Pipe Caulk - Red
51	02	Pipe Caulk - Red
52	STWL1	9" x 9" Tan Floor Tile and Associated Mastic
53	102	9" x 9" Tan Floor Tile and Associated Mastic
54	104	9" x 9" Tan Floor Tile and Associated Mastic
55	STWL1	12" x 12" Tan Floor Tile and Associated Mastic
56	STWL1	12" x 12" Tan Floor Tile and Associated Mastic
57	STWL1	12" x 12" Tan Floor Tile and Associated Mastic
58	100	12" x 12" Brown Floor Tile and Associated Mastic
59	100	12" x 12" Brown Floor Tile and Associated Mastic
60	100	12" x 12" Brown Floor Tile and Associated Mastic
61	100	Window Caulk - White
62	109	Window Caulk - White
63	104	Window Caulk - White
64	100	Door Caulk - White
65	104	Door Caulk - White
66	109	Door Caulk - White

BULK SAMPLE LOG

Client: City of Kenosha	Construction Date: Unknown
Project: Multi-Family Residential Building	Date of Inspection: 10/19/2017
Address: 6720 25th Ave. Kenosha, WI	Inspector: Mike Larsen
	Inspector #: All-13850

SAMPLE NUMBER	SAMPLE LOCATION	MATERIAL DESCRIPTION
67	100	12" x 12" Beige Floor Tile and Associated Mastic
68	101	12" x 12" Beige Floor Tile and Associated Mastic
69	101	12" x 12" Beige Floor Tile and Associated Mastic
70	103	White Linoleum
71	103	White Linoleum
72	103	White Linoleum
73	103	Panel Mastic - Tan
74	103	Panel Mastic - Tan
75	202	Panel Mastic - Tan
76	108	Tub Surround Mastic - Beige
77	103	Tub Surround Mastic - Beige
78	203	Tub Surround Mastic - Beige
79	103	Backer Board
80	103	Backer Board
81	103	Backer Board
82	104	12" x 12" Cream/Green Floor Tile and Associated Mastic
83	104	12" x 12" Cream/Green Floor Tile and Associated Mastic
84	104	12" x 12" Cream/Green Floor Tile and Associated Mastic
85	104	12" x 12" Green Floor Tile and Associated Mastic
86	104	12" x 12" Green Floor Tile and Associated Mastic
87	104	12" x 12" Green Floor Tile and Associated Mastic
88	104	Sink Undercoating - Black
89	109	Sink Undercoating - Black
90	209	Sink Undercoating - Black
91	105	Window Rope
92	203	Window Rope
93	204	Window Rope
94	108	Yellow/Black Linoleum
95	108	Yellow/Black Linoleum
96	108	Yellow/Black Linoleum
97	108	12" x 12" Pink Floor Tile and Associated Mastic
98	109	12" x 12" Pink Floor Tile and Associated Mastic
99	109	12" x 12" Pink Floor Tile and Associated Mastic

BULK SAMPLE LOG


Client:	City of Kenosha	Construction Date:	Unknown
Project:	Multi-Family Residential Building	Date of Inspection:	10/19/2017
Address:	6720 25th Ave. Kenosha, WI	Inspector:	Mike Larsen
		Inspector #:	All-13850

SAMPLE NUMBER	SAMPLE LOCATION	MATERIAL DESCRIPTION
100	109	12" x 12" Beige/Brown Floor Tile and Associated Mastic
101	STWL2	12" x 12" Beige/Brown Floor Tile and Associated Mastic
102	109	12" x 12" Beige/Brown Floor Tile and Associated Mastic
103	109	12" x 12" Cream/Tan Floor Tile and Associated Mastic
104	109	12" x 12" Cream/Tan Floor Tile and Associated Mastic
105	STWL2	12" x 12" Cream/Tan Floor Tile and Associated Mastic
106	109	12" x 12" White/Black Floor Tile and Associated Mastic
107	109	12" x 12" White/Black Floor Tile and Associated Mastic
108	STWL2	12" x 12" White/Black Floor Tile and Associated Mastic
109	109	Drywall (No Joint Compound)
110	109	Drywall (No Joint Compound)
111	109	Drywall (No Joint Compound)
112	2098	9" x 9" Brown Floor Tile and Associated Mastic
113	209	9" x 9" Brown Floor Tile and Associated Mastic
114	STWL4	9" x 9" Brown Floor Tile and Associated Mastic
115	STWL3	Cream Linoleum
116	STWL3	Cream Linoleum
117	STWL3	Cream Linoleum
118	STWL3	12" x 12" Black Floor Tile and Associated Mastic
119	STWL3	12" x 12" Black Floor Tile and Associated Mastic
120	STWL3	12" x 12" Black Floor Tile and Associated Mastic
121	STWL3	Brown Stair Tread and Associated Mastic
122	STWL3	Brown Stair Tread and Associated Mastic
123	STWL3	Brown Stair Tread and Associated Mastic
124	204	12" x 12" Olive Floor Tile and Associated Mastic
125	204	12" x 12" Olive Floor Tile and Associated Mastic
126	204	12" x 12" Olive Floor Tile and Associated Mastic
127	202	12" x 12" Orange/Tan Floor Tile and Associated Mastic
128	202	12" x 12" Orange/Tan Floor Tile and Associated Mastic
129	202	12" x 12" Orange/Tan Floor Tile and Associated Mastic
130	204	12" x 12" Beige/Cream/Tan Floor Tile and Associated Mastic
131	204	12" x 12" Beige/Cream/Tan Floor Tile and Associated Mastic
132	204	12" x 12" Beige/Cream/Tan Floor Tile and Associated Mastic

BULK SAMPLE LOG

Client:	City of Kenosha	Construction Date:	Unknown
Project:	Multi-Family Residential Building	Date of Inspection:	10/19/2017
Address:	6720 25th Ave. Kenosha, WI	Inspector:	Mike Larsen
		Inspector #:	All-13850

SAMPLE NUMBER	SAMPLE LOCATION	MATERIAL DESCRIPTION
133	204	Ceramic Tile Mastic
134	204	Ceramic Tile Mastic
135	209	Ceramic Tile Mastic
136	204	Ceramic Tile Grout
137	204	Ceramic Tile Grout
138	209	Ceramic Tile Grout
139	208	White/Gray Linoleum
140	208	White/Gray Linoleum
141	208	White/Gray Linoleum
142	208	1' x 1' Ceiling Tile: Textured
143	208	1' x 1' Ceiling Tile: Textured
144	208	1' x 1' Ceiling Tile: Textured
145	209	12" x 12" Yellow/Gray Floor Tile and Associated Mastic
146	209	12" x 12" Yellow/Gray Floor Tile and Associated Mastic
147	209	12" x 12" Yellow/Gray Floor Tile and Associated Mastic
148	01	Plaster - Single Coat
149	02	Plaster - Single Coat
150	STWL1	Plaster - Single Coat
151	STWL2	Plaster - Single Coat
152	STWL4	Plaster - Single Coat
153	104	Plaster - Base and Skim Coat
154	100	Plaster - Base and Skim Coat
155	105	Plaster - Base and Skim Coat
156	109	Plaster - Base and Skim Coat
157	201	Plaster - Base and Skim Coat
158	204	Plaster - Base and Skim Coat
159	206	Plaster - Base and Skim Coat
160	202	Plaster - Base and Textured Skim Coat
161	204	Plaster - Base and Textured Skim Coat
162	101	Plaster - Base and Textured Skim Coat
163	204	Red Linoleum
164	204	Red Linoleum
165	204	Red Linoleum



NORTH

PSI Project Number:
00541480

Date:
10/19/2017


Scale:
Not to Scale

City of Kenosha
6720 25th Avenue
Kenosha, WI

**Floor Plan
Basement**

Environmental Services
821 Corporate Court
Waukesha, Wisconsin 53189
(262) 521-2125 Fax (262) 521-2471





PSI Project Number:
00541480

Scale:
Not to Scale


Date:
10/19/2017

City of Kenosha
6720 25th Avenue
Kenosha, WI

Floor Plan
First Floor

Environmental Services
821 Corporate Court
Waukesha, Wisconsin 53189
(262) 521-2125 Fax (262) 521-2471





NORTH

PSI Project Number:
00541480

Date:
10/19/2017

Scale:
Not to Scale

City of Kenosha
6720 25th Avenue
Kenosha, WI

Floor Plan
Second Floor

Environmental Services
821 Corporate Court
Waukesha, Wisconsin 53189
(262) 521-2125 Fax (262) 521-2471



Milwaukee Lead/Asbestos Information Center

A division of Midwest Certified Training, Inc.

3495 North 124th Street, Brookfield, WI 53005 Phone: 414-481-9070



Michael Louis Franklin Larsen

Has successfully completed a course and passed the examination on April 28, 2016 with a minimum score of 70 percent, that meets all criteria for the State of Wisconsin Recertification as an

Asbestos Inspector Refresher Course

Date of Course: April 28, 2016

Date Issued April 28, 2016

Date of Expiration: April 28, 2017

Certification Number: AIR16042854708

Location: Milwaukee Lead/Asbestos Information Center, 3495 North 124th Street, Brookfield, WI 53005

DCQ Course ID #: 9606

A handwritten signature in blue ink that reads "Rocky Everly".

Rocky Everly, Director of Milwaukee Lead/Asbestos Information Center, Inc.
3495 North 124th Street
Brookfield, WI 53005
414-481-9070

Company Certificate

This certifies that

PSI - PROFESSIONAL SERVICE INDUSTRIES INC

821 CORPORATE CT
WAUKESHA WI 53189-5009

is certified under ch. DHS 159, Wis. Adm. Code as a

Asbestos Company - Primary

Certificate Issue Date: 07/16/2015
Expiration Date: 08/01/2017, 12:01 a.m.
Certification #: CAP-16820

Wisconsin Department of Health Services
Division of Public Health
Bureau of Environmental and Occupational Health
Asbestos & Lead Section
PO Box 2659
Madison WI 53701-2659
Phone: (608) 261-6876



Shelley A Bruce

Shelley A Bruce,
Unit Supervisor.





SCOPE OF ACCREDITATION TO ISO/IEC 17025:2005

CEI Labs, Inc.
730 SE Maynard Road
Cary, NC 27511
Dr. Tianbao Bai
Phone: 919-481-1413 Fax: 919-481-1442
Email: bai@ceilabs.com
<http://www.ceilabs.com>

ASBESTOS FIBER ANALYSIS

NVLAP LAB CODE 101768-0

Bulk Asbestos Analysis

<u>Code</u>	<u>Description</u>
18/A01	EPA 600/M4-82-020: Interim Method for the Determination of Asbestos in Bulk Insulation Samples
18/A03	EPA 600/R-93/116: Method for the Determination of Asbestos in Bulk Building Materials

Airborne Asbestos Analysis

<u>Code</u>	<u>Description</u>
18/A02	U.S. EPA's "Interim Transmission Electron Microscopy Analytical Methods-Mandatory and Nonmandatory-and Mandatory Section to Determine Completion of Response Actions" as found in 40 CFR, Part 763, Subpart E, Appendix A.

A handwritten signature in black ink, appearing to read "Dana S. Laman".

For the National Voluntary Laboratory Accreditation Program

United States Department of Commerce
National Institute of Standards and Technology



Certificate of Accreditation to ISO/IEC 17025:2005

NVLAP LAB CODE: 101768-0

CEI Labs, Inc.
Cary, NC

is accredited by the National Voluntary Laboratory Accreditation Program for specific services,
listed on the Scope of Accreditation, for:

Asbestos Fiber Analysis

This laboratory is accredited in accordance with the recognized International Standard ISO/IEC 17025:2005.
This accreditation demonstrates technical competence for a defined scope and the operation of a laboratory quality management system (refer to joint ISO-ILAC-IAF Communique dated January 2009).

2016-04-01 through 2017-03-31


Effective Dates



David F. Alderman

For the National Voluntary Laboratory Accreditation Program

General Location Map



 Subject Property - 1727 52nd Street



June 23, 2017

Mr. Mark Willing
Purchasing Manager
City of Kenosha- Department of Finance
Municipal Building- Room 208
625 52nd Street
Kenosha, Wisconsin 53140

Re: NESHAP Asbestos Survey at
Residence
1727 52nd Street
Kenosha, Wisconsin
PSI Project No. 00541425

Dear Mr. Willing:

In accordance with our agreement dated May 15, 2012, Professional Service Industries, Inc. (PSI), has performed an Asbestos Survey of the above-referenced property to identify all Asbestos-Containing Materials (ACM) including Category I and Category II non-friable ACM. Below, please find a discussion of our survey and results.

Facility Description

The facility included in this National Emissions Standard for Hazardous Air Pollutants (NESHAPs) Asbestos Survey was a two-story residential structure with basement and attic. At the time of PSI's survey, the building was vacant.

Survey Intent

This asbestos survey was intended to meet the requirements of the NESHAP for Asbestos demolition or renovation. The survey included a thorough inspection of all areas of demolition or renovation. PSI's inspection team identified, quantified and assessed the condition of all Regulated Asbestos Containing Material (RACM), Category I non-friable ACM and Category II non-friable ACM. A hand pressure test was used to determine whether the material was friable.

Representative samples were collected and submitted to an accredited laboratory for analysis by Polarized Light Microscopy. Reports of Analysis are attached along with Chain of Custody documentation, Bulk Sample Logs, Site Layout Diagrams, and Inspector and Laboratory Certifications.

Findings

Asbestos-containing materials were discovered during this asbestos survey. Assumed asbestos-containing materials were identified and included electrical boxes. The table below details the findings of this survey.

Table 1-Asbestos Containing Materials

Material Description	Locations in Facility	Total Quantity	RACM, Cat. I or Cat. II	Friable (Y/N)	Condition
<i>Pipe Packing – Black</i>	<i>Room 01</i>	<i>1 SF</i>	<i>RACM</i>	<i>Y</i>	<i>Poor</i>
<i>Window Caulk – White</i>	<i>Room 100</i>	<i>2 SF</i>	<i>Cat. I</i>	<i>N</i>	<i>Good</i>
<i>Window Pane Glazing - Beige</i>	<i>Rooms 101 and 102</i>	<i>4 SF</i>	<i>Cat. I</i>	<i>N</i>	<i>Good</i>
<i>Roof Flashing Associated with Shingled Roof</i>	<i>Roof 1</i>	<i>12 SF</i>	<i>Cat. I</i>	<i>N</i>	<i>Good</i>
<i>Roof Flashing Associated with Membrane Roof</i>	<i>Roof 2</i>	<i>800 SF</i>	<i>Cat. I</i>	<i>N</i>	<i>Good</i>
<i>Electrical Boxes (Assumed Transite Components)</i>	<i>Room 105</i>	<i>1 Box</i>	<i>RACM</i>	<i>N</i>	<i>Good</i>

SF=Square Feet
EA=Each

In addition, please note that vermiculite insulation was identified during asbestos inspection activities. Vermiculite insulation was noted in the attic (Room 300), totaling approximately 1,000 square feet. The vermiculite was sampled and analyzed by Polarized Light Microscopy (PLM). No asbestos was detected in any of the samples. Per Wisconsin Department of Health Services regulations (DHS 159.04):

“Vermiculite insulation” means vermiculite that has been expanded through a heating process and is used as loose-fill building insulation. It is a “suspect asbestos-containing material” under sub. (50). Vermiculite insulation is assumed to be asbestos-containing material unless proven otherwise in accordance with Environmental Protection Agency (EPA) recommended sampling and analysis protocols specific to vermiculite insulation.

As of the publication of this chapter, the EPA has not published official guidance for sampling and testing protocols to test for the presence or absence of asbestos in vermiculite insulation. When recommended protocols are published, vermiculite insulation may be sampled and analyzed using the EPA recommended protocols to determine any asbestos content. Until such time, vermiculite insulation must be assumed to contain asbestos and be treated as an asbestos-containing material under this chapter.

Although the DHS considers this material to be an ACM, the Wisconsin Department of Natural Resources (WDNR) allows for existing analysis procedures (PLM) to be used to determine the asbestos content of vermiculite insulation. As such, this material may remain in place for demolition. As per below, the DHS does not require an Asbestos Certified Worker to perform the demolition as long as the demolition is not performed by hand.

DHS 159.06 Exceptions to certification. (3) An individual operates a motorized vehicle to demolish or remove a facility when asbestos-containing material is allowed to remain under s. NR 447.08 (1) (a) to (d)."

As per Wisconsin DHS regulations (discussed earlier in this report), vermiculite can remain in place during demolition as long as the demolition is not conducted by hand as noted above.

Warranty

The information contained in this report is based upon the data furnished by the Client and observations and test results provided by PSI. These observations and results are time dependent, are subject to changing site conditions, and revisions to Federal, State and local regulations.

PSI warrants that these findings have been promulgated after being prepared in general accordance with generally accepted practices in the asbestos industry. PSI also recognizes that raw laboratory test data are not usually sufficient to make all abatement and management decisions.

As directed by the client, PSI did not provide any service to investigate or detect the presence of moisture, mold or other biological contaminants in or around any structure, or any service that was designed or intended to prevent or lower the risk of the occurrence of the amplification of the same. Client acknowledges that mold is ubiquitous to the environment with mold amplification occurring when building materials are impacted by moisture. Client further acknowledges that site conditions are outside of PSI's control, and that mold amplification will likely occur, or continue to occur, in the presence of moisture. As such, PSI cannot and shall not be held responsible for the occurrence or recurrence of mold amplification.

This report was prepared pursuant to the contract PSI has with the City of Kenosha. That contractual relationship included an exchange of information about the subject site that was unique and between PSI and its client and serves as the basis upon which this report was prepared. Because of the importance of the communication between PSI and its client, reliance or any use of this report by anyone other than the City of Kenosha, for whom it was prepared, is prohibited and therefore not foreseeable to PSI.

Reliance or use by any such third party without explicit authorization in the report does not make said third party a third-party beneficiary to PSI's contract with the City of Kenosha. Any such unauthorized reliance on or use of this report, including any of its information or conclusions, will be at third party's risk. For the same reasons, no warranties or representations, expressed or implied in this report, are made to any such third party.

No other warranties are implied or expressed.

Unidentifiable Conditions

This report is necessarily limited to the conditions observed and to the information available at the time of the work. Due to the nature of the work, there is a possibility that there may exist conditions which could not be identified within the scope of work or which were not apparent at the time of our site work. This report is also limited to information available from the client at the

time it was conducted. The report may not represent all conditions at the subject site as it only reflects the information gathered from specific locations.

Thank you for choosing PSI as your consultant for this project. If you have any questions, or if we can be of additional service, please call us at 262.521.2125.

Respectfully submitted,
PROFESSIONAL SERVICE INDUSTRIES, INC.



Mike Larsen
WI Asbestos Inspector #All-13850



Michael Tjaden
Principal Consultant

Appendices

- A. Report of Bulk Sample Analysis for Asbestos/Chain of Custody
- B. Asbestos Bulk Sample Log
- C. Site Layout Drawings
- D. Inspector & Company Certifications



June 19, 2017

PSI
821 Corporate Ct.
Waukesha, WI 53189

CLIENT PROJECT: 1727 52nd St Kenosha, WI; 00541425
CEI LAB CODE: A17-8548

Dear Customer:

Enclosed are asbestos analysis results for PLM Bulk samples received at our laboratory on June 16, 2017. The samples were analyzed for asbestos using polarizing light microscopy (PLM) per the EPA 600 Method.

Sample results containing >1% asbestos are considered asbestos-containing materials (ACMs) per EPA regulatory requirements. The detection limit for the EPA 600 Method is <1% asbestos by weight as determined by visual estimation.

Thank you for your business and we look forward to continuing good relations. If you have any questions, please feel free to call our office at 919-481-1413.

Kind Regards,

A handwritten signature in black ink, appearing to read "Tianbao Bai".

Tianbao Bai, Ph.D., CIH
Laboratory Director





ASBESTOS ANALYTICAL REPORT

By: Polarized Light Microscopy

Prepared for

PSI

CLIENT PROJECT: 1727 52nd St Kenosha, WI; 00541425

CEI LAB CODE: A17-8548

TEST METHOD: EPA 600 / R93 / 116 and EPA 600 / M4-82 / 020

REPORT DATE: 06/19/17

TOTAL SAMPLES ANALYZED: 112

SAMPLES >1% ASBESTOS: 14

TEL: 866-481-1412

www.ceilabs.com



Asbestos Report Summary

By: POLARIZING LIGHT MICROSCOPY

PROJECT: 1727 52nd St Kenosha, WI; 00541425

CEI LAB CODE: A17-8548

METHOD: EPA 600 / R93 / 116 and EPA 600 / M4-82 / 020

Client ID	Layer	Lab ID	Color	Sample Description	ASBESTOS %
01		A2426900	Tan	MB	None Detected
02		A2426901	Tan	MB	None Detected
03		A2426902	Tan	MB	None Detected
04		A2426903	Tan	Mbm	None Detected
05		A2426904	Tan	Mbm	None Detected
06		A2426905	Tan	Mbm	None Detected
07		A2426906	Black	Mpp	Chrysotile 5%
08		A2426907	Black	Mpp	Chrysotile 5%
09		A2426908	Black	Mpp	Chrysotile 5%
10		A2426909	Tan	Mbi	None Detected
11		A2426910	Tan	Mbi	None Detected
12		A2426911	Tan	Mbi	None Detected
13		A2426912	Gray	Mfp	None Detected
14		A2426913	Gray	Mfp	None Detected
15		A2426914	Gray	Mfp	None Detected
16		A2426915	White	Mjc	None Detected
17		A2426916	White	Mjc	None Detected
18		A2426917	White	Mjc	None Detected
19		A2426918	Gray	Mtt	None Detected
20		A2426919	Gray	Mtt	None Detected
21		A2426920	Gray	Mtt	None Detected
22		A2426921	Tan,Black	Mbat	None Detected
23		A2426922	Tan,Black	Mbat	None Detected
24		A2426923	Tan,Black	Mbat	None Detected
25		A2426924	White	Mwc	Chrysotile 5%
26		A2426925	White	Mwc	Chrysotile 5%
27		A2426926	Brown	Mwc	None Detected
28		A2426927	Brown	Mcm	None Detected
29		A2426928	Brown	Mcm	None Detected
30		A2426929	Brown	Mcm	None Detected
31		A2426930	Tan	Mpg	Chrysotile 2%



Asbestos Report Summary

By: POLARIZING LIGHT MICROSCOPY

PROJECT: 1727 52nd St Kenosha, WI; 00541425

CEI LAB CODE: A17-8548

METHOD: EPA 600 / R93 / 116 and EPA 600 / M4-82 / 020

Client ID	Layer	Lab ID	Color	Sample Description	ASBESTOS %
32		A2426931	Tan	Mpg	Chrysotile 2%
33		A2426932	Tan	Mpg	Chrysotile 2%
34		A2426933	White	Mdwc	None Detected
35		A2426934	White	Mdwc	None Detected
36		A2426935	White	Mdwc	None Detected
37		A2426936	Yellow	Mem2	None Detected
38		A2426937	Yellow	Mem2	None Detected
39		A2426938	Yellow	Mem2	None Detected
40		A2426939	Gray	Mcb	None Detected
41		A2426940	Gray	Mcb	None Detected
42		A2426941	Gray	Mcb	None Detected
43		A2426942	Gray	Mcbm	None Detected
44		A2426943	Gray	Mcbm	None Detected
45		A2426944	Gray	Mcbm	None Detected
46		A2426945	Tan,White	Msct1	None Detected
47		A2426946	Tan,White	Msct1	None Detected
48		A2426947	Tan,White	Msct1	None Detected
49	Layer 1	A2426948	White	Sp2	None Detected
	Layer 2	A2426948	White	Sp2	None Detected
	Layer 3	A2426948	Tan	Sp2	None Detected
50	Layer 1	A2426949	White	Sp2	None Detected
	Layer 2	A2426949	White	Sp2	None Detected
	Layer 3	A2426949	Tan	Sp2	None Detected
51	Layer 1	A2426950	White	Sp2	None Detected
	Layer 2	A2426950	White	Sp2	None Detected
	Layer 3	A2426950	Tan	Sp2	None Detected
52		A2426951A	Black	Mstk	None Detected
		A2426951B	Brown	Mstk	None Detected
53		A2426952	Black	Mstk	None Detected
54		A2426953A	Black	Mstk	None Detected
		A2426953B	Brown	Mstk	None Detected



Asbestos Report Summary

By: POLARIZING LIGHT MICROSCOPY

PROJECT: 1727 52nd St Kenosha, WI; 00541425

CEI LAB CODE: A17-8548

METHOD: EPA 600 / R93 / 116 and EPA 600 / M4-82 / 020

Client ID	Layer	Lab ID	Color	Sample Description	ASBESTOS %
55		A2426954	Gray	Mctm	None Detected
56		A2426955	Gray	Mctm	None Detected
57		A2426956	Gray	Mctm	None Detected
58		A2426957	Tan	Mctg	None Detected
59		A2426958	Tan	Mctg	None Detected
60		A2426959	Tan	Mctg	None Detected
61		A2426960	Off-white	Mts	None Detected
62		A2426961	Off-white	Mts	None Detected
63		A2426962	Off-white	Mts	None Detected
64		A2426963	Off-white	Mbi2	None Detected
65		A2426964	Off-white	Mbi2	None Detected
66		A2426965	Off-white	Mbi2	None Detected
67		A2426966	Gold	Verm	None Detected
68		A2426967	Gold	Verm	None Detected
69		A2426968	Gold	Verm	None Detected
70		A2426969	Black	Mwce	None Detected
71		A2426970	Black	Mwce	None Detected
72		A2426971	Black	Mwce	None Detected
73		A2426972	Brown,Off-white	Mdce	None Detected
74		A2426973	Brown,Off-white	Mdce	None Detected
75		A2426974	Brown,Off-white	Mdce	None Detected
76		A2426975	Brown,Off-white	Mdce2	None Detected
77		A2426976	Brown,Off-white	Mdce2	None Detected
78		A2426977	Brown,Off-white	Mdce2	None Detected
79		A2426978	Black	Mrs1	None Detected
80		A2426979	Black	Mrs1	None Detected
81		A2426980	Black	Mrs1	None Detected
82		A2426981	Black	Mrs2	None Detected
83		A2426982	Black	Mrs2	None Detected
84		A2426983	Black	Mrs2	None Detected
85		A2426984	Black	Mrs3	None Detected



Asbestos Report Summary

By: POLARIZING LIGHT MICROSCOPY

PROJECT: 1727 52nd St Kenosha, WI; 00541425

CEI LAB CODE: A17-8548

METHOD: EPA 600 / R93 / 116 and EPA 600 / M4-82 / 020

Client ID	Layer	Lab ID	Color	Sample Description	ASBESTOS %
86		A2426985	Black	Mrs3	None Detected
87		A2426986	Black	Mrs3	None Detected
88		A2426987	Black	Mrs4	None Detected
89		A2426988	Black	Mrs4	None Detected
90		A2426989	Black	Mrs4	None Detected
91		A2426990	Black	Mrs5	None Detected
92		A2426991	Black	Mrs5	None Detected
93		A2426992	Black	Mrs5	None Detected
94		A2426993	Black	Mrf	Chrysotile 5%
95		A2426994	Black	Mrf	Chrysotile 5%
96		A2426995	Black	Mrf	Chrysotile 5%
97		A2426996	Tan	Mrm	None Detected
98		A2426997	Tan	Mrm	None Detected
99		A2426998	Tan	Mrm	None Detected
100		A2426999	Black,Tan	Mrf2	Chrysotile 5%
101		A2427000	Black,Tan	Mrf2	Chrysotile 5%
102		A2427001	Black,Tan	Mrf2	Chrysotile 5%
103	Layer 1	A2427002	Off-white	Sp1	None Detected
	Layer 2	A2427002	Gray	Sp1	None Detected
104	Layer 1	A2427003	Off-white	Sp1	None Detected
	Layer 2	A2427003	Gray	Sp1	None Detected
105	Layer 1	A2427004	Off-white	Sp1	None Detected
	Layer 2	A2427004	Gray	Sp1	None Detected
106	Layer 1	A2427005	Off-white	Sp1	None Detected
	Layer 2	A2427005	Gray	Sp1	None Detected
107	Layer 1	A2427006	Off-white	Sp1	None Detected
	Layer 2	A2427006	Gray	Sp1	None Detected
108	Layer 1	A2427007	Pink,Tan	Sp1	None Detected
	Layer 2	A2427007	Off-white	Sp1	None Detected
	Layer 3	A2427007	Gray	Sp1	None Detected
109	Layer 1	A2427008	Pink,Tan	Sp1	None Detected



Asbestos Report Summary

By: POLARIZING LIGHT MICROSCOPY

PROJECT: 1727 52nd St Kenosha, WI; 00541425

CEI LAB CODE: A17-8548

METHOD: EPA 600 / R93 / 116 and EPA 600 / M4-82 / 020

Client ID	Layer	Lab ID	Color	Sample Description	ASBESTOS %
	Layer 2	A2427008	Off-white	Sp1	None Detected
	Layer 3	A2427008	Gray	Sp1	None Detected
110		A2427009	Black	Mwb	None Detected
111		A2427010	Black	Mwb	None Detected
112		A2427011	Black	Mwb	None Detected



ASBESTOS BULK ANALYSIS

By: POLARIZING LIGHT MICROSCOPY

Client: PSI
 821 Corporate Ct.
 Waukesha, WI 53189

CEI Lab Code: A17-8548
Date Received: 06-16-17
Date Analyzed: 06-19-17
Date Reported: 06-19-17

Project: 1727 52nd St Kenosha, WI; 00541425

ASBESTOS BULK PLM, EPA 600 METHOD

Client ID Lab ID	Lab Description	Lab Attributes	NON-ASBESTOS COMPONENTS		ASBESTOS %
			Fibrous	Non-Fibrous	
01 A2426900	MB	Heterogeneous	15%	Binder	None Detected
		Tan	85%	Silicates	
		Non-fibrous			
		Bound			
02 A2426901	MB	Heterogeneous	15%	Binder	None Detected
		Tan	80%	Silicates	
		Non-fibrous	5%	Paint	
		Bound			
03 A2426902	MB	Heterogeneous	15%	Binder	None Detected
		Tan	80%	Silicates	
		Non-fibrous	5%	Paint	
		Bound			
04 A2426903	Mbm	Heterogeneous	15%	Binder	None Detected
		Tan	85%	Silicates	
		Non-fibrous			
		Bound			
05 A2426904	Mbm	Heterogeneous	15%	Binder	None Detected
		Tan	85%	Silicates	
		Non-fibrous			
		Bound			
06 A2426905	Mbm	Heterogeneous	15%	Binder	None Detected
		Tan	80%	Silicates	
		Non-fibrous	5%	Paint	
		Bound			
07 A2426906	Mpp	Heterogeneous	15%	Silicates	5% Chrysotile
		Black	80%	Tar	
		Fibrous	<1%	Paint	
		Bound			



ASBESTOS BULK ANALYSIS

By: POLARIZING LIGHT MICROSCOPY

Client: PSI
 821 Corporate Ct.
 Waukesha, WI 53189

CEI Lab Code: A17-8548
Date Received: 06-16-17
Date Analyzed: 06-19-17
Date Reported: 06-19-17

Project: 1727 52nd St Kenosha, WI; 00541425

ASBESTOS BULK PLM, EPA 600 METHOD

Client ID Lab ID	Lab Description	Lab Attributes	NON-ASBESTOS COMPONENTS		ASBESTOS %		
			Fibrous	Non-Fibrous			
08 A2426907	Mpp	Heterogeneous	15%	Silicates	5% Chrysotile		
		Black	80%	Tar			
		Fibrous	<1%	Paint			
		Bound					
09 A2426908	Mpp	Heterogeneous	15%	Silicates	5% Chrysotile		
		Black	80%	Tar			
		Fibrous	<1%	Paint			
		Bound					
10 A2426909	Mbi	Heterogeneous	100%	Cellulose	None Detected		
		Tan					
		Fibrous					
		Loosely Bound					
11 A2426910	Mbi	Heterogeneous	100%	Cellulose	None Detected		
		Tan					
		Fibrous					
		Loosely Bound					
12 A2426911	Mbi	Heterogeneous	100%	Cellulose	None Detected		
		Tan					
		Fibrous					
		Loosely Bound					
13 A2426912	Mfp	Heterogeneous	<1%	Cellulose	20%	Binder	None Detected
		Gray			80%	Silicates	
		Non-fibrous					
		Bound					
14 A2426913	Mfp	Heterogeneous	<1%	Cellulose	20%	Binder	None Detected
		Gray			80%	Silicates	
		Non-fibrous					
		Bound					



ASBESTOS BULK ANALYSIS

By: POLARIZING LIGHT MICROSCOPY

Client: PSI
 821 Corporate Ct.
 Waukesha, WI 53189

CEI Lab Code: A17-8548
Date Received: 06-16-17
Date Analyzed: 06-19-17
Date Reported: 06-19-17

Project: 1727 52nd St Kenosha, WI; 00541425

ASBESTOS BULK PLM, EPA 600 METHOD

Client ID Lab ID	Lab Description	Lab Attributes	NON-ASBESTOS COMPONENTS				ASBESTOS %
			Fibrous	Non-Fibrous			
15 A2426914	Mfp	Heterogeneous	<1%	Cellulose	20%	Binder	None Detected
		Gray			80%	Silicates	
		Non-fibrous			<1%	Paint	
		Bound					
16 A2426915	Mjc	Heterogeneous			100%	Binder	None Detected
		White					
		Non-fibrous					
17 A2426916	Mjc	Heterogeneous			100%	Binder	None Detected
		White					
		Non-fibrous					
		Bound					
18 A2426917	Mjc	Heterogeneous			100%	Binder	None Detected
		White					
		Non-fibrous					
19 A2426918	Mtt	Heterogeneous			85%	Silicates	None Detected
		Gray			15%	Binder	
		Non-fibrous					
		Bound					
20 A2426919	Mtt	Heterogeneous			85%	Silicates	None Detected
		Gray			15%	Binder	
		Non-fibrous					
		Bound					
21 A2426920	Mtt	Heterogeneous			85%	Silicates	None Detected
		Gray			15%	Binder	
		Non-fibrous					
		Bound					



ASBESTOS BULK ANALYSIS

By: POLARIZING LIGHT MICROSCOPY

Client: PSI
 821 Corporate Ct.
 Waukesha, WI 53189

CEI Lab Code: A17-8548
Date Received: 06-16-17
Date Analyzed: 06-19-17
Date Reported: 06-19-17

Project: 1727 52nd St Kenosha, WI; 00541425

ASBESTOS BULK PLM, EPA 600 METHOD

Client ID Lab ID	Lab Description	Lab Attributes	NON-ASBESTOS COMPONENTS				ASBESTOS %
			Fibrous		Non-Fibrous		
22 A2426921	Mbat	Heterogeneous	15%	Cellulose	25%	Tar	None Detected
		Tan,Black Fibrous Bound	25%	Fiberglass	35%	Binder	
23 A2426922	Mbat	Heterogeneous	15%	Cellulose	25%	Tar	None Detected
		Tan,Black Fibrous Bound	25%	Fiberglass	35%	Binder	
24 A2426923	Mbat	Heterogeneous	15%	Cellulose	25%	Tar	None Detected
		Tan,Black Fibrous Bound	25%	Fiberglass	35%	Binder	
25 A2426924	Mwc	Heterogeneous			95%	Binder	5% Chrysotile
		White Fibrous Bound					
26 A2426925	Mwc	Heterogeneous			95%	Binder	5% Chrysotile
		White Fibrous Bound					
27 A2426926	Mwc	Heterogeneous			100%	Binder	None Detected
		Brown Non-fibrous Bound					
28 A2426927	Mcm	Heterogeneous	<1%	Cellulose	100%	Mastic	None Detected
		Brown Non-fibrous Bound	<1%	Synthetic Fiber			



ASBESTOS BULK ANALYSIS

By: POLARIZING LIGHT MICROSCOPY

Client: PSI
 821 Corporate Ct.
 Waukesha, WI 53189

CEI Lab Code: A17-8548
Date Received: 06-16-17
Date Analyzed: 06-19-17
Date Reported: 06-19-17

Project: 1727 52nd St Kenosha, WI; 00541425

ASBESTOS BULK PLM, EPA 600 METHOD

Client ID Lab ID	Lab Description	Lab Attributes	NON-ASBESTOS COMPONENTS			ASBESTOS %	
			Fibrous	Non-Fibrous			
29 A2426928	Mcm	Heterogeneous	<1%	Cellulose	100%	Mastic	None Detected
		Brown	<1%	Synthetic Fiber			
		Non-fibrous					
		Bound					
30 A2426929	Mcm	Heterogeneous	<1%	Cellulose	100%	Mastic	None Detected
		Brown	<1%	Synthetic Fiber			
		Non-fibrous					
		Bound					
31 A2426930	Mpg	Heterogeneous			5%	Paint	2% Chrysotile
		Tan			93%	Binder	
		Fibrous					
		Bound					
32 A2426931	Mpg	Heterogeneous			5%	Paint	2% Chrysotile
		Tan			93%	Binder	
		Fibrous					
		Bound					
33 A2426932	Mpg	Heterogeneous			5%	Paint	2% Chrysotile
		Tan			93%	Binder	
		Fibrous					
		Bound					
34 A2426933	Mdwc	Heterogeneous	15%	Cellulose	30%	Calc Carb	None Detected
		White			50%	Binder	
		Fibrous			5%	Silicates	
		Bound					
35 A2426934	Mdwc	Heterogeneous	15%	Cellulose	30%	Calc Carb	None Detected
		White			50%	Binder	
		Fibrous			5%	Silicates	
		Bound					



ASBESTOS BULK ANALYSIS

By: POLARIZING LIGHT MICROSCOPY

Client: PSI
 821 Corporate Ct.
 Waukesha, WI 53189

CEI Lab Code: A17-8548
Date Received: 06-16-17
Date Analyzed: 06-19-17
Date Reported: 06-19-17

Project: 1727 52nd St Kenosha, WI; 00541425

ASBESTOS BULK PLM, EPA 600 METHOD

Client ID Lab ID	Lab Description	Lab Attributes	NON-ASBESTOS COMPONENTS				ASBESTOS %
			Fibrous		Non-Fibrous		
36 A2426935	Mdwc	Heterogeneous White Fibrous Bound	15%	Cellulose	30%	Calc Carb 50% Binder 5% Silicates	None Detected
37 A2426936	Mem2	Heterogeneous Yellow Fibrous Loose	<1% <1%	Cellulose Synthetic Fiber	100%	Mastic	None Detected
38 A2426937	Mem2	Heterogeneous Yellow Fibrous Loose	<1% <1%	Cellulose Synthetic Fiber	100%	Mastic	None Detected
39 A2426938	Mem2	Heterogeneous Yellow Fibrous Loose	<1% <1%	Cellulose Synthetic Fiber	100%	Mastic	None Detected
40 A2426939	Mcb	Heterogeneous Gray Non-fibrous Bound			5% 80% 15%	Paint Silicates Binder	None Detected
41 A2426940	Mcb	Heterogeneous Gray Non-fibrous Bound			5% 80% 15%	Paint Silicates Binder	None Detected
42 A2426941	Mcb	Heterogeneous Gray Non-fibrous Bound			5% 80% 15%	Paint Silicates Binder	None Detected



ASBESTOS BULK ANALYSIS

By: POLARIZING LIGHT MICROSCOPY

Client: PSI
 821 Corporate Ct.
 Waukesha, WI 53189

CEI Lab Code: A17-8548
Date Received: 06-16-17
Date Analyzed: 06-19-17
Date Reported: 06-19-17

Project: 1727 52nd St Kenosha, WI; 00541425

ASBESTOS BULK PLM, EPA 600 METHOD

Client ID Lab ID	Lab Description	Lab Attributes	NON-ASBESTOS COMPONENTS				ASBESTOS %
			Fibrous		Non-Fibrous		
43 A2426942	Mcbm	Heterogeneous			5%	Paint	None Detected
		Gray			80%	Silicates	
		Non-fibrous			15%	Binder	
		Bound					
44 A2426943	Mcbm	Heterogeneous			5%	Paint	None Detected
		Gray			80%	Silicates	
		Non-fibrous			15%	Binder	
		Bound					
45 A2426944	Mcbm	Heterogeneous			5%	Paint	None Detected
		Gray			80%	Silicates	
		Non-fibrous			15%	Binder	
		Bound					
46 A2426945	Msct1	Heterogeneous	25%	Cellulose	5%	Paint	None Detected
		Tan,White	25%	Fiberglass	25%	Perlite	
		Fibrous			20%	Binder	
		Bound					
47 A2426946	Msct1	Heterogeneous	25%	Cellulose	5%	Paint	None Detected
		Tan,White	25%	Fiberglass	25%	Perlite	
		Fibrous			20%	Binder	
		Bound					
48 A2426947	Msct1	Heterogeneous	25%	Cellulose	5%	Paint	None Detected
		Tan,White	25%	Fiberglass	25%	Perlite	
		Fibrous			20%	Binder	
		Bound					
49 Layer 1 A2426948	Sp2	Heterogeneous			10%	Paint	None Detected
		White			55%	Calc Carb	
		Non-fibrous			35%	Binder	
		Bound					



ASBESTOS BULK ANALYSIS

By: POLARIZING LIGHT MICROSCOPY

Client: PSI
 821 Corporate Ct.
 Waukesha, WI 53189

CEI Lab Code: A17-8548
Date Received: 06-16-17
Date Analyzed: 06-19-17
Date Reported: 06-19-17

Project: 1727 52nd St Kenosha, WI; 00541425

ASBESTOS BULK PLM, EPA 600 METHOD

Client ID Lab ID	Lab Description	Lab Attributes	NON-ASBESTOS COMPONENTS				ASBESTOS %				
			Fibrous		Non-Fibrous						
Layer 2 A2426948	Sp2	Heterogeneous White Non-fibrous Bound	5%	Paint	55%	Calc Carb	40%	Binder	None Detected		
Layer 3 A2426948	Sp2	Heterogeneous Tan Fibrous Bound	2%	Cellulose	3%	Hair	30%	Binder	65%	Silicates	None Detected
50 Layer 1 A2426949	Sp2	Heterogeneous White Non-fibrous Bound	10%	Paint	55%	Calc Carb	35%	Binder	None Detected		
Layer 2 A2426949	Sp2	Heterogeneous White Non-fibrous Bound	5%	Paint	55%	Calc Carb	40%	Binder	None Detected		
Layer 3 A2426949	Sp2	Heterogeneous Tan Fibrous Bound	2%	Cellulose	3%	Hair	30%	Binder	65%	Silicates	None Detected
51 Layer 1 A2426950	Sp2	Heterogeneous White Non-fibrous Bound	10%	Paint	55%	Calc Carb	35%	Binder	None Detected		
Layer 2 A2426950	Sp2	Heterogeneous White Non-fibrous Bound	5%	Paint	55%	Calc Carb	40%	Binder	None Detected		



ASBESTOS BULK ANALYSIS

By: POLARIZING LIGHT MICROSCOPY

Client: PSI
 821 Corporate Ct.
 Waukesha, WI 53189

CEI Lab Code: A17-8548
Date Received: 06-16-17
Date Analyzed: 06-19-17
Date Reported: 06-19-17

Project: 1727 52nd St Kenosha, WI; 00541425

ASBESTOS BULK PLM, EPA 600 METHOD

Client ID Lab ID	Lab Description	Lab Attributes	NON-ASBESTOS COMPONENTS				ASBESTOS %
			Fibrous		Non-Fibrous		
Layer 3 A2426950	Sp2	Heterogeneous Tan Fibrous Bound	2%	Cellulose	30%	Binder	None Detected
			3%	Hair	65%	Silicates	
52 A2426951A	Mstk	Heterogeneous Black Fibrous Bound			100%	Vinyl	None Detected
A2426951B	Mstk	Heterogeneous Brown Fibrous Bound	15%	Cellulose	85%	Mastic	None Detected
53 A2426952	Mstk	Heterogeneous Black Fibrous Bound			100%	Vinyl	None Detected
54 A2426953A	Mstk	Heterogeneous Black Fibrous Bound			100%	Vinyl	None Detected
A2426953B	Mstk	Heterogeneous Brown Fibrous Bound	15%	Cellulose	85%	Mastic	None Detected
55 A2426954	Mctm	Heterogeneous Gray Non-fibrous Bound			35%	Binder	None Detected
					65%	Silicates	



ASBESTOS BULK ANALYSIS

By: POLARIZING LIGHT MICROSCOPY

Client: PSI
 821 Corporate Ct.
 Waukesha, WI 53189

CEI Lab Code: A17-8548
Date Received: 06-16-17
Date Analyzed: 06-19-17
Date Reported: 06-19-17

Project: 1727 52nd St Kenosha, WI; 00541425

ASBESTOS BULK PLM, EPA 600 METHOD

Client ID Lab ID	Lab Description	Lab Attributes	NON-ASBESTOS COMPONENTS		ASBESTOS %
			Fibrous	Non-Fibrous	
56 A2426955	Mctm	Heterogeneous Gray Non-fibrous Bound	35%	Binder 65% Silicates	None Detected
57 A2426956	Mctm	Heterogeneous Gray Non-fibrous Bound	90%	Silicates 10% Binder	None Detected
58 A2426957	Mctg	Heterogeneous Tan Non-fibrous Bound	90%	Silicates 10% Binder	None Detected
59 A2426958	Mctg	Heterogeneous Tan Non-fibrous Bound	90%	Silicates 10% Binder	None Detected
60 A2426959	Mctg	Heterogeneous Tan Non-fibrous Bound	90%	Silicates 10% Binder	None Detected
61 A2426960	Mts	Heterogeneous Off-white Non-fibrous Bound	100%	Binder	None Detected
62 A2426961	Mts	Heterogeneous Off-white Non-fibrous Bound	100%	Binder	None Detected



ASBESTOS BULK ANALYSIS

By: POLARIZING LIGHT MICROSCOPY

Client: PSI
 821 Corporate Ct.
 Waukesha, WI 53189

CEI Lab Code: A17-8548
Date Received: 06-16-17
Date Analyzed: 06-19-17
Date Reported: 06-19-17

Project: 1727 52nd St Kenosha, WI; 00541425

ASBESTOS BULK PLM, EPA 600 METHOD

Client ID Lab ID	Lab Description	Lab Attributes	NON-ASBESTOS COMPONENTS		ASBESTOS %
			Fibrous	Non-Fibrous	
63 A2426962	Mts	Heterogeneous Off-white Non-fibrous Bound	100%	Binder	None Detected
64 A2426963	Mbi2	Heterogeneous Off-white Fibrous Bound	100%	Fiberglass	None Detected
65 A2426964	Mbi2	Heterogeneous Off-white Fibrous Bound	100%	Fiberglass	None Detected
66 A2426965	Mbi2	Heterogeneous Off-white Fibrous Bound	100%	Fiberglass	None Detected
67 A2426966	Verm	Heterogeneous Gold Non-fibrous Bound	100%	Vermiculite	None Detected
68 A2426967	Verm	Heterogeneous Gold Non-fibrous Bound	100%	Vermiculite	None Detected
69 A2426968	Verm	Heterogeneous Gold Non-fibrous Bound	100%	Vermiculite	None Detected



ASBESTOS BULK ANALYSIS

By: POLARIZING LIGHT MICROSCOPY

Client: PSI
 821 Corporate Ct.
 Waukesha, WI 53189

CEI Lab Code: A17-8548
Date Received: 06-16-17
Date Analyzed: 06-19-17
Date Reported: 06-19-17

Project: 1727 52nd St Kenosha, WI; 00541425

ASBESTOS BULK PLM, EPA 600 METHOD

Client ID Lab ID	Lab Description	Lab Attributes	NON-ASBESTOS COMPONENTS				ASBESTOS %
			Fibrous	Non-Fibrous			
70 A2426969	Mwce	Heterogeneous Black Non-fibrous Bound	100%	Binder			None Detected
71 A2426970	Mwce	Heterogeneous Black Non-fibrous Bound	100%	Binder			None Detected
72 A2426971	Mwce	Heterogeneous Black Non-fibrous Bound	100%	Binder			None Detected
73 A2426972	Mdce	Heterogeneous Brown,Off-white Non-fibrous Bound	5%	Cellulose	95%	Binder	None Detected
74 A2426973	Mdce	Heterogeneous Brown,Off-white Non-fibrous Bound	5%	Cellulose	95%	Binder	None Detected
75 A2426974	Mdce	Heterogeneous Brown,Off-white Non-fibrous Bound	5%	Cellulose	95%	Binder	None Detected
76 A2426975	Mdce2	Heterogeneous Brown,Off-white Non-fibrous Bound	5%	Cellulose	95%	Binder	None Detected



ASBESTOS BULK ANALYSIS

By: POLARIZING LIGHT MICROSCOPY

Client: PSI
 821 Corporate Ct.
 Waukesha, WI 53189

CEI Lab Code: A17-8548
Date Received: 06-16-17
Date Analyzed: 06-19-17
Date Reported: 06-19-17

Project: 1727 52nd St Kenosha, WI; 00541425

ASBESTOS BULK PLM, EPA 600 METHOD

Client ID Lab ID	Lab Description	Lab Attributes	NON-ASBESTOS COMPONENTS				ASBESTOS %
			Fibrous		Non-Fibrous		
77 A2426976	Mdce2	Heterogeneous Brown,Off-white Non-fibrous Bound	5%	Cellulose	95%	Binder	None Detected
78 A2426977	Mdce2	Heterogeneous Brown,Off-white Non-fibrous Bound	5%	Cellulose	95%	Binder	None Detected
79 A2426978	Mrs1	Heterogeneous Black Fibrous Bound	5% 75%	Cellulose Fiberglass	5% 15%	Gravel Tar	None Detected
80 A2426979	Mrs1	Heterogeneous Black Fibrous Bound	5% 75%	Cellulose Fiberglass	5% 15%	Gravel Tar	None Detected
81 A2426980	Mrs1	Heterogeneous Black Fibrous Bound	5% 75%	Cellulose Fiberglass	5% 15%	Gravel Tar	None Detected
82 A2426981	Mrs2	Heterogeneous Black Fibrous Bound	5% 75%	Cellulose Fiberglass	5% 15%	Gravel Tar	None Detected
83 A2426982	Mrs2	Heterogeneous Black Fibrous Bound	5% 75%	Cellulose Fiberglass	5% 15%	Gravel Tar	None Detected



ASBESTOS BULK ANALYSIS

By: POLARIZING LIGHT MICROSCOPY

Client: PSI
 821 Corporate Ct.
 Waukesha, WI 53189

CEI Lab Code: A17-8548
Date Received: 06-16-17
Date Analyzed: 06-19-17
Date Reported: 06-19-17

Project: 1727 52nd St Kenosha, WI; 00541425

ASBESTOS BULK PLM, EPA 600 METHOD

Client ID Lab ID	Lab Description	Lab Attributes	NON-ASBESTOS COMPONENTS				ASBESTOS %
			Fibrous		Non-Fibrous		
84 A2426983	Mrs2	Heterogeneous	5%	Cellulose	5%	Gravel	None Detected
		Black	75%	Fiberglass	15%	Tar	
		Fibrous Bound					
85 A2426984	Mrs3	Heterogeneous	5%	Cellulose	5%	Gravel	None Detected
		Black	75%	Fiberglass	15%	Tar	
		Fibrous Bound					
86 A2426985	Mrs3	Heterogeneous	5%	Cellulose	5%	Gravel	None Detected
		Black	75%	Fiberglass	15%	Tar	
		Fibrous Bound					
87 A2426986	Mrs3	Heterogeneous	5%	Cellulose	5%	Gravel	None Detected
		Black	75%	Fiberglass	15%	Tar	
		Fibrous Bound					
88 A2426987	Mrs4	Heterogeneous	5%	Cellulose	5%	Gravel	None Detected
		Black	75%	Fiberglass	15%	Tar	
		Fibrous Bound					
89 A2426988	Mrs4	Heterogeneous	5%	Cellulose	5%	Gravel	None Detected
		Black	75%	Fiberglass	15%	Tar	
		Fibrous Bound					
90 A2426989	Mrs4	Heterogeneous	5%	Cellulose	5%	Gravel	None Detected
		Black	75%	Fiberglass	15%	Tar	
		Fibrous Bound					



ASBESTOS BULK ANALYSIS

By: POLARIZING LIGHT MICROSCOPY

Client: PSI
821 Corporate Ct.
Waukesha, WI 53189

CEI Lab Code: A17-8548
Date Received: 06-16-17
Date Analyzed: 06-19-17
Date Reported: 06-19-17

Project: 1727 52nd St Kenosha, WI; 00541425

ASBESTOS BULK PLM, EPA 600 METHOD

Client ID Lab ID	Lab Description	Lab Attributes	NON-ASBESTOS COMPONENTS				ASBESTOS %
			Fibrous		Non-Fibrous		
91 A2426990	Mrs5	Heterogeneous	5%	Cellulose	5%	Gravel	None Detected
		Black	75%	Fiberglass	15%	Tar	
		Fibrous Bound					
92 A2426991	Mrs5	Heterogeneous	5%	Cellulose	5%	Gravel	None Detected
		Black	75%	Fiberglass	15%	Tar	
		Fibrous Bound					
93 A2426992	Mrs5	Heterogeneous	5%	Cellulose	5%	Gravel	None Detected
		Black	75%	Fiberglass	15%	Tar	
		Fibrous Bound					
94 A2426993	Mrf	Heterogeneous	10%	Cellulose	85%	Tar	5% Chrysotile
		Black					
		Fibrous Bound					
95 A2426994	Mrf	Heterogeneous	10%	Cellulose	85%	Tar	5% Chrysotile
		Black					
		Fibrous Bound					
96 A2426995	Mrf	Heterogeneous	10%	Cellulose	85%	Tar	5% Chrysotile
		Black					
		Fibrous Bound					
97 A2426996	Mrm	Heterogeneous	75%	Cellulose	25%	Binder	None Detected
		Tan					
		Fibrous Bound					



ASBESTOS BULK ANALYSIS

By: POLARIZING LIGHT MICROSCOPY

Client: PSI
821 Corporate Ct.
Waukesha, WI 53189

CEI Lab Code: A17-8548
Date Received: 06-16-17
Date Analyzed: 06-19-17
Date Reported: 06-19-17

Project: 1727 52nd St Kenosha, WI; 00541425

ASBESTOS BULK PLM, EPA 600 METHOD

Client ID Lab ID	Lab Description	Lab Attributes	NON-ASBESTOS COMPONENTS				ASBESTOS %
			Fibrous		Non-Fibrous		
98 A2426997	Mrm	Heterogeneous Tan Fibrous Bound	75%	Cellulose	25%	Binder	None Detected
99 A2426998	Mrm	Heterogeneous Tan Fibrous Bound	75%	Cellulose	25%	Binder	None Detected
100 A2426999	Mrf2	Heterogeneous Black, Tan Fibrous Bound	75%	Cellulose	20%	Tar	5% Chrysotile
101 A2427000	Mrf2	Heterogeneous Black, Tan Fibrous Bound	75%	Cellulose	20%	Tar	5% Chrysotile
102 A2427001	Mrf2	Heterogeneous Black, Tan Fibrous Bound	75%	Cellulose	20%	Tar	5% Chrysotile
103 Layer 1 A2427002	Sp1	Heterogeneous Off-white Fibrous Bound			5%	Paint	None Detected
					85%	Calc Carb	
					10%	Binder	
Layer 2 A2427002	Sp1	Heterogeneous Gray Fibrous Bound			85%	Silicates	None Detected
					15%	Binder	



ASBESTOS BULK ANALYSIS

By: POLARIZING LIGHT MICROSCOPY

Client: PSI
 821 Corporate Ct.
 Waukesha, WI 53189

CEI Lab Code: A17-8548
Date Received: 06-16-17
Date Analyzed: 06-19-17
Date Reported: 06-19-17

Project: 1727 52nd St Kenosha, WI; 00541425

ASBESTOS BULK PLM, EPA 600 METHOD

Client ID Lab ID	Lab Description	Lab Attributes	NON-ASBESTOS COMPONENTS		ASBESTOS %
			Fibrous	Non-Fibrous	
104 Layer 1 A2427003	Sp1	Heterogeneous	5%	Paint	None Detected
		Off-white	85%	Calc Carb	
		Fibrous	10%	Binder	
		Bound			
Layer 2 A2427003	Sp1	Heterogeneous	85%	Silicates	None Detected
		Gray	15%	Binder	
		Fibrous			
		Bound			
105 Layer 1 A2427004	Sp1	Heterogeneous	5%	Paint	None Detected
		Off-white	85%	Calc Carb	
		Fibrous	10%	Binder	
		Bound			
Layer 2 A2427004	Sp1	Heterogeneous	85%	Silicates	None Detected
		Gray	15%	Binder	
		Fibrous			
		Bound			
106 Layer 1 A2427005	Sp1	Heterogeneous	5%	Paint	None Detected
		Off-white	85%	Calc Carb	
		Fibrous	10%	Binder	
		Bound			
Layer 2 A2427005	Sp1	Heterogeneous	85%	Silicates	None Detected
		Gray	15%	Binder	
		Fibrous			
		Bound			
107 Layer 1 A2427006	Sp1	Heterogeneous	5%	Paint	None Detected
		Off-white	85%	Calc Carb	
		Fibrous	10%	Binder	
		Bound			



ASBESTOS BULK ANALYSIS

By: POLARIZING LIGHT MICROSCOPY

Client: PSI
 821 Corporate Ct.
 Waukesha, WI 53189

CEI Lab Code: A17-8548
Date Received: 06-16-17
Date Analyzed: 06-19-17
Date Reported: 06-19-17

Project: 1727 52nd St Kenosha, WI; 00541425

ASBESTOS BULK PLM, EPA 600 METHOD

Client ID Lab ID	Lab Description	Lab Attributes	NON-ASBESTOS COMPONENTS		ASBESTOS %
			Fibrous	Non-Fibrous	
Layer 2 A2427006	Sp1	Heterogeneous Gray Fibrous Bound	85% 15%	Silicates Binder	None Detected
108 Layer 1 A2427007	Sp1	Heterogeneous Pink,Tan Non-fibrous Bound	5% 85% 10%	Paint Calc Carb Binder	None Detected
Layer 2 A2427007	Sp1	Heterogeneous Off-white Non-fibrous Bound	85% 15%	Calc Carb Binder	None Detected
Layer 3 A2427007	Sp1	Heterogeneous Gray Fibrous Bound	85% 15%	Silicates Binder	None Detected
109 Layer 1 A2427008	Sp1	Heterogeneous Pink,Tan Non-fibrous Bound	5% 85% 10%	Paint Calc Carb Binder	None Detected
Layer 2 A2427008	Sp1	Heterogeneous Off-white Non-fibrous Bound	85% 15%	Calc Carb Binder	None Detected
Layer 3 A2427008	Sp1	Heterogeneous Gray Fibrous Bound	85% 15%	Silicates Binder	None Detected



ASBESTOS BULK ANALYSIS

By: POLARIZING LIGHT MICROSCOPY

Client: PSI
 821 Corporate Ct.
 Waukesha, WI 53189

CEI Lab Code: A17-8548
Date Received: 06-16-17
Date Analyzed: 06-19-17
Date Reported: 06-19-17

Project: 1727 52nd St Kenosha, WI; 00541425

ASBESTOS BULK PLM, EPA 600 METHOD

Client ID Lab ID	Lab Description	Lab Attributes	NON-ASBESTOS COMPONENTS		ASBESTOS %
			Fibrous	Non-Fibrous	
110 A2427009	Mwb	Heterogeneous	85%	Silicates	None Detected
		Black	15%	Binder	
		Non-fibrous			
		Bound			
111 A2427010	Mwb	Heterogeneous	85%	Silicates	None Detected
		Black	15%	Binder	
		Non-fibrous			
		Bound			
112 A2427011	Mwb	Heterogeneous	85%	Silicates	None Detected
		Black	15%	Binder	
		Non-fibrous			
		Bound			



LEGEND: Non-Anth = Non-Asbestiform Anthophyllite
Non-Trem = Non-Asbestiform Tremolite
Calc Carb = Calcium Carbonate

METHOD: EPA 600 / R93 / 116 and EPA 600 / M4-82 / 020


REPORTING LIMIT: <1% by visual estimation

REGULATORY LIMIT: >1% by weight

Due to the limitations of the EPA 600 method, nonfriable organically bound materials (NOBs) such as vinyl floor tiles can be difficult to analyze via polarized light microscopy (PLM). EPA recommends that all NOBs analyzed by PLM, and found not to contain asbestos, be further analyzed by Transmission Electron Microscopy (TEM). Please note that PLM analysis of dust and soil samples for asbestos is not covered under NVLAP accreditation. Estimated measurement of uncertainty is available on request.

This report relates only to the samples tested or analyzed and may not be reproduced, except in full, without written approval by CEI Labs, Inc. CEI Labs makes no warranty representation regarding the accuracy of client submitted information in preparing and presenting analytical results. Interpretation of the analytical results is the sole responsibility of the client. Samples were received in acceptable condition unless otherwise noted. This report may not be used by the client to claim product endorsement by NVLAP or any other agency of the U.S. Government.

ANALYST: 
Mikaela Batta

APPROVED BY: 
Tianbao Bai, Ph.D., CIH
Laboratory Director





107 New Edition Court, Cary, NC 27511
 Tel: 866-481-1412; Fax: 919-481-1442

(112) A17-8548
 A2426900-
 A2427011

ASBESTOS CHAIN OF CUSTODY

LAB USE ONLY:
CEI Lab Code:
CEI Lab I.D. Range:

COMPANY INFORMATION	PROJECT INFORMATION
CEI CLIENT #:	Job Contact: <u>JIM UBIK</u>
Company: <u>PSI, INC</u>	Email / Tel: <u>Jim. Ubik@PSIUSA.COM</u>
Address: <u>821 CORPORATE COURT</u> <u>WAUKESHA, WI 53189</u>	Project Name: <u>1727 52nd ST Kenosha, WI</u>
Email: <u>LARRY. ROETHER@PSIUSA.COM</u>	Project ID# <u>0054/1/25</u>
Tel: <u>262-521-2125</u> Fax: <u>262-521-2471</u>	PO #:
STATE SAMPLES COLLECTED IN: <u>WI</u>	

IF TAT IS NOT MARKED STANDARD 3 DAY TAT APPLIES.

ASBESTOS	METHOD	TURN AROUND TIME					
		4 HR	8 HR	24 HR	2 DAY	3 DAY	5 DAY
PLM BULK	EPA 600	<input type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>	<input checked="" type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>
PLM POINT COUNT (400)	EPA 600	<input type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>
PLM POINT COUNT (1000)	EPA 600	<input type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>
PLM GRAV w POINT COUNT	EPA 600		<input type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>
PLM BULK	CARB 435		<input type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>
PCM AIR	NIOSH 7400	<input type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>
TEM AIR	EPA AHERA	<input type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>
TEM AIR	NIOSH 7402	<input type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>
TEM AIR	ISO 10312	<input type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>
TEM AIR	ASTM 6281-09	<input type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>
TEM BULK	CHATFIELD		<input type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>
TEM DUST WIPE	ASTM D6480-05	<input type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>
TEM DUST MICROVAC	ASTM D5755-09	<input type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>
TEM SOIL	ASTM D7521-13			<input type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>
TEM VERMICULITE	CINCINNATI METHOD			<input type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>
OTHER:		<input type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>

REMARKS / SPECIAL INSTRUCTIONS:			
<u>SAMPLES # 067-112</u>		<input checked="" type="checkbox"/> Accept Samples <input type="checkbox"/> Reject Samples	
Relinquished By:	Date/Time	Received By:	Date/Time
<u>Mike Larson</u>	<u>6/15/17</u>	<u>PL</u>	<u>6-16 8:50</u>
	<u>2:00pm</u>		

Samples will be disposed of 30 days after analysis

BULK SAMPLE LOG

Client:	City of Kenosha	Construction Date:	Unknown
Project:	Two-Story Residential Building	Date of Inspection:	6-13-15/17
Address:	1727 52nd St., Kenosha, WI	Inspector:	Mike Larsen
		Inspector #:	All-13850

SAMPLE NUMBER	SAMPLE LOCATION	MATERIAL DESCRIPTION
01	01	Brick
02	104	Brick
03	Exterior	Brick
04	01	Brick Mortar
05	104	Brick Mortar
06	Exterior	Brick Mortar
07	01	Pipe Packing - Black
08	01	Pipe Packing - Black
09	01	Pipe Packing - Black
10	01	Blown-in Insulation - Gray
11	103	Blown-in Insulation - Gray
12	207	Blown-in Insulation - Gray
13	01	Flue Packing
14	01	Flue Packing
15	104	Flue Packing
16	02	Joist Caulk - White
17	02	Joist Caulk - White
18	02	Joist Caulk - White
19	02	Transite Tub
20	02	Transite Tub
21	02	Transite Tub
22	STWL1	Fiberglass Batt Insulation with Suspect Layer
23	105	Fiberglass Batt Insulation with Suspect Layer
24	105	Fiberglass Batt Insulation with Suspect Layer
25	100	Window Caulk - White
26	100	Window Caulk - White
27	100	Window Caulk - White
28	101	Exposed Mastic - Brown
29	101	Exposed Mastic - Brown
30	102	Exposed Mastic - Brown
31	101	Window Pane Glazing - Beige
32	101	Window Pane Glazing - Beige
33	102	Window Pane Glazing - Beige

BULK SAMPLE LOG


Client: City of Kenosha	Construction Date: Unknown
Project: Two-Story Residential Building	Date of Inspection: 6-13-15/17
Address: 1727 52nd St., Kenosha, WI	Inspector: Mike Larsen
	Inspector #: All-13850

SAMPLE NUMBER	SAMPLE LOCATION	MATERIAL DESCRIPTION
34	103	Drywall/Joint Compound System
35	STWL2	Drywall/Joint Compound System
36	202	Drywall/Joint Compound System
37	104	Exposed Caulk - Yellow
38	104	Exposed Caulk - Yellow
39	104	Exposed Caulk - Yellow
40	104	Concrete Block
41	106	Concrete Block
42	Exterior	Concrete Block
43	104	Concrete Block Mortar
44	106	Concrete Block Mortar
45	Exterior	Concrete Block Mortar
46	104	2' x 4' Suspended Ceiling Tile: Pinholes and Fissures
47	104	2' x 4' Suspended Ceiling Tile: Pinholes and Fissures
48	104	2' x 4' Suspended Ceiling Tile: Pinholes and Fissures
49	202	Decorative Plaster
50	202	Decorative Plaster
51	202	Decorative Plaster
52	STWL2	Black Stair Tread
53	STWL2	Black Stair Tread
54	STWL2	Black Stair Tread
55	202	Ceramic Tile Mastic
56	202	Ceramic Tile Mastic
57	206	Ceramic Tile Mastic
58	202	Ceramic Tile Grout
59	202	Ceramic Tile Grout
60	206	Ceramic Tile Grout
61	206	Tub Surround Mastic - White
62	206	Tub Surround Mastic - White
63	206	Tub Surround Mastic - White
64	300	Blown-in Insulation - White
65	300	Blown-in Insulation - White
66	300	Blown-in Insulation - White

BULK SAMPLE LOG

Client: City of Kenosha	Construction Date: Unknown
Project: Two-Story Residential Building	Date of Inspection: 6-13-15/17
Address: 1727 52nd St., Kenosha, WI	Inspector: Mike Larsen
	Inspector #: All-13850

SAMPLE NUMBER	SAMPLE LOCATION	MATERIAL DESCRIPTION
67	300	Vermiculite
68	300	Vermiculite
69	300	Vermiculite
70	Exterior	Exterior Window Caulk - Brown
71	Exterior	Exterior Window Caulk - Brown
72	Exterior	Exterior Window Caulk - Brown
73	Exterior	Exterior Door Caulk - White
74	Exterior	Exterior Door Caulk - White
75	Exterior	Exterior Door Caulk - White
76	Exterior	Exterior Window Caulk - Gray
77	Exterior	Exterior Window Caulk - Gray
78	Exterior	Exterior Window Caulk - Gray
79	Roof 1	Brown Roof Shingle - Top Layer
80	Roof 1	Brown Roof Shingle - Top Layer
81	Roof 1	Brown Roof Shingle - Top Layer
82	Roof 1	Red Roof Shingle - 2nd Layer
83	Roof 1	Red Roof Shingle - 2nd Layer
84	Roof 1	Red Roof Shingle - 2nd Layer
85	Roof 1	Green Roof Shingle - 3rd Layer
86	Roof 1	Green Roof Shingle - 3rd Layer
87	Roof 1	Green Roof Shingle - 3rd Layer
88	Roof 1	Gray Roof Shingle - 4th Layer
89	Roof 1	Gray Roof Shingle - 4th Layer
90	Roof 1	Gray Roof Shingle - 4th Layer
91	Roof 1	Black Roof Shingle - Bottom Layer
92	Roof 1	Black Roof Shingle - Bottom Layer
93	Roof 1	Black Roof Shingle - Bottom Layer
94	Roof 1	Roof Flashing Associated with Shingled Roof
95	Roof 1	Roof Flashing Associated with Shingled Roof
96	Roof 1	Roof Flashing Associated with Shingled Roof
97	Roof 2	Roof Membrane
98	Roof 2	Roof Membrane
99	Roof 2	Roof Membrane



PSI Project Number:
00541425

Scale:
Not to Scale


Date:
6/15/2017

City of Kenosha
1727 52nd Street
Kenosha, WI

**Floor Plan
Basement**

Environmental Services
821 Corporate Court
Waukesha, Wisconsin 53189
(262) 521-2125 Fax (262) 521-2471





PSI Project Number:
00541425

Scale:
Not to Scale


Date:
6/15/2017

City of Kenosha
1727 52nd Street
Kenosha, WI

Floor Plan
First Floor

Environmental Services
821 Corporate Court
Waukesha, Wisconsin 53189
(262) 521-2125 Fax (262) 521-2471





PSI Project Number:
00541425

Date:
6/15/2017


Scale:
Not to Scale

City of Kenosha
1727 52nd Street
Kenosha, WI

Floor Plan
2nd Floor

Environmental Services
821 Corporate Court
Waukesha, Wisconsin 53189
(262) 521-2125 Fax (262) 521-2471





PSI Project Number:
00541425

Date:
6/15/2017

Scale:
Not to Scale

City of Kenosha
1727 52nd Street
Kenosha, WI

**Floor Plan
Attic**

Environmental Services
821 Corporate Court
Waukesha, Wisconsin 53189
(262) 521-2125 Fax (262) 521-2471



Milwaukee Lead/Asbestos Information Center

A division of Midwest Certified Training, Inc.
3495 North 124th Street, Brookfield, WI 53005 Phone: 414-481-9070



Michael Louis Franklin Larsen

Has successfully completed a course and passed the examination on April 28, 2016 with a minimum score of 70 percent, that meets all criteria for the State of Wisconsin Recertification as an

Asbestos Inspector Refresher Course

Date of Course: April 28, 2016

Date Issued April 28, 2016

Date of Expiration: April 28, 2017

Certification Number: AIR16042854708

Location: Milwaukee Lead/Asbestos Information Center, 3495 North 124th Street, Brookfield, WI 53005

DCQ Course ID #: 9606

A handwritten signature in blue ink that reads "Rocky Everly".

Rocky Everly, Director of Milwaukee Lead/Asbestos Information Center, Inc.
3495 North 124th Street
Brookfield, WI 53005
414-481-9070

Company Certificate

This certifies that

PSI - PROFESSIONAL SERVICE INDUSTRIES INC

821 CORPORATE CT
WAUKESHA WI 53189-5009

is certified under ch. DHS 159, Wis. Adm. Code as a

Asbestos Company - Primary

Certificate Issue Date: 07/16/2015
Expiration Date: 08/01/2017, 12:01 a.m.
Certification #: CAP-16820

Wisconsin Department of Health Services
Division of Public Health
Bureau of Environmental and Occupational Health
Asbestos & Lead Section
PO Box 2659
Madison WI 53701-2659
Phone: (608) 261-6876



Shelley A Bruce
Shelley A Bruce,
Unit Supervisor.



SCOPE OF ACCREDITATION TO ISO/IEC 17025:2005

CEI Labs, Inc.
730 SE Maynard Road
Cary, NC 27511
Dr. Tianbao Bai
Phone: 919-481-1413 Fax: 919-481-1442
Email: bai@ceilabs.com
<http://www.ceilabs.com>

ASBESTOS FIBER ANALYSIS

NVLAP LAB CODE 101768-0

Bulk Asbestos Analysis

<u>Code</u>	<u>Description</u>
18/A01	EPA 600/M4-82-020: Interim Method for the Determination of Asbestos in Bulk Insulation Samples
18/A03	EPA 600/R-93/116: Method for the Determination of Asbestos in Bulk Building Materials

Airborne Asbestos Analysis

<u>Code</u>	<u>Description</u>
18/A02	U.S. EPA's "Interim Transmission Electron Microscopy Analytical Methods-Mandatory and Nonmandatory-and Mandatory Section to Determine Completion of Response Actions" as found in 40 CFR, Part 763, Subpart E, Appendix A.

A handwritten signature in black ink, appearing to read "Dana S. Laman".

For the National Voluntary Laboratory Accreditation Program

United States Department of Commerce
National Institute of Standards and Technology



Certificate of Accreditation to ISO/IEC 17025:2005

NVLAP LAB CODE: 101768-0

CEI Labs, Inc.
Cary, NC

is accredited by the National Voluntary Laboratory Accreditation Program for specific services,
listed on the Scope of Accreditation, for:

Asbestos Fiber Analysis

This laboratory is accredited in accordance with the recognized International Standard ISO/IEC 17025:2005.
This accreditation demonstrates technical competence for a defined scope and the operation of a laboratory quality management system (refer to joint ISO-ILAC-IAF Communique dated January 2009).

2016-04-01 through 2017-03-31

Effective Dates



David F. Alderman

For the National Voluntary Laboratory Accreditation Program

**THE CITY OF KENOSHA, WISCONSIN
REQUEST FOR PROPOSAL TO REMOVE AND DISPOSE OF
ASBESTOS CONTAINING MATERIAL, RAZE STRUCTURE(S)
AND RESTORE LOT(S)**

Proposal No. 02-18

GENERAL SPECIFICATIONS AND CONDITIONS

ASBESTOS CONTAINING MATERIAL. Category I, Category II and Regulated Asbestos Containing Material (RACM), are defined in 40 C.F.R. 61.141.

The Contractor shall warrant that all Work performed under the Contract by the Contractor, subcontractors, and major material suppliers shall be performed in accordance with all Federal, State and local laws, rules and regulations, including but not limited to the National Emission Standards for Hazardous Air Pollutants (NESHAP), 40 C.F.R. 61.145.

The Contractor shall complete a Notification for Demolition and/or Renovation and Application for Permit Exemption (Form 4500-113), and supply a copy to the Department of Community Development and Inspections at the time of permitting.

EQUIPMENT AND MATERIAL STORAGE. The use of any other parcel of land for the storing of equipment and materials is prohibited unless specifically permitted by the Director of Community Development and Inspections and the Director of Public Works or their designee. A public right-of-way may not be used for the storing of equipment and materials without the Contractor obtaining a Street Opening/Occupying Permit from the Department of Public Works.

PERMITS, APPROVALS AND TIME OF PERFORMANCE. The Contractor shall obtain all required permits and approvals to perform the Work within fifteen (15) calendar days of notification of execution of the Contract with directions to proceed from the City. The Work shall be completed within 45 calendar days of notification of execution of the Contract with directions to proceed from the City. The Work shall be diligently performed until complete in accordance with the Contract, time being of the essence with respect to the commencement and completion of the Work. The Contractor shall furnish sufficient labor, material, equipment, and supervision to complete the Work within the required time of performance. Time lost and any costs incurred by the Contractor due to the Contractor's lack of coordination with the City or the Contractor's subcontractors and major material suppliers shall not be grounds for a claim for additional compensation or an extension of time to complete the Work. Refer to the Detailed Description of Work to be Performed for a description of the Work to be performed and the manner in which the Work is to be performed.

UTILITY SERVICES. The Contractor shall be required to contact Diggers Hotline for utility locations prior to the commencement of any Work. Prior to obtaining a Raze Permit, the Contractor shall disconnect and cap all sanitary sewer, storm sewer and water laterals in accordance with Chapter 32 of the Code of General Ordinances. The City shall disconnect gas and electrical power and remove power lines from the structure(s) to be razed.

FOUNDATION, FLOOR AND CONCRETE REMOVAL. The foundation and floor shall be completely removed. All concrete and/or gravel on the premises except for City public sidewalks not marked shall be removed. The Contractor must contact the Department of Community Development and Inspections for an inspection of the excavation before backfilling begins on-site.

DRIVEWAY APPROACH REMOVAL AND SITE RESTORATION. The Contractor shall remove existing driveway approaches within the property limits. This Work shall also include disposing of the resulting materials, backfilling trenches and pits with appropriate backfill material, seeding and mulching, and site cleanup. The Contractor shall obtain all permits required for removing driveway approaches prior to beginning Work within the public right-of-way. If any utilities or structures exist within the removal limits, the Contractor shall be responsible for contacting the City and other appropriate authorities promptly.

CURB AND GUTTER REMOVAL AND REPLACEMENT. The Contractor shall remove the existing concrete curb and gutter driveway opening to an existing joint and shall replace said section with a "full-head" concrete curb and gutter. This Work shall be done in accordance with the current edition of the Wisconsin Department of Transportation Standard Specifications for Highway and Structure Construction.

If an existing curb and gutter section is overlaid with asphaltic pavement, the Contractor shall reconstruct the curb and gutter section and resurface it with asphaltic pavement. The Contractor shall saw-cut the pavement and curb and gutter section in accordance with the Department of Public Works requirements. This Work shall be inspected prior to pouring.

This Work shall also consist of saw-cutting, removing and replacing unsuitable foundation underlying the curb and gutter section; providing, installing and compacting crushed aggregate base course; concrete masonry, expansion felt, finishing, curing and protecting; cleaning, backfilling, restoring disturbed areas and disposal of excess material; tools, labor, material, equipment, and other incidentals necessary to complete the Work. The Contractor shall obtain all permits required for removing and replacing curb and gutter prior to the beginning such Work within the public right-of-way. If any utilities or structures exist within the removal limits, the Contractor shall be responsible for contacting the City and other appropriate authorities promptly.

PUBLIC SIDEWALK REMOVAL AND REPLACEMENT. The Contractor shall remove and replace any public sidewalk marked for removal by the City and any public sidewalk damaged by the Contractor in course of performing the Work. The replacement shall be done using 1-1/4" base aggregate. The Contractor shall be responsible for maintaining the integrity of the public sidewalk after the removal of the foundation walls. The Contractor shall obtain all required permits for the removal and replacement of any public sidewalk. If the public sidewalk is undermined during the raze process, the City of Kenosha's Department of Public Works shall, in its sole discretion, decide whether the sidewalk must be reconstructed and replaced. The Work shall consist of saw-cutting, removing and replacing unsuitable foundation underlying the public sidewalk; providing, installing, and compacting crushed aggregate base course; concrete masonry, expansion felt, finishing, curing and protecting; cleaning, backfilling, restoring disturbed areas and disposal of excess material; tools, labor, material, equipment and all other incidentals necessary to complete Work in accordance with the current edition of the Wisconsin Department of Transportation Standard Specifications for Highway and Structure Construction.

REMOVAL OF MATERIAL AND DEBRIS. The Contractor shall remove all combustible material, shrubs, junk and debris from the site.

DAMAGE OR THEFT. The City does not assume any responsibility to protect any structure or the contents thereof, including, but not limited to, salvageable furnishings, fixtures, or attachments of whatever kind or nature so as to permit salvage prior to the time of razing. The City shall not be liable to the Contractor for any loss, destruction, theft or removal of any property from the premises nor shall the Contractor be entitled to any allowance or other claim against the City should any of said acts occur.

FILL MATERIAL AND FINAL GRADING. The Contractor shall use clean fill material with stones not exceeding one inch (1") in diameter and shall fill the lot to match the public sidewalk grade and adjacent lot line grade. A description and the original source of the fill material is required. Soil testing will be necessary if the source of the fill material is not from a historically clean site or is from an unknown source. The Contractor shall not assume that fill material will be available from the Department of Public Works or the Kenosha Water Utility. No price based upon these assumptions shall be provided and will cause rejection of the Proposal. The final grading plan shall be approved by the City's Erosion Control Inspector.

EROSION CONTROL. The Contractor shall be responsible for obtaining an Erosion Control Permit and for complying with the Land-Disturbing Erosion and Sediment Control Ordinance as set forth in Chapter XXXIII of the Code of General Ordinances for City of Kenosha.

TOP SOIL, SEEDING AND MULCHING. Upon completion of the demolition, the Contractor shall fill the lot with four (4") to six (6") inches of top soil which shall be seeded with seed mixture 40 or other approved seed mixture and mulched with hay, straw, or other material approved by the City. Seeding and mulching shall be completed when conditions will allow as determined by the City. Top soil shall be clear of rocks, twigs, foreign materials and clumps that cannot be broken down in order to provide a uniformly textured soil.

DEMOLITION TECHNIQUES. The Work shall be performed in accordance with accepted demolition techniques of the National Association of Demolition Contractors, incorporated herein by reference. Water shall be used as a dust suppressant whenever practicable.

BLASTING PROHIBITED. The Work will not be performed through blasting with explosives.

**THE CITY OF KENOSHA, WISCONSIN
 REQUEST FOR PROPOSAL TO REMOVE AND DISPOSE OF
 ASBESTOS CONTAINING MATERIAL, RAZE STRUCTURE(S)
 AND RESTORE LOT(S)**

Proposal No. 02-18

PROPOSAL

Finance:

A representative of this organization has inspected the structure(s) and lot(s) described below at the specified location(s), and hereby submits the following Proposal to Remove and Dispose of Asbestos Containing Material, Raze Structure(s) and to Restore Lot(s) at the following prices, to be firm for thirty (30) days from the date of this Proposal, subject to the Proposal being accepted within that time and a Contract entered into for that price.

1505 60th Street, Kenosha, Wisconsin	05-123-06-203-003
Address	Tax Parcel No.

\$ _____	_____
Dollar Amount	Written Dollar Amount

1727 52nd Street, Kenosha, Wisconsin	12-223-31-326-003
Address	Tax Parcel No.

\$ _____	_____
Dollar Amount	Written Dollar Amount

6720 25th Avenue, Kenosha, Wisconsin	01-122-01-404-028
Address	Tax Parcel No.

\$ _____	_____
Dollar Amount	Written Dollar Amount

\$ _____	_____
TOTAL DOLLAR AMOUNT	TOTAL WRITTEN DOLLAR AMOUNT

Continued on next page

The effective date of the Contract shall be the date of last execution. The Work shall commence and deadlines for performance shall commence upon notification of execution of the Contract with directions to proceed from the City. The Contractor shall furnish sufficient labor, material, equipment and supervision in order to complete the Work within the required time of performance.

Respectfully submitted,

Firm: _____

Signature: _____

Type/Print Name: _____

Title: _____

Date: _____

PERFORMANCE AND PAYMENT BOND

§

Project No. 02-18

BY: (Principal)

**To And For The Benefit Of
The City of Kenosha, Wisconsin**

Know All Men By These Presents, that we,

as Principal, and _____, (Surety), are held and firmly bound unto the City of Kenosha, Wisconsin, a municipal corporation as Obligee in the full and just sum of _____ (\$_____), lawful money of the United States, to the payment of which sum, well and truly to be made, the Principal and Surety bind themselves and each of their heirs, executors, administrators, successors and assigns, jointly and severally, firmly by these presents.

WHEREAS, the Principal has entered into a written Contract with the Obligee for the above project, which Contract is hereby referred to and made a part hereof as fully and to the same extent as if copied at length herein.

NOW, THEREFORE, the condition of this obligation is such, that if the Principal shall faithfully perform said Contract according to its terms, covenants and conditions and shall promptly pay all persons supplying labor or material to the Principal for use in the prosecution of the work under said Contract, then this obligation shall be void; otherwise it shall remain in full force and effect.

Subject to the named Obligee's priority, all persons who have supplied labor or material directly to the Principal for use in the prosecution of the work under said Contract shall have a direct right of action under this Bond.

The Surety's aggregate liability hereunder shall in no event exceed the amount set forth above.

No claim, suit or action shall be brought hereunder after the expiration of one (1) year following the date of City acceptance of the work on said Contract, or one (1) year following expiration of any warranty or guaranty covering the work and materials set forth under said Contract, whichever is longer. If this limitation is made void by any law controlling the construction hereof, such limitation shall be deemed to be amended to equal the minimum period of limitation permitted by such law.

Signed and dated at Kenosha, Wisconsin, this ____ day of _____, _____.

PRINCIPAL

Witness

By:_____

Name:_____

Title:_____

SURETY

Witness

By:_____

Name:_____

Title:_____

PERFORMANCE AND PAYMENT BOND

Examined and approved as to form and execution this ____ day of _____, _____.

By:_____
City Attorney

Print Name:_____

Project No. 02-18
CHANGE ORDER

Project Number: _____

Account Number: _____

Contractor: _____

Date of Common Council Action: _____

CITY and CONTRACTOR agree that the above Contract is amended by (increasing) (decreasing) the amount of the Contract by \$ _____ from \$ _____ to \$ _____ . This amendment shall have the effect of (increasing) (decreasing) (not changing) the date of Project completion from _____ to _____ .

This Change Order is approved by:

CONTRACTOR

CITY OF KENOSHA, MAYOR

By: _____

By: _____

Print Name: _____

Print Name: _____

Date: _____

Date: _____

**THE CITY OF KENOSHA, WISCONSIN
REQUEST FOR PROPOSAL TO REMOVE AND DISPOSE
OF ASBESTOS CONTAINING MATERIAL, RAZE STRUCTURE(S),
AND RESTORE LOT(S)**

Proposal No. 02-18

CONTACT /VENDOR INFORMATION

Firm Name: _____

Firm Address: _____

Phone: _____

Fax: _____

E-Mail: _____